

IN-LB

Inch-Pound Units

SI

International System of Units

Guide for Proportioning Concrete Mixtures with Ground Calcium Carbonate and Other Mineral Fillers

Reported by ACI Committee 211

ACI 211.7R-20



American Concrete Institute
Always advancing



Guide for Proportioning Concrete Mixtures with Ground Calcium Carbonate and Other Mineral Fillers

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide for Proportioning Concrete Mixtures with Ground Calcium Carbonate and Other Mineral Fillers

Reported by ACI Committee 211

Timothy S. Folks,* Chair

William L. Barringer
Katie J. Bartojay
Muhammed P. A. Basheer
James C. Blankenship
Casimir J. Bognacki
Ramon L. Carrasquillo
Bryan R. Castles
Teck L. Chua*
John F. Cook
D. Gene Daniel
Kirk K. Deadrick

Ezgi Wilson, Vice Chair

Bernard J. Eckholdt, III
Joshua J. Edwards
David W. Fowler*
G. Terry Harris
T. J. Harris
Patrick J. Harrison
Richard D. Hill
David L. Hollingsworth
Tarif M. Jaber
Robert S. Jenkins
Joe Kelley

Ed T. McGuire, Secretary

Gary F. Knight*
Eric P. Koehler**
Frank A. Kozeliski
Tyler Ley
John J. Luciano
Darmawan Ludirdja*
Allyn C. Luke
Kevin A. MacPherson
Warren E. McPherson
Karthik H. Obla
H. Cenk Ozvildirim

James S. Pierce
Steven A. Ragan
Royce J. Rhoads
John P. Ries
G. Michael Robinson
James M. Shilstone
Lawrence L. Sutter*
Woodward L. Vogt
Michael A. Whisonant

Subcommittee Members

Yasar Yahia Abualrous
David Anstine*
Dale P. Bentz*
Eric Bosler
James Bury
Zane Bussler
Laurence M. Clodic

Dimitri Feys
Plinio Estuardo Herrera Rodas*
Gene Hightower
Azadeh Hosseinpanahi
Berndt Kanduth
Kenneth G. Kazanis*
Nicolas Ali Libre

Guy Lortie*
Yang Lu
Blaine B. Nye
Bryan L. Petty
Nicholas J. Popoff*
Domenick Thomas Ruttura
Mahmoud Shaaban Sayed Ahmed

Lane G. Shaw*
Paul D. Tennis*
Paul J. Thomas*
James R. Van Acker

*Also members of ACI 211-N.
*Chair of Subcommittee 211-N.

Subcommittee 211-N

Robert Bergman

Joseph A. Daczko

Caroline M. Talbot

John W. Vaughn

Consulting Members

Donald E. Dixon

Said Irvani

James N. Lingscheit

Ava Shypula

ACI Committee Reports, Guides, and Commentaries are intended to provide guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

The use of ground calcium carbonate (GCC) and other mineral fillers can enhance the performance, economy, and sustainability of concrete mixtures. Modifications to the conventional proportioning method in ACI 211.1 are needed to incorporate these materials. This guide describes GCC and dust-of-fracture aggregate mineral fillers, including their properties, characterization, and qualification, and effects on concrete properties and sustainability. Recom-

ACI 211.7R-20 was adopted and published in November 2020

Copyright © 2020, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

recommendations are provided for proportioning concrete mixtures with these materials.

Keywords: aggregate mineral filler; dust-of-fracture; ground calcium carbonate; ground limestone; mixture proportioning; paste volume; powder content; proportioning.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

CHAPTER 2—DEFINITIONS, p. 3

CHAPTER 3—CONSTITUENT MATERIALS, p. 3

- 3.1—Introduction, p. 3
- 3.2—Ground calcium carbonate, p. 3
- 3.3—Dust-of-fracture aggregate mineral filler, p. 3

CHAPTER 4—GROUND CALCIUM CARBONATE AND AGGREGATE MINERAL FILLER CHARACTERIZATION AND QUALIFICATION, p. 3

- 4.1—Introduction, p. 3
- 4.2—Morphology (shape, angularity, and texture), p. 3
- 4.3—Mineralogy, p. 4
- 4.4—Particle size and particle size distribution, p. 5
- 4.5—Deleterious materials, p. 5
- 4.6—Relative density (specific gravity), p. 6

CHAPTER 5—EFFECTS ON CONCRETE PROPERTIES, p. 6

- 5.1—Rheology and workability, p. 6
- 5.2—Placement and finishing characteristics, p. 6
- 5.3—Strength, p. 7
- 5.4—Setting time, p. 7
- 5.5—Durability, p. 7

CHAPTER 6—PROPORTIONING METHODS, p. 9

- 6.1—Basic relationships, p. 9
- 6.2—Modified ACI 211.1 method for ground calcium carbonate, p. 10
- 6.3—Modified ACI 211.1 method for dust-of-fracture aggregate mineral fillers, p. 10

CHAPTER 7—SAMPLE COMPUTATIONS, p. 12

- 7.1—Wet aggregate mineral filler in manufactured sand, p. 12
- 7.2—Dry aggregate mineral filler, p. 13
- 7.3—Adjustment of trial batches, p. 14

CHAPTER 8—SUSTAINABILITY, p. 14

- 8.1—Ground calcium carbonate, p. 14
- 8.2—Dust-of-fracture aggregate mineral fillers, p. 14

CHAPTER 9—REFERENCES, p. 14

- Authored documents, p. 15

CHAPTER 1—INTRODUCTION

This guide provides recommendations for proportioning normalweight concrete with ground calcium carbonate (GCC) and dust-of-fracture aggregate mineral fillers (AMF). It also provides background information on these materials, techniques for their characterization, and their effects on concrete properties; however, it is not intended to be a comprehensive literature review and the reader should conduct trial batches to evaluate specific materials being used and to confirm concrete performance. It is intended to supplement ACI 211.1 and is for materials meeting ASTM C1797. Proportioning methods for GCC and for dust-of-fracture AMF are discussed separately.

Mineral filler is defined as a finely divided mineral product at least 65 percent of which passes the No. 200 (75 μm) sieve. This definition includes the materials addressed herein; namely, GCC as specified in ASTM C1797 and dust-of-fracture AMF from quarried rock as specified in either ASTM C1797 or ASTM C33/C33M.

GCC, also known as ground limestone, is a manufactured fine product composed primarily of calcium carbonate and with particles sized within narrow ranges. GCC has been used successfully in concrete in Europe for decades, either added to the concrete mixture separately from the cement or interground with clinker to form portland-limestone cement (European Committee for Standardization 2009).

Dust-of-fracture AMF is rock dust created during production, processing, or handling of quarried stone. Such material can vary in mineral composition and other physical characteristics, depending on the parent stone from which they are derived, the crushing process, and the washing or air separation process. Dust-of-fracture AMF can be provided as a dry bulk powder meeting ASTM C1797 or as part of manufactured sand as described in ASTM C33/C33M.

This guide does not address precipitated calcium carbonate or material finer than the No. 200 (75 μm) sieve in natural sand, nor the use of limestone as a cement ingredient, which is addressed in ASTM C150/C150M, C595/C595M, and C1157. Although GCC typically falls within the definition of AMF, it is dealt with separately in this guide. It is manufactured under controlled conditions to be a consistent product. Dust-of-fracture AMF consisting primarily of calcium carbonate is not considered GCC.

The aggregate suspension mixture proportioning method described in ACI 211.6T has been used to proportion concrete with GCC and dust-of-fracture AMF.

The use of both GCC and dust-of-fracture AMF can improve the sustainability of concrete production. GCC has a lower embodied energy and lower CO₂ emission during its production than an equivalent mass of portland cement. Dust-of-fracture AMF is typically a by-product of the blasting and crushing of aggregate. This guide can facilitate the use of GCC and aggregate mineral fillers as a means of optimizing the powder content of concrete, thereby increasing sustainability.

Applicability of these materials is not limited to a select class or type of concrete but can be considered for use in a wide variety of applications and production methods. The