

# Guide to Roller- Compacted Concrete Pavements

Reported by ACI Committee 327

ACI 327R-14



American Concrete Institute  
*Always advancing*



## Guide to Roller-Compacted Concrete Pavements

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

**American Concrete Institute**  
3880 Country Club Drive  
Farmington Hills, MI 48331  
Phone: +1.248.848.3700  
Fax: +1.248.848.3701

# Guide to Roller-Compacted Concrete Pavements

Reported by ACI Committee 327

Norbert J. Delatte, Chair

Anthony M. Sorcic, Secretary

Wayne S. Adaska  
J. Howard Allred  
Kerry S. Hall  
Frank Lennox  
H. Celik Ozyildirim  
Ronald L. Peltz

David W. Pittman  
Jan R. Prusinski  
David W. Scott  
Terry W. Sherman  
Matthew W. Singel  
Tim James Smith

Shiraz D. Tayabji  
Christopher R. Tull  
Samuel S. Tyson  
Kevin A. Wentland  
Gergis W. William

The committee would like to recognize the contributions of Dale Harrington, Fares Abou, and Chetan Jazayeri to the source material for this document.

*This guide provides owner-agencies, contractors, materials suppliers, and others with a thorough introduction to roller-compacted concrete (RCC) and its many paving applications. This guide describes RCC and how it works as a paving material, how it compares to concrete pavement, its common uses and benefits, and potential limitations compared to other paving materials. Troubleshooting guidelines are provided, as well as detailed overviews of RCC properties and materials, mixture proportioning, structural design issues, production and construction considerations, and quality control.*

**Keywords:** industrial pavement; inspection and testing; joints; pavement; pavement design; roller-compacted concrete (RCC); RCC mixture proportioning; RCC pavement construction; RCC production.

## CONTENTS

### CHAPTER 1—INTRODUCTION, p. 2

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 2

### CHAPTER 3—KEY ELEMENTS, p. 2

- 3.1—Performance comparison of RCC to conventional concrete pavement, p. 2
- 3.2—Materials and structural performance properties, p. 3

- 3.3—Performance differences between RCC and conventional concrete pavement, p. 4
- 3.4—Benefits of RCC, p. 5
- 3.5—Sustainability, p. 7
- 3.6—Potential limitations, p. 7

### CHAPTER 4—COMMON USES, p. 7

- 4.1—Ports, intermodal facilities, and heavy industrial facilities, p. 7
- 4.2—Light industrial areas, p. 9
- 4.3—Airport service areas, p. 9
- 4.4—Arterial streets, p. 9
- 4.5—Local streets, p. 10
- 4.6—Widening and shoulders, p. 10
- 4.7—Multilayer pavement systems for high-speed uses, p. 11
- 4.8—Logging facilities, composting areas, and storage yards, p. 11

### CHAPTER 5—PROPERTIES AND MATERIALS, p. 11

- 5.1—Roller-compacted concrete engineering properties, p. 11
- 5.2—RCC materials selection, p. 14

### CHAPTER 6—MIXTURE PROPORTIONING, p. 16

- 6.1—Mixture proportioning methodologies, p. 16
- 6.2—Materials considerations in RCC mixture proportioning, p. 17
- 6.3—Methods for mixture proportioning, p. 18

### CHAPTER 7—STRUCTURAL DESIGN, p. 20

- 7.1—Basis for design, p. 20
- 7.2—Subgrade, subbase, and base design, p. 21
- 7.3—Design procedures, p. 21
- 7.4—RCC-PAVE software (PCA procedure), p. 21
- 7.5—PCASE software (USACE procedure), p. 24
- 7.6—ACI design procedures, p. 25

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the information contained herein. ACI disclaims any and all responsibility for the use of the information herein. The Institute shall not be liable for any loss or damage arising therefrom. Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

This ACI document contains requirements that can, at the time of the document's adoption by ACI, be satisfied practically only by use of a patented material, product, process, procedure, or apparatus. ACI does not endorse this technology. The selection of any design methodology or use of any patented technology is at the option of the user.

ACI 327R-14 supersedes ACI 325.10R-95 and was adopted and published February 2015.

Copyright © 2015, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

7.7—American Concrete Pavement Association Street-Pave design procedure, p. 27

7.8—Jointing, p. 27

## CHAPTER 8—PRODUCTION, p. 31

8.1—Handling and storage, p. 32

8.2—Roller-compacted concrete mixing plants, p. 32

8.3—Batching and monitoring, p. 34

8.4—Production levels, p. 34

## CHAPTER 9—CONSTRUCTION, p. 35

9.1—Subgrade, subbase, and base course preparation, p. 35

9.2—Transporting RCC, p. 36

9.3—Trial construction using test strips, p. 36

9.4—Placement, p. 37

9.5—Compaction, p. 38

9.6—Troubleshooting, p. 43

## CHAPTER 10—INSPECTION AND TESTING, p. 45

10.1—General, p. 45

10.2—Preconstruction inspection and testing, p. 45

10.3—Construction inspection and testing, p. 46

10.4—Post-construction inspection and testing, p. 47

## CHAPTER 11—REFERENCES, p. 48

Authored references, p. 49

## APPENDIX—MIXTURE PROPORTIONING BASED ON SOIL COMPACTION, p. 50

A.1—Analogy method, p. 50

### CHAPTER 1—INTRODUCTION

Roller-compacted concrete (RCC) is an economical, fast construction candidate for many pavement applications. Because of its relatively coarse surface, RCC has traditionally been used for pavements carrying heavy loads in low-speed areas. In recent years, however, its use in commercial areas and for local streets and highways is increasing.

This guide is largely based on Harrington et al. (2010). The review panel for the Harrington report was made up largely of ACI Committee 327 members. With the cooperation of the Portland Cement Association, the report was used as the basis for this guide. Extensive changes were made during the committee review, including incorporating material from ACI 325.10R. Additional references and examples have been added.

### CHAPTER 2—NOTATION AND DEFINITIONS

#### 2.1—Notation

$C$  = coefficient relating flexural and compressive strength with values ranging from 9 to 11

$E$  = modulus of elasticity, psi (MPa)

$f_r$  = flexural strength (third-point loading), psi (MPa)

$f_c$  = compressive strength, psi (MPa)

$h$  = slab thickness, in. (mm)

$k$  = modulus of subgrade reaction, psi/in. (MPa/mm)

$\sigma$  = stress, psi (MPa)

$\epsilon$  = strain, in./in. (mm/mm)

#### 2.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://www.concrete.org/Tools/ConcreteTerminology.aspx>. Definitions provided herein complement that source.

**curling**—out-of-plane deformation of the corners, edges, and surface of a pavement from its original shape due to differential temperature within the pavement.

**warping**—out-of-plane deformation of the corners, edges, and surface of a pavement from its original shape due to differential moisture within the pavement.

### CHAPTER 3—KEY ELEMENTS

#### 3.1—Performance comparison of RCC to conventional concrete pavement

Roller-compacted concrete (RCC) gets its name from the heavy vibratory steel drum and rubber-tired rollers used to compact it into its final form. Roller-compacted concrete has similar strength properties and consists of the same basic ingredients as conventional concrete—well-graded aggregates, cementitious materials, and water—but has different mixture proportions. The biggest difference between RCC and conventional concrete mixtures is that RCC has a higher percentage of fine aggregates to allow for tight packing and compaction.

Fresh RCC is stiffer than typical zero-slump conventional concrete, with a consistency that is stiff enough to remain stable under vibratory rollers, yet wet enough to permit adequate mixing and distribution of paste without segregation.

RCC is typically placed with an asphalt-type paver equipped with a standard or high-density screed, followed by a combination of passes with rollers for compaction. Final compaction is usually achieved within 1 hour of mixing. Unlike conventional concrete pavements, RCC pavements are constructed without forms, dowels, or reinforcing steel. Joint sawing is not required, but when sawing is specified, transverse joints are spaced farther apart than with conventional concrete pavements.

RCC pavements are strong, dense, and durable. These characteristics, combined with construction speed and economy, make RCC pavements an excellent alternative for parking and storage areas including port, intermodal, and military facilities; highway shoulders; streets; and highways. RCC can also be used in composite systems as base material.

The use of RCC in public and private applications has been increasing steadily in recent years (Fig. 3.1), particu-




Fig. 3.1—Increasing use of RCC pavements (Pittman and Anderton 2009). (Note: 1 yd<sup>2</sup> = 0.8 m<sup>2</sup>.)