

Design and Construction of Circular Prestressed Concrete Structures with Circumferential Tendons

Reported by ACI Committee 373

James R. Libby
Chairman

Steven R. Close
Secretary

Robert T. Bates
Daniel W. Falconer
G. Craig Freas
Amin Ghali

Charles S. Hanskat
Bradley Harris
Frank J. Heger
Thomas L. Holben

Richard R. Imper
Arthur M. James
Dennis C. Kohl

Gerard J. N. Gu
Hoshi H. Sesswala
Morris Schupack

Associate and Consulting ACI 373 Committee Members who contributed to the development of this report:

Troels Brondum-Nielsen

Ib Falk Jorgensen

Miroslav Vejsada

FOREWORD

This report provides recommendations for the design and construction of circular prestressed concrete structures (commonly referred to as “tanks”) post-tensioned with circumferential tendons. These thin cylindrical shells of either cast-in-place or precast concrete are commonly used for liquid and bulk storage. Vertical post-tensioning is often incorporated in the walls as part of the vertical reinforcement. Recommendations are applicable to circumferential prestressing achieved by post-tensioning tendons placed within the wall or on the exterior surface of the wall. Procedures to prevent corrosion of the prestressing elements are emphasized. The design and construction of dome roofs are also covered.

Keywords: circumferential prestressing; concrete; corrosion resistance; domes; floors; footings; joints; loads; prestressed concrete; prestressed reinforcement; reinforcing steel; roofs; shotcrete; shrinkage; tanks; temperature; tendons; walls.

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

Chapter 1—General, p. 2

- 1.1—Introduction
- 1.2—Objective
- 1.3—Scope
- 1.4—History and development
- 1.5—Definitions
- 1.6—Notation

Chapter 2—Materials, p. 5

- 2.1—Concrete
- 2.2—Shotcrete and filler materials
- 2.3—Admixtures
- 2.4—Grout for bonded tendons
- 2.5—Reinforcement
- 2.6—Tendon systems of tank wall and domes
- 2.7—Waterstop, bearing pad, and filler materials
- 2.8—Epoxy injection
- 2.9—Epoxy adhesives
- 2.10—Coatings for outer surfaces of tank walls and domes

Chapter 3—Design, p. 7

- 3.1—Strength and serviceability
- 3.2—Floor and footing design
- 3.3—Wall design
- 3.4—Roof design

ACI 373R-97 became effective May 8, 1997.
Copyright © 1997, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Chapter 4—Construction procedures, p. 19

- 4.1—Concrete
- 4.2—Shotcrete
- 4.3—Forming
- 4.4—Nonprestressed steel reinforcement
- 4.5—Prestressing tendons
- 4.6—Tolerances
- 4.7—Seismic cables
- 4.8—Waterstops and sealants
- 4.9—Elastomeric bearing pads
- 4.10—Sponge rubber fillers
- 4.11—Cleaning and disinfection

Chapter 5—Acceptance criteria for liquid-tightness of tanks, p. 23

- 5.1—Testing
- 5.2—Acceptance criteria
- 5.3—Visual criteria
- 5.4—Repairs and retesting

Chapter 6—References, p. 23

- 6.1—Recommended references
- 6.2—Cited references

CHAPTER 1—GENERAL**1.1—Introduction**

The design and construction of circular prestressed concrete structures using tendons requires specialized engineering knowledge and experience. This report reflects over four decades of experience in designing and constructing circular prestressed concrete structures with tendons. When designed and constructed by knowledgeable individuals, these structures can be expected to serve for fifty years or more without requiring significant maintenance.

This report is not intended to prevent development or use of new advances in the design and construction of circular prestressed concrete structures. This report is not intended for application to nuclear reactor pressure vessels or cryogenic containment structures.

This report describes current design and construction practices for tanks prestressed with circumferential post-tensioned tendons placed within or on the exterior surface of the wall.

1.2—Objective

The objective of this report is to provide guidance in the design and construction of circular prestressed concrete structures circumferentially prestressed using tendons.

1.3—Scope

The recommendations in this report are intended to supplement the general requirements for reinforced concrete and prestressed concrete design, materials and construction, given in ACI 318, ACI 301 and ACI 350R.

This report is concerned principally with recommendations for circular prestressed concrete structures for liquid storage. The recommendations contained here may also be applied to circular structures containing low-pressure gases, dry materials, chemicals, or other materials capable of creating outward pressures. The recommendations may also

be applied to domed concrete roofs over other types of circular structures. Liquid storage materials include water, wastewater, process liquids, cement slurry, petroleum, and other liquid products. Gas storage materials include gaseous by-products of waste treatment processes and other gaseous material. Dry storage materials include grain, cement, sugar, and other dry granular products.

The recommendations in this report may also be applicable to the repair of tanks using externally applied tendons.

Design and construction recommendations cover the following elements or components of tendon tanks:

- a. Floors
 - Prestressed Concrete
 - Reinforced Concrete
- b. Floor-Wall Joints
 - Hinged
 - Fixed
 - Partially Fixed
 - Unrestrained
 - Changing Restraint
- c. Walls
 - Cast-in-Place Concrete
 - Precast Concrete
- d. Wall-Roof Joints
 - Hinged
 - Fixed
 - Partially Fixed
 - Free
- e. Roofs
 - Concrete Dome Roofs with Prestressed Dome Ring
 - (1) Cast-in-place Concrete.
 - (2) Shotcrete.
 - Other Roofs
 - (1) Prestressed Concrete.
 - (2) Reinforced Concrete.
- f. Wall and Dome Ring Prestressing Methods
 - Circumferential
 - (1) Individual high-strength strands in plastic sheaths or multiple high-strength strand tendons in ducts positioned within the wall and post-tensioned after placement and curing of the wall concrete, as shown in Fig. 1.1.
 - (2) Individual or multiple high-strength strands and, less frequently, individual high-strength bar tendons, prestressed after being positioned on the exterior surface of the wall.
 - Vertical
 - (1) Individual or multiple high-strength strand or individual high-strength bar tendons, enclosed in sheathing or ducts within the wall, anchored near the wall joints at the bottom and top of the wall.
 - (2) Pretensioned high-strength strands in precast panels.

1.4—History and development

The late Eugene Freyssinet, a distinguished French engineer generally regarded as the father of prestressed concrete, was the first to recognize the need to use steels of high quality and strength, stressed to relatively high levels, in