

ACI 439.5R-18

# Guide for the Specification, Manufacture, and Construction Use of Welded Wire Reinforcement

Reported by ACI Committee 439



American Concrete Institute  
*Always advancing*



## Guide for the Specification, Manufacture, and Construction Use of Welded Wire Reinforcement

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

**American Concrete Institute**  
38800 Country Club Drive  
Farmington Hills, MI 48331  
Phone: +1.248.848.3700  
Fax: +1.248.848.3701

[www.concrete.org](http://www.concrete.org)

# Guide for the Specification, Manufacture, and Construction Use of Welded Wire Reinforcement

Reported by ACI Committee 439

Todd R. Hawkinson, Chair

David H. DeValve, Secretary

Paul B. Aubee  
Brian L. Barrows  
Richard H. Birley  
George T. Biro  
Joseph A. Bohinsky  
Domingo J. Carreira  
Louis J. Colarusso  
Salem S. Faza  
Anthony L. Felder

Augusta Gaertner  
William C. Gallenz  
Steven E. Holdsworth  
Allen J. Hulshizer  
Richard Huza  
Josh Ison  
Jason Koehler  
Harry B. Lancelot III  
Kenneth A. Luttrell

LeRoy A. Lutz  
Carl D. Maki  
Mark D. Marvin  
David R. Maul  
David B. McDonald  
Theodore A. Mize  
Conrad Paulson  
Ryan W. Pelter  
Richard A. Ramsey

Harold E. Reed  
Robert J. Reiterman  
Mario E. Rodriguez  
Clifford A. Sabo  
William H. Zehrt Jr.  
Phil J. Zivich

## Consulting Members

Jose Bagg  
Jean-Jacques Braun

Luis E. Garcia  
Kent A. Harries

Douglas D. Lee

*Welded wire reinforcement (WWR) is prefabricated reinforcement consisting of high-strength cold-worked steel wires that are resistance-welded together in square or rectangular grids by continuous automatic welders. This report provides WWR product information, material specifications, and design/detailing recommendations, with an overview of manufacturing, shipping, and construction use in various applications of concrete construction.*

**Keywords:** cast-in-place; cold-working; constructability; deformed reinforcement; mesh; precast; post-tensioned; prestressed; reinforcement; welded wire.

## CONTENTS

### CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

1.1—Introduction, p. 2

1.2—Scope, p. 2

1.3—W and D designations, p. 2

1.4—Product description, p. 2

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 5

2.1—Notation, p. 5

2.2—Definitions, p. 6

### CHAPTER 3—CODES AND STANDARDS, p. 6

3.1—AASHTO, p. 6

3.2—American Concrete Institute, p. 6

3.3—ASTM International, p. 6

### CHAPTER 4—MANUFACTURING PROCESS, p. 6

4.1—Sustainability, p. 6

4.2—Cold-working, p. 6

4.3—Straightening and cutting, p. 7

4.4—Welding, p. 7

4.5—Fabrication, p. 7

4.6—Shipping and handling, p. 9

### CHAPTER 5—CONSTRUCTION APPLICATIONS, p. 9

5.1—Cast-in-place reinforced concrete, p. 9

ACI Committee Reports, Guides, and Commentaries are intended to provide guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 439.5R-18 was adopted and published July 2018.

Copyright © 2018, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 5.2—Precast concrete, p. 10
- 5.3—Prestressed and post-tensioned concrete, p. 11
- 5.4—Tilt-up, p. 12

## CHAPTER 6—CONSTRUCTIBILITY, p. 12

- 6.1—Field welding, p. 12
- 6.2—Field bending, p. 12
- 6.3—Cutting, p. 13
- 6.4—Lap splicing and anchorage, p. 13
- 6.5—Placing tolerances, p. 13
- 6.6—Detailing, p. 13

## CHAPTER 7—REFERENCES, p. 13

- Authored documents, p. 14

## CHAPTER 1—INTRODUCTION AND SCOPE

### 1.1—Introduction

Welded wire reinforcement (WWR) is a prefabricated reinforcement consisting of a series of cold-worked steel wires that are resistance-welded together in square or rectangular grids by continuous automatic welders, and is one of the recognized and established forms of concrete reinforcement. United States patents covering the production of wires welded in this method were first issued in 1901 (Richardson 2000).

Plain or deformed wires, or a combination of both, may be used in WWR. Plain WWR bonds to concrete by mechanical anchorage at each wire intersection, whereas deformed WWR uses surface deformations plus welded intersections for bond and anchorage. The small-diameter, closely-spaced wires provide uniformly distributed reinforcement and effective crack control in footings, slabs, walls, paving, and roofs, in addition to providing shear resistance and confinement in columns, beams, and girders. WWR is provided in special seismic systems where the weld is required to resist stresses in response to confinement, lateral support of longitudinal bars, shear, or other actions in accordance with ACI 318. A wide range of wire sizes and spacings makes it possible to furnish more precise requirements for steel area. The placement of WWR can result in cost savings over non-prefabricated reinforcement. Material savings are obtainable by specifying WWR with high yield strengths as recognized by ACI 318 and ASTM A884/A884M, A1060/A1060M, and A1064/A1064M.

Extensive use was made of WWR in the Empire State Building and World Trade Center Towers in New York, and the Marina City Towers and Standard Oil Building in Chicago. The interstate highway system was built using an extensive amount of WWR in the 1950s and 1960s, and WWR continues to be used today in many transportation structural applications.

### 1.2—Scope

WWR is prefabricated reinforcement consisting of high-strength cold-worked steel wires that are resistance-welded together in square or rectangular grids by continuous automatic welders. This guide provides WWR product information, material specifications, and design/detailing recom-

mendations, with an overview of manufacturing, shipping, and construction use in various applications of concrete construction.

### 1.3—W and D designations

Individual wire (plain and deformed) size designations are based on the cross-sectional area of a given wire. Gauge numbers were used exclusively for many years but were eliminated in the 1970s to reduce the confusion caused from misunderstanding the specified gauge size. The prefixes W and D are used in combination with a number. The letter W designates a plain wire, and the letter D denotes a deformed wire. The number following the letter gives the cross-sectional area in hundredths of a square inch (equivalent millimeter). When describing metric wire, the prefix M is added; MW describes metric plain wire and MD metric deformed wire. The wire spacing in metric WWR is given in millimeters (mm) and the cross-sectional area of the wire is in square millimeters (mm<sup>2</sup>).

For instance, wire designation #4 (W26) would indicate a plain wire with a cross-sectional area of 0.04 in.<sup>2</sup> (26 mm<sup>2</sup>) and a D10 (MD39) wire would indicate a deformed wire with a cross-sectional area of 0.10 in.<sup>2</sup> (65 mm<sup>2</sup>). The size of wires in WWR is designated in the same manner. This system provides many advantages. Because the design professional knows the cross-sectional area of a wire and the spacing, the total cross-sectional area per unit width can easily be determined. For instance, a D6 (MD39) wire on 4 in. (102 mm) centers would provide three wires per 1 ft (305 mm) with a total cross-sectional area of 0.18 in.<sup>2</sup>/ft (381 mm<sup>2</sup>/m).

Many common wire sizes were developed to reduce peak-season lead times and aid in overall plant efficiency. The most readily available wire sizes along with the nominal diameter, area, and weight per unit length are shown in Table 1.3a (plain wire) and Table 1.3b (deformed wire). Plain wire is smooth cold-worked wire from a hot-rolled steel rod into the size or sizes needed for processing into welded sheets. Deformed wire can be indented or raised ribbed cold-worked wire from a hot-rolled rod into the size or sizes needed for processing into welded sheets. Areas of wire should be checked with the most efficient and readily available material from manufacturers. Other wire sizes are available and many manufacturers are able to produce them in 0.0015 in.<sup>2</sup> (1 mm<sup>2</sup>) increments.

### 1.4—Product description

Spacing and size of wire in WWR are identified by style. The following subsections explain the orientation and definition of each part in the makeup of a WWR sheet. When the WWR sheet is designated with uniform or fixed spacing for quotation or order entry, it should be described as follows,

In in-lb units:

6 x 12 – D20.0 x D15.0 (Grade 80) – 78 in. (+12, +6) x  
20 ft (24, 12) – 263.53 lb/sheet – 150 sheets needed

In SI units: