

ACI 544.2R-17

Report on the Measurement of Fresh State Properties and Fiber Dispersion of Fiber- Reinforced Concrete

Reported by ACI Committee 544



American Concrete Institute
Always advancing



Report on the Measurement of Fresh State Properties and Fiber Dispersion of Fiber-Reinforced Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Report on the Measurement of Fresh State Properties and Fiber Dispersion of Fiber-Reinforced Concrete

Reported by ACI Committee 544

Barzin Mobasher*, Chair
Neven Krstulovic-Opara, Secretary

Clifford N. MacDonald, Membership Secretary

Corina-Maria Aldea
Emmanuel K. Attiogbe
Mehdi Bakhshi
Nemkumar Banthia
Joaquim Oliveria Barros
Amir Bonakdar
Amanda C. Bordelon*
Jean-Philippe Charron
Xavier Destree*

Ashish Dubey
Mahmut Ekenel
Liberato Ferrara†
Gregor D. Fischer
Dean P. Forgeron*
Emilio Garcia Taengua
Rishi Gupta*
Heidi Helmink
George C. Hoff

Marco Invernizzi
John Jones
David A. Lange
Michael A. Mahoney
Bruno Massonotti
James Milligan
Nicholas C. Mitchell
Jeffrey I. Novak
Giovanni Pizzari

Klaus Alexander Rieder
Pierre Rossi
Steve Schaeff
Surendra P. Shah
Flavio de Andrade Silva*
Luca Sorelli
Thomas E. West Jr.
Kay Wille
Robert C. Zellers

Consulting Members

P. N. Balaguru
Hiram Price Ball Jr.
Gordon B. Batson

Arnon Bentur
Anderzej M. Brandt
James I. Daniel

S. Jney Freedman
Christian Meyer
Henry J. Molloy

Antoine E. Naaman
Venkataswamy Ramakrishnan

*Members of subcommittee who contributed to the document.

†Chair of the Subcommittee C who developed the document.

The committee would like to thank R. Lequense and M. Porter for their contributions to this report.

This report outlines existing procedures for testing and measuring fresh state performance and fiber dispersion of fiber-reinforced concrete (FRC). As for the former, test methods applicable to both ordinary vibrated FRC and fiber-reinforced self-consolidating concrete (FR-SCC) are reviewed. Methods of nondestructive monitoring of fiber dispersion and orientation in FRC materials and structures are also presented and their pros and cons addressed.

Keywords: fiber dispersion; fiber-reinforced concrete; fiber-reinforced self-consolidating concrete; fresh state performance; nondestructive testing.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 3

CHAPTER 3—FRESH STATE PROPERTIES, p. 3

- 3.1—Sampling, unit weight, yield, and air content, p. 3
- 3.2—Workability and fresh state performance, p. 3
- 3.3—Rheometer tests, p. 8

ACI 544.2R-17 supersedes ACI 544.2R-89 and was adopted and published May 2017.
Copyright © 2017, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 4—FIBER DISPERSION AND ORIENTATION, p. 11

- 4.1—General, p. 11
- 4.2—Destructive method, p. 13
- 4.3—Nondestructive methods, p. 13

CHAPTER 5—CONCLUSION AND SUMMARY OF TEST METHODS, p. 17

CHAPTER 6—REFERENCES, p. 17

Authored documents, p. 18

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

The use of fiber-reinforced concrete (FRC) has evolved from experimental small-scale applications to routine factory and field applications involving the use of tens of millions of cubic yards (meters) each year globally. This has created a need to review existing test methods and, where necessary, develop new methods for determining the fresh and hardened properties of FRC that may be of interest for different engineering applications and may be required at different stages of the design, construction, and maintenance process. These methods are presented in an effort to standardize test procedures and equipment, and also to ensure that test results from different sources can be compared effectively. Whereas it is recognized that the use of procedures and equipment other than those discussed in this report may be employed because of past practices or availability of equipment, the use of standard tests facilitates the comparison of information, promotes the development or broadening of the data base needed to consistently quantify properties of the various types of FRC, and is preferable to nonstandard variants. Such data are also instrumental in developing consistent and internationally recognized design procedures that are based on standard measurements of relevant properties of the material, as well as in formulating reliable performance criteria to classify and accept the material.

Although most of the test methods described in this report were developed initially for steel FRC (SFRC), they are also applicable to concretes reinforced with glass, polymeric, and natural fibers, except where noted.

As the applications of FRC are being expanded and new fibers are introduced to the market, some existing test methods may be found insufficient or unable to provide meaningful data. Therefore, changes can be applied and, in these instances, care is taken in consideration of the issues of repeatability and reproducibility of test results. Repeatability is defined as the variability among replicate test results obtained on the same material within a single laboratory or job site by one operator. Reproducibility refers to variability among test results obtained on the same material in different laboratories, job sites, or both. Regarding reproducibility, users are advised to carefully check the applicability of the test methods, both in lab conditions and in the field, as differences may exist between them.

1.2—Scope

This report applies to the measurement of fresh state and fiber-dispersion properties of both conventionally mixed and placed (vibrated) FRC and fiber-reinforced self-consolidating concrete (FR-SCC) using steel, glass, polymeric carbon, minerals (such as basalt), and natural fibers.

The test methods reported herein are also applicable to ultra-high-performance concrete (UHPC). It is worth remarking that, generally, UHPC does not contain coarse aggregates and is employed in combination with reduced or no amounts of conventional reinforcement. In view of this, care should be taken in assessing the significance of the results, as far as the consistency is concerned, of the volume of material employed in the tests with reference to the heterogeneity scale of the mixture (maximum aggregate size, maximum fiber length). Moreover, passing ability tests, such as the ones reviewed in 3.2.2, may also provide information of limited significance.

This report does not relate to thin class FRC or mortar products produced by the spray-up process. The **Prestressed Concrete Institute (1981)**, **International Glassfibre Reinforced Concrete Association (2016a,b)**, and **ASTM C1116/C1116M** contain recommendations for test methods for these spray-up materials.

Measurement of the properties of fiber-reinforced shotcrete (FSC) that contain the aforementioned fiber types can be performed using the test methods described herein. Special procedures may be required to cast specimens or obtain them from existing structures, as well as to measure properties specific to shotcreting technology. Relevant provisions can be found in **ACI 506.2**.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

c	=	clear gap spacing in L-box test
d_f	=	fiber diameter, in. (mm)
d_{max}	=	maximum diameter of the flow spread in J-ring test, in. (mm)
d_{perp}	=	diameter measured perpendicular to the maximum diameter d_{max} in J-ring test, in. (mm)
l_f	=	fiber length, in. (mm)
R	=	electrical resistivity of fiber-reinforced concrete or fiber-reinforced cementitious composite, ohm
R_m	=	electrical resistivity of the parent plain concrete (matrix), ohm
T_{20} or T_{500}	=	time for the flow spread to reach a diameter of 20 in. (500 mm) in slump flow test, s (in European literature, it has been referenced as T_{50} , where 50 represents the threshold diameter in cm)
T_{final}	=	time for the flow spread to reach the final slump-flow diameter in slump flow test, s
T_V	=	V-funnel flow time, that is, time for the fluid concrete filling the funnel to completely come out once the nozzle of the funnel is opened, s
V_f	=	fiber volume fraction (generally expressed in percent)
γ	=	filling capacity in filling box test

- $\dot{\gamma}$ = shear strain rate, applied to a fluid (in a rheometer test), s^{-1}
- μ = plastic viscosity (in Bingham fluid model), that is, resistance of the fluid (concrete) to flow once the value of the yield stress has been overcome, psi-s (Pa-s)
- σ = electrical conductivity of fiber-reinforced concrete or fiber-reinforced cementitious composite – inverse of R (Siemens)
- $[\sigma_{fiber}]$ = intrinsic conductivity of fiber (Siemens)
- σ_m = electrical resistivity of the parent plain concrete (matrix) – inverse of R_m
- τ = shear stress applied to a fluid (in a rheometer test), psi (Pa)
- τ_0 = yield stress, that is, value of the shear stress that has to be overcome for the fluid (concrete) to start flowing (in Bingham fluid model), psi (Pa)

2.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <https://www.concrete.org/store/productdetail.aspx?ItemID=CT13>. Definitions provided herein complement that source.

dynamic segregation—in a fluid concrete flow, separation of concrete constituents along the flow direction as a function of their specific gravity (heavier constituents tend to lag behind because of insufficient viscosity of the suspending phase to drag them ahead).

fiber aspect ratio—ratio of the length to the diameter of one single fiber or fiber filament.

fiber volume fraction—total fiber volume in a unit volume of concrete (generally expressed as a percentage)

fiber factor—product between the fiber volume fraction and the fiber aspect ratio.

specific surface area—total lateral surface area of a unit mass quantity of a given powder type/granular material or assortment of materials; it depends on the grain size distribution of the particles and on the specific gravity of the material.

static segregation—separation, in a fluid concrete mixture when at rest, of its constituents, as a function of their relative specific gravity (heavier constituents tend to settle because of insufficient yield stress of the suspending phase to hold them in suspension).

CHAPTER 3—FRESH STATE PROPERTIES

3.1—Sampling, unit weight, yield, and air content

To perform the tests described in this chapter to measure the fresh state properties of fiber-reinforced concrete (FRC), the sampling procedures outlined in [ASTM C172/C172M](#) and [EN 12350-1](#) for conventional concrete should be applied.

Similarly, standard test equipment and procedures used for conventional concrete can be employed for determining the air content, yield, and unit weight of FRC ([ASTM C138/C138M](#); [ASTM C173/C173M](#); [ASTM C231/C231M](#); [EN 12350-6](#); [EN 12350-7](#)). Because of the alteration in fiber dispersion and orientation that may result from specimen preparation, the specimen molds should be filled in one lift. Consolidation may result in alteration in fiber dispersion

and orientation. Because of this, samples should be consolidated, when applicable, using external or internal vibration as permitted by [ASTM C31/C31M](#) and [ASTM C192/C192M](#) only when the fiber orientation is not an issue, regarding the performance to be measured. Rodding should not be applied.

3.2—Workability and fresh state performance

3.2.1 Workability tests for conventional vibrated FRC—Workability is defined as that property of freshly mixed concrete or mortar that determines the ease with which it can be mixed, placed, consolidated, and finished to a homogeneous condition. The presence of fibers can result in specific issues that require incorporation into the broad definition of workability, as stated previously and in related measuring techniques. This will be addressed more in this report. Workability is generally assessed using the following simple field tests.

3.2.1.1 Slump test—The slump test ([ASTM C143/C143M](#); [EN 12350-2](#)) is a common, convenient, and inexpensive test, but it may not be a good indicator of workability for FRC. The addition of fibers alters the flow behavior of fresh concrete, especially if no adjustment is made to the mixture composition ([Bayasi and Soroushian 1992](#)). An example is the rearrangement of coarse aggregate grading in consideration of the effects of fibers on the void ratio of the solid particle skeleton ([Ferrara et al. 2007](#)). Therefore, the addition of fibers can lead to a decrease in the measured slump with increasing the fiber factor, which is the product of the fiber volume fraction and the fiber aspect ratio. The rate of change in the measured slump with the fiber factor is directly related to the fiber type ([Mangat and Swamy 1974](#); [Swamy and Mangat 1974](#); [Hughes and Fattuhi 1976](#); [Bayasi and Soroushian 1992](#)). In this respect, because slump is a simple visual measurement, the exact meaning of the measured slump may become questionable if merely compared to that of the mixture with no fibers. The real workability of a FRC can be better evaluated by measuring, for example, the mixing energy required to work the given FRC to the target casting condition ([Chopin et al. 2004](#); [Cazacliu and Roquet 2009](#)). However, once it has been established by preliminary testing that a specific FRC mixture has satisfactory handling and placing characteristics at a given slump, with respect to the intended application, the slump test may be used as a quality control test to monitor the FRC consistency from batch to batch.

3.2.1.2 Vebe test—The Vebe consistometer test, described in [EN 12350-3](#), measures the behavior of concrete subjected to external vibration and is acceptable for determining the workability of concrete placed using vibration, including FRC. It effectively evaluates the ability of FRC to flow under vibration, and helps to assess the ease with which entrapped air can be expelled.

The apparatus is placed on top of a vibrating table. The fresh concrete is compacted into a conical slump mold. The mold is removed and a clear plastic disc is placed on the top of the concrete. The vibrating table is started and the time taken for the transparent disc to be fully in contact with the concrete (the Vebe time), is measured. Similar to the slump test, the