

ACI 548.12-12

**Specification for Bonding Hardened
Concrete and Steel to Hardened
Concrete with an Epoxy Adhesive**

An ACI Standard

Reported by ACI Committee 548



American Concrete Institute®



First Printing
March 2013

American Concrete Institute®
Advancing concrete knowledge

Specification for Bonding Hardened Concrete and Steel to Hardened Concrete with an Epoxy Adhesive

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38801 Country Club Drive
Farmington Hills, MI 48331
U.S.A.
Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN-13: 978-0-87031-807-8
ISBN: 0-87031-807-1

Specification for Bonding Hardened Concrete and Steel to Hardened Concrete with an Epoxy Adhesive

An ACI Standard

Reported by ACI Committee 548

Bradley Nemunaitis
Chair

Mahmoud M. Reda Taha
Secretary

Ashraf I. Ahmed
Mohammad A. Alhassan
Milton D. Anderson
Jacques A. Bertrand
Constantin Bodea
Timothy Bower

David W. Fowler
Robert W. Gaul
Quentin L. Hibben
Albert O. Kaeding
John R. Milliron
Myles A. Murray

Joseph A. Nuciforo Jr.
John R. Robinson
Michael L. Schmidt
Qizhong Sheng
Joe Solomon
Michael M. Spinnler

Michael S. Stenko
Donald P. Tragianese
Wafeek S. Wahby
David White
David P. Whitney
Richard E. Wollmershauser

Consulting Members

Lu Anqi
Craig A. Ballinger
John J. Bartholomew
Shashi P. Bhatnagar
Zhi-Yuan Chen
Inz Lech Czarnacki
Harold (Dan) R. Edwards

Larry J. Farrell
Jack J. Fontana
George Horeczko
David P. Hu
Bert Paul Kreikemans
Deon Kruger
William Lee

Troy Douglas Madeley
Herbert N. Marsh Jr.
Peter Mendis
Peter J. Moss
Yoshihiko Ohama
Kelly M. Page
Jerzy Pietrzykowski

Richard C. Prusinski
Hamid Saadatmanesh
Donald A. Schmidt
Meyer Steinberg
Harold H. Weber Jr.

This specification addresses bonding hardened concrete and steel to hardened concrete with an epoxy adhesive intended for this purpose in ASTM C881. Included are controls for adhesive labeling, storage, handling, mixing and application, surface evaluation and preparation, as well as inspection and quality control.

The materials, processes, quality control measures, and inspections described in this document should be tested, monitored, or performed as applicable only by individuals holding the appropriate ACI certifications or equivalent.

Keywords: adhesive; bonding; construction; epoxy; quality control; repair; safety; steel.

CONTENTS

(mandatory portion follows)

Part 1—General, p. 2

- 1.1—Scope, p. 2
- 1.2—Definitions, p. 2
- 1.3—Referenced standards, p. 2
- 1.4—Submittals, p. 2
- 1.5—Product delivery, storage, and handling, p. 2
- 1.6—Project conditions, p. 2

Part 2—Products, p. 2

- 2.1—Materials, p. 2

Part 3—Execution, p. 3

- 3.1—Preparation, p. 3
- 3.2—Inspection and testing, p. 3
- 3.3—Adhesive mixtures, p. 3
- 3.4—Adhesive application, p. 3
- 3.5—Cleanup, p. 3
- 3.6—Safety, p. 3

(nonmandatory portion follows)

Notes to specifier, p. 4

- General notes, p. 4

ACI 548.12-12 supersedes ACI 503.1-92 and was adopted December 2012 and published March 2013.

Copyright © 2012, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Foreword to checklists, p. 4**Mandatory requirements checklist, p. 5****Optional requirements checklist, p. 5****Submittals checklist, p. 5**

(mandatory portion follows)

PART 1—GENERAL**1.1—Scope**

1.1.1 This specification covers the bonding of hardened concrete and steel to hardened concrete with an epoxy adhesive. This specification does not apply to anchoring dowels or anchors in concrete.

1.1.2 The provisions of this specification shall govern unless otherwise specified in Contract Documents. In case of conflicting requirements, Contract Documents shall govern.

1.1.3 Values in this specification are stated in inch-pound units. A companion specification in SI units is also available.

1.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://terminology.concrete.org>. Definitions provided herein complement that resource.

accepted—determined to be satisfactory by Architect/Engineer.

Architect/Engineer—architect, engineer, architectural firm, engineering firm, or architectural and engineering firm issuing Contract Documents, administering the Work under Contract Documents, or both.

Contract Documents—set of documents supplied by Owner to Contractor as the basis for construction; these documents contain contract forms, contract conditions, specifications, drawings, addenda, and contract changes.

Contractor—person, firm, or entity under contract for construction of Work.

epoxy—thermosetting polymer that is the reaction product of epoxy resin and hardener.

Owner—corporation, association, partnership, individual, public body, or authority for whom Work is constructed.

submittal—document or material provided to Architect/Engineer for review or acceptance.

submit—provide to Architect/Engineer for review.

Work—entire construction or separately identifiable parts thereof required to be furnished under Contract Documents.

1.3—Referenced standards

Standards of ASTM International, International Organization for Standardization, and The Society for Protective Coatings referred to in this standard are listed with serial designation, including year of adoption or revision.

ASTM International

ASTM C881/C881M-10—Standard Specification for Epoxy-Resin-Base Bonding Systems for Concrete

ASTM C1583/C1583M-04—Standard Test Method for Tensile Strength of Concrete Surfaces and the Bond Strength or Tensile Strength of Concrete Repair and Overlay Materials by Direct Tension (Pull-off Method)

ASTM D4263-83(2012)—Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method

The Society for Protective Coatings

VIS 1-2002—Guide and Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning

SP 1-1982(2004)—Surface Preparation Specification No. 1, Solvent Cleaning

SP 2-1982(2004)—Surface Preparation Specification No. 2, Hand Tool Cleaning

SP 3-1982(2004)—Surface Preparation Specification No. 3, Power Tool Cleaning

SP 6/NACE No. 3-2006—Surface Preparation Specification No. 6, Commercial Blast Cleaning

These publications may be obtained from:

ASTM International

100 Barr Harbor Drive

West Conshohocken, PA 19422

www.astm.org

The Society for Protective Coatings (SSPC)

40 24th Street, 5th Floor

Pittsburgh, PA 15222

www.sspc.org

1.4—Submittals

1.4.1 Certifications—Submit manufacturer’s certification verifying conformance to material specifications.

1.4.2 Application control—Submit mixing and application procedures for acceptance prior to use.

1.4.3 Data—Submit technical data sheets and material safety data sheets (MSDS).

1.5—Product delivery, storage, and handling

1.5.1 Delivery of materials—Deliver all materials in sealed containers with labels legible and intact.

1.5.2 Labeling—Clearly mark all containers with the following information:

- Name of manufacturer;
- Manufacturer’s product identification;
- Manufacturer’s instructions for mixing;
- Warning for handling and toxicity; and
- Expiration date and lot number.

1.5.3 Storage of materials—Store materials at temperatures between 40 and 100°F (4.4 and 37.8°C), unless otherwise specified.

1.5.4 Handling of materials—Handle materials in a manner that complies with the MSDS and manufacturer’s recommendations.

1.6—Project conditions

1.6.1 Environmental requirements—Comply with manufacturer’s recommendations regarding environmental conditions under which the epoxy adhesive shall be applied, unless otherwise specified.