

ACI 548.7-04

**Test Load Capacity of Polymer
Concrete Underground
Utility Structures**

Reported by ACI Committee 548



American Concrete Institute®

WITHDRAWN DOCUMENT—This document has been discontinued by ACI as of March 16, 2012, and is available for informational purposes only.



December 2012
printing

American Concrete Institute®
Advancing concrete knowledge

Test Method for Load Capacity of Polymer Concrete Underground Utility Structures

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenue or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
3889 Country Club Drive
Farmington Hills, MI 48331
U.S.A.
Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN 13: 978-0-87031-173-4

Test Method for Load Capacity of Polymer Concrete Underground Utility Structures

Reported by ACI Committee 548

Albert O. Kaeding
Chair

James Maass
Secretary

Milton D. Anderson
J. Christopher Ball
John J. Bartholomew
Constantin Bodea
James T. Dikeou
Floyd E. Dimmick, Sr.
Harold R. Edwards
Garth J. Fallis
Larry J. Farrell
David W. Fowler

Robert W. Gaul
Mohammad S. Khan
Stella L. Marusin
Joseph A. McElroy
Peter Mendis
John R. Milliron
Brad Nemunaitis
Richard C. Prusinski
Mahmoud M. Reda Taha
Suresh Sawant

Donald A. Schmidt
Qizhong Sheng
W. Glenn Smoak
Joe Solomon
Ariel Soriano
George L. Southworth
Michael M. Sprinkel
Michael S. Sterko
Bing Tian
Donald P. Triggianese

Cumaraswamy Vipinandan
R. D. W. Wogt
S. K. Wahby
D. C. Walters
Harold H. Weber, Jr.
David White
David P. Whitney
Tom Wickett
Phillip Y. Yang
Stefan Zmigrodzki

Polymer concrete underground utility structures are used to house outside plant equipment such as electrical distribution line splices, natural gas distribution vaults, water meters, and communication line splices. This test method provides procedures for full-scale testing of three loading conditions similar to vehicle loading that may be experienced in field installations. Results obtained may be used to determine the load-carrying capacity of the structure being tested and provide data for direct comparison between structures of various designs. While this method may be used for an underground structure, it is primarily for use on polymer concrete and polymer concrete/composite structures up to 10 x 10 x 10 ft (3 x 3 x 3 m) in size.

Keywords: handholes; polymer concrete; testing; underground structure; utility structure.

CONTENTS

Section 1—Introduction	p. 1
Section 2—Scope	2
Section 3—Referenced documents	p. 2
Section 4—Terminology	p. 2
Section 5—Significance and use	p. 2
Section 6—Apparatus	p. 3
Section 7—Sampling, test specimens, and test units	p. 3
Section 8—Measurements	p. 3
Section 9—Conditioning	p. 3

Section 10—Procedures, p. 3

Section 11—Calculation or interpretation of results, p. 5

Section 12—Report, p. 5

Appendix, p. 5

SECTION 1—INTRODUCTION

1.1

Testing polymer concrete (PC) underground utility structures as described herein began during the 1970s and the method was included in the *Western Underground Guide 3.6, Nonconcrete Enclosures*, last printed in 1988.* Guide 3.6 was developed by a group of utilities in the western United States to specify underground utility structures made from materials other than portland-cement concrete for their use. The guide includes complete product specifications and addresses four specific enclosure sizes. Its use has spread across the country and the Guide has become a de facto standard. Preparation of this ACI 548.7 document as a stan-

**Western Underground Committee Guide, Nonconcrete Enclosures, WUC 3.6/02/0588, Western Underground Committee.*

ACI 548.7-04 became effective October 27, 2004.
Copyright © 2004, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

standardized, separate test method permits users to specify performance criteria and incorporate testing procedures by reference. It can be used for all underground utility structure sizes currently in use. This document is to be provided to ASTM for consideration as an ASTM test method.

SECTION 2—SCOPE

2.1

This test method provides data to be used in evaluating the load-carrying capacity of polymer concrete (PC) underground utility structures, frequently called handholes, by full-scale testing of the structure. A PC underground structure includes a box, typically without a bottom, and a matching cover (Fig. 1). It may include an extension and, if so, testing shall be of the box and extension together. These test methods are primarily for PC and PC/fiber-reinforced polymer composite enclosures. They may also be used to test underground enclosures of portland-cement concrete or other materials.

2.2

Four procedures are provided:

2.2.1 Vertical load capacity evaluation for the enclosure cover—A concentrated load is applied to the cover to approximate a vehicle wheel load.

2.2.2 Vertical load capacity evaluation for enclosure walls—A concentrated load is applied to the box along its edge to approximate a vehicle wheel as it passes onto or off of the assembly.

2.2.3 Lateral load capacity evaluation for enclosure walls—A uniformly distributed load is applied to the largest box wall to approximate the pressures resulting from earth backfill and the surcharge of a nearby vehicle.

2.2.4 Determination of failure loads for the three defined load conditions as detailed in Section 10.4.

2.3

Each of three specimens shall be tested to the design load and cycled for each procedure. Test the three specimens to failure using Procedure 4 as given in 10.4 for each.

2.4

The design load shall be determined for testing purposes, and all safety factors related to the design load shall be reported.

2.5

Ambient service temperatures affect the performance of the enclosure. These tests shall be conducted at $75 \pm 10^\circ\text{F}$ ($24 \pm 5^\circ\text{C}$) unless another temperature is specified in the request for testing.

2.6

The paired values stated in inch-pound and SI units are usually not exact equivalents. Therefore, each system is to be used independently of the other. Combining values from the two systems may result in nonconformance with this test method.




Fig. 1—Typical cover, box, and extension assembly.

SECTION 3—REFERENCED DOCUMENTS

3.1—ASTM standards

C 857 Standard Practice for Maximum Structural Design Loading for Underground Precast Concrete Utility Structures

SECTION 4—TERMINOLOGY

4.1—Definitions

4.1.1 box—main section of handhole containing a recess to receive the cover.

4.1.2 cover—top surface section of the handhole for closing the top access opening of the box section.

4.1.3 design load—The actual, expected load or loads that an underground utility structure supports in service calculated using ASTM C 857 or other rational design method.

4.1.4 extension—An add-on section that fits to the bottom or to the top of a box and extends its height.

4.1.5 handhole—A complete assembly that is not large enough for a person to enter and providing an access to an underground utility or fixture. The assembly includes a box, a cover, and, if needed, an extension.

4.1.6 underground utility structure—An enclosure for use underground that may be either a handhole or manhole.

SECTION 5—SIGNIFICANCE AND USE

5.1

The results from these test methods provide users with information about the maximum load capacity and deflection characteristics of the enclosure under three static loading conditions. The loading conditions approximate the three most severe conditions of loading encountered in actual installations and allow users to compare alternative materials and constructions to determine relative structural performance in service.

5.2

Actual loads and load footprints vary in service.

5.3

This test method provides information under repetitive static load conditions and does not provide any determination of resistance to impact, creep, or fatigue.