

An ACI Standard

Specification for Type EM (Epoxy Multi-Layer) Polymer Overlay for Bridge and Parking Garage Decks

Reported by ACI Committee 548

ACI 548.8-19



American Concrete Institute
Always advancing



Specification for Type EM (Epoxy Multi-Layer) Polymer Overlay for Bridge and Parking Garage Decks

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint, and may be obtained by contacting ACI.

ACI codes, specifications, and practices are made available in the ACI Collection of Concrete Codes, Specifications, and Practices. The online subscription to the ACI Collection is always updated, and includes current and historical versions of ACI's codes and specifications (in both inch-pound and SI units) plus new titles as they are published. The ACI Collection is also available as an eight-volume set of books and a USB drive.

American Concrete Institute
3830 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Specification for Type EM (Epoxy Multi-Layer) Polymer Overlay for Bridge and Parking Garage Decks

An ACI Standard

Reported by ACI Committee 548

Mahmoud M. Reda Taha, Chair

Ashraf I. Ahmed
Mohammad A. Alhassan
Jacques A. Bertrand
Constantin Bodea
Chris Davis
James T. Dikeou*

Don Edwards
David W. Fowler
Quentin L. Hibben
Albert O. Kaeding
Jay Lee
John R. Milliron

Myles A. Murray*
Bradley Nemunaitis
Joseph A. Nuciforo Jr.
John R. Robinson
Michael L. Schmitt
Joseph R. Solomon

Michael M. Sprinkel
Michael S. Stenko
Donald P. Tragianese
Wafeek S. Wahby
David White

*Deceased

Consulting Member

Milton D. Anderson
Lu Anqi
Craig A. Ballinger
John J. Bartholomew
Shashi P. Bhatnagar
Jerry D. Byrne
Zhi-Yuan Chen

Lech Czarnecki
Harold (Dan) R. Edwards
Larry J. Farrell
George Horeczko
David P. Hu
Bert Paul Kriekemars
Deon Kruger

William Lee
Troy D. Madeley
Henry N. Marsh Jr.
Peter Mendis
Peter J. Moss
Yoshihiko Ohama
Kelly M. Page

Hamid Saadatmanesh
Donald A. Schmidt
Meyer Steinberg
Harold H. Weber Jr.

This Specification covers epoxy multi-layer (EM) polymer overlay for bridge and parking garage decks. Type EM polymer overlay incorporates a low-modulus epoxy binder and selected aggregate to produce a flexible, skid-resistant, and low-permeability overlay. The overlay may be used for both new construction and rehabilitation of existing structures. The overlay is placed by applying the neat epoxy binder to the surface and broadcasting aggregate. This Specification includes requirements for epoxy resin, aggregates, storage and handling, surface preparation, surface profile, mixing, placement, quality control, and quality assurance.

Keywords: bridge decks; epoxy; multi-layer; parking garage decks; polymer overlay; surface preparation; low permeability.

CONTENTS

SECTION 1—GENERAL, p. 2

- 1.1—Scope, p. 2
- 1.2—Interpretation, p. 2
- 1.3—Definitions, p. 2
- 1.4—Reference standards, p. 2
- 1.5—Submittals, p. 3
- 1.6—Project conditions, p. 3
- 1.7—Labeling, storage, and handling of materials, p. 3

1.8—Quality assurance and quality control acceptance of work, p. 3

SECTION 2—PRODUCTS, p. 3

- 2.1—Epoxy binder, p. 3
- 2.2—Aggregate, p. 3

SECTION 3—EXECUTION, p. 4

- 3.1—Procedure qualification, p. 4
- 3.2—Surface preparation, p. 4
- 3.3—Mixing epoxy binder, p. 4
- 3.4—Overlay application, p. 5
- 3.5—Curing, p. 5
- 3.6—Excess aggregate removal, p. 5
- 3.7—Joints, p. 5
- 3.8—Open to traffic, p. 5

ACI 548.8-19 supersedes ACI 548.8-07, became effective May 31, 2019, and was published August 2019.

Copyright © 2019, American Concrete Institute

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

NOTES TO SPECIFIER (nonmandatory), p. 5

General notes, p. 5

Foreword to checklists, p. 6

MANDATORY REQUIREMENTS CHECKLIST, p. 7**SUBMITTAL CHECKLIST, p. 7****SECTION 1—GENERAL****1.1—Scope**

1.1.1 This Specification covers materials and procedures for constructing a multi-layer, low-permeability epoxy polymer (Type EM) overlay for new construction and rehabilitation of bridge and parking garage decks, using mechanical, semi-automated, and fully-automated methods. Type EM polymer overlay incorporates a low-modulus, epoxy binder and selected aggregate to produce a flexible, skid-resistant, and low-permeability overlay. This Specification includes requirements for epoxy resin components, aggregates, storage and handling, surface preparation, surface profile, mixing, placement, quality control, and quality assurance.

1.1.2 This Specification supplements the contract documents and provides requirements for the contractor.

1.1.3 This Specification governs for construction within its scope, except the contract documents govern if there is a conflict.

1.1.4 This Specification governs if there is a conflict with its referenced standards.

1.1.5 The Contractor is permitted to submit written alternatives to any provisions in the Specification.

1.1.6 Do not use this Specification in conjunction with ACI 301 or ACI 350.5.

1.1.7 Ignore provisions of the Specification that are not applicable to the Work.

1.1.8 Values in this Specification are stated in both-pound units. A companion specification in SI units is also available.

1.1.9 The Notes to the Specifier are not part of this Specification.

1.2—Interpretation

1.2.1 Unless otherwise explicitly stated, this Specification shall be interpreted using the following principles:

1.2.1.1 Interpret this Specification consistent with the plain meaning of the words and terms used.

1.2.1.2 Definitions provided in this Specification govern over the definitions of the same or similar words or terms found elsewhere.

1.2.1.3 Whenever possible, interpret this Specification so that its provisions are in harmony and do not conflict.

1.2.1.4 Headings are part of this Specification and are intended to identify the scope of the provision or sections that follow. If there is a difference in meaning or implication between the text of a provision and a heading, the meaning of the text governs.

1.2.1.5 Where a provision of this Specification involves two or more items, conditions, requirements, or events

connected by the conjunctions “and” or “or,” interpret the conjunction as follows:

“and” indicates that all of the connected items, conditions, requirements, or events apply

“or” indicates that the connected items, conditions, requirements, or events apply singularly

1.2.1.6 The use of the verbs “may” or “will” indicates that the Specification provision is for information to the contractor.

1.2.1.7 The phrase “unless otherwise specified” means the specifier included an alternative to the default requirements in Contract Documents.

1.2.1.8 The phrase “if specified” means the specifier may have included a requirement in Contract Documents for which there is no default requirements in this Specification.

1.3—Definitions

broadcast—to scatter over a wide area by hand or mechanical method.

cure time—time interval after mixing in which a polymer concrete system develops the required strength.

fully automated—metering, mixing of epoxy resin components with pumps and static mixing equipment and application of epoxy resin without the use of squeegees and broadcasting of aggregate

gel time—time interval after mixing that a liquid material exhibits a significant viscosity increase.

mechanical—mixing of epoxy resin components with drills and mixing paddles and spreading with squeegees and broadcasting of aggregate.

semi-automated—metering, mixing of epoxy resin components with pumps and static mixing equipment, and spreading of the epoxy resin with squeegees and broadcasting of aggregate.

1.4—Reference standards**1.4.1 AASHTO Standards**

AASHTO T 277-15—Standard Method of Test for Electrical Indication of Concrete’s Ability to Resist Chloride Ion Penetration

1.4.2 ASTM Standards

ASTM C566-13—Standard Test Method for Total Evaporable Moisture Content of Aggregate by Drying

ASTM C579-01(2012)—Standard Test Methods for Compressive Strength of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes

ASTM C778-13—Standard Specification for Standard Sand
ASTM C881/C881M-15—Standard Specification for Epoxy-Resin-Base Bonding Systems for Concrete

ASTM C884/C884M-98(2010)—Standard Test Method for Thermal Compatibility between Concrete and an Epoxy Resin Overlay

ASTM C1202-12—Standard Test Method for Electrical Indication of Concrete’s Ability to Resist Chloride Ion Penetration

ASTM C1583/C1583M-13—Standard Test Method for Tensile Strength of Concrete Surfaces and the Bond Strength