

IN-LB

Inch-Pound Units

SI

International System of Units

Guide to Design and Construction of Externally Bonded Fabric-Reinforced Cementitious Matrix (FRCM) and Steel-Reinforced Grout (SRG) Systems for Repair and Strengthening Masonry Structures

Reported by ACI Committee 549

ACI 549.6R-20



American Concrete Institute
Always advancing



Guide to Design and Construction of Externally Bonded Fabric-Reinforced Cementitious Matrix (FRCM) and Steel-Reinforced Grout (SRG) Systems for Repair and Strengthening Masonry Structures

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
3800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide to Design and Construction of Externally Bonded Fabric-Reinforced Cementitious Matrix (FRCM) and Steel-Reinforced Grout (SRG) Systems for Repair and Strengthening Masonry Structures

Prepared by the ACI 549-L – RILEM TC 250 Liaison Subcommittee

Gianmarco de Felice*, Chair

Christian Carloni*, Secretary

Reported by ACI Committee 549

Antonio Nanni*, Chair

Corina-Maria Malena, Secretary

Nemkumar Banthia
Dale P. Bentz
Christian Carloni*
Paolo Casadei*
Gianmarco de Felice*
Michael E. Driver

Ashish Dubey
Usama A. Ebead
Mahmut Ekenel
Brad L. Erickson
Garth J. Fallis
Barzin Mobasher

Hani H. Nassif
James E. Patterson
Bekir Yilmaz Pekmezci
Arif C. Pinar
Mary K. Pland
Sreemanta P. Shah

Yixin Shao
Lesley H. Sneed
J. Gustavo Tumialan

Consulting Members

Gordon B. Batson
James I. Daniel

John Jones
Antoine E. Naaman

Paul Nedwell
P. Paramasivam

Parviz Soroushian

ACI 549-L – RILEM TC 250 Liaison Subcommittee

Maria Antonietta Aiello*
Marco Corradi*
Tommaso D'Antino
Stefano De Santis*

Emmanuel G. L. G. G. G.
Arkadiusz Lewicki*
Gian Piero Liguola*
Paulo B. Lourenço

Marialaura Malena*
Claudio Mazzotti*
Daniel Oliveira
Andrea Prota*

Thanasis C. Triantafillou
Maria Rosa Valluzzi*

The committee would like to thank the following for their contributions to this guide: A. Bellini*, A. Cascardi*, G. Castorini*, M. L. Ludovico*, H. Hadad*, P. Meriggi*, C. Papanicolaou*, G. Thermou*, G. Tassinelli*

*ACI members, RILEM members, and contributors who prepared this report.

ACI Committee Reports, Guides, and Commentaries are intended to provide guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

This guide addresses the use of externally bonded (EB) fabric-reinforced cementitious matrix (FRCM) and steel-reinforced grout (SRG) systems for repair and strengthening of masonry structures. FRCM and SRG are composite materials composed of a reinforcement in the form of open fabric bonded on the masonry surface through an inorganic matrix. In particular, the structural reinforcement for FRCM consists of an open grid fabric of continuous fibers made of carbon, alkali-resistant (AR) glass, polyparaphenylene benzobisoxazole (PBO), aramid, or basalt fibers, while SRG systems use steel cords of twisted wires arranged to form a unidirectional fabric. The matrixes are typically based on combinations of portland cement, silica fume, and fly ash as the binder (cement-based), or on natural hydraulic lime (lime-based), or even on geopolymer (geopolymer-based). FRCM and SRG systems represent an alternative to traditional strengthening techniques such as steel tie

ACI 549.6R-20 was adopted and published November 2020.

Copyright © 2020, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

rods, section enlargement, or even fiber-reinforced polymer (FRP) systems. FRCM and SRG systems can be used for various structural purposes—for example, they are used to: 1) increase the load-bearing capacity of structural members; 2) improve the seismic capacity of buildings; 3) counteract specific incipient or already developed damage; 4) limit opening of cracks; and 5) strengthen local weaknesses. Based on experimental research, analytical work, and field applications, this guide provides the recommendations for the design and structural evaluation of FRCM and SRG systems according to both American and European existing regulations and guidelines.

Keywords: composites; confinement; earthquake-resistant; fabric-reinforced cementitious matrix; lap splices; mortar matrix; steel-reinforced grout; structural analysis; structural design.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3

CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

- 2.1—Notation, p. 3
- 2.2—Definitions, p. 10

CHAPTER 3—SCIENTIFIC BACKGROUND, p. 10

- 3.1—FRCM/SRG systems characteristics, p. 10
- 3.2—Historical development, p. 11
- 3.3—FRCM/SRG mechanical properties, p. 11
- 3.4—Strengthening of masonry, p. 15
- 3.5—Examples of commercially available FRCM/SRG systems, p. 23

CHAPTER 4—FIELD APPLICATION EXAMPLES, p. 24

- 4.1—Application procedure, p. 25
- 4.2—Strengthening of masonry walls, p. 28
- 4.3—Strengthening of masonry arches and vaults, p. 32
- 4.4—Confinement of masonry columns, p. 37

CHAPTER 5—MATERIAL CHARACTERISTICS AND SYSTEM QUALIFICATION, p. 39

- 5.1—Experimental tests for material characterization, p. 39
- 5.2—Determination of qualification parameters, p. 44

CHAPTER 6—GENERAL DESIGN CONSIDERATIONS, p. 46

- 6.1—Design philosophy, p. 47
- 6.2—Strength and limits, p. 48
- 6.3—FRCM/SRG design properties, p. 48
- 6.4—Design supported by testing, p. 49

CHAPTER 7—OUT-OF-PLANE STRENGTHENING OF WALLS, p. 49

- 7.1—Out-of-plane flexural strengthening, p. 49
- 7.2—Crowning-beams and ties, p. 52

CHAPTER 8—IN-PLANE STRENGTHENING OF WALLS, p. 56

- 8.1—Introduction, p. 56

8.2—Design assumptions, p. 56

8.3—In-plane shear capacity of unreinforced masonry walls (URM), p. 58

8.4—In-plane shear capacity of FRCM/SRG-strengthened masonry walls, p. 59

8.5—In-plane flexural strength of FRCM/SRG-strengthened masonry walls, p. 60

8.6—Experimental validation, p. 61

CHAPTER 9—CONFINEMENT OF COLUMNS, p. 62

9.1—Introduction, p. 62

9.2—Design rules, p. 62

9.3—Design axial strength, p. 64

9.4—Design limitations, p. 65

9.5—Experimental validation, p. 65

CHAPTER 10—STRENGTHENING OF VAULTS, p. 65

10.1—Introduction, p. 65

10.2—Design assumptions, p. 66

10.3—Design by kinematic approach, p. 67

10.4—Design by static approach, p. 70

CHAPTER 11—REINFORCEMENT DETAILS, DRAWINGS, SPECIFICATIONS, AND SUBMITTALS, p. 72

11.1—Bond and delamination, p. 72

11.2—Tensile connectors against leaf/wythe separation, p. 73

11.3—Engineering requirements, p. 73

11.4—Drawings and specifications, p. 73

11.5—Submittals, p. 73

11.6—Quality control, p. 73

11.7—Inspection and assessment, p. 74

CHAPTER 12—DESIGN EXAMPLES, p. 74

CHAPTER 13—REFERENCES, p. 151

Authored documents, p. 151

CHAPTER 1—INTRODUCTION

1.1—Introduction

Fabric-reinforced cementitious matrix (FRCM) and steel-reinforced grout (SRG) composites have recently emerged as a viable technology for repairing and strengthening masonry structures, as they offer important advantages in terms of tensile strength, weight, and thickness (Triantafyllou and Papanicolaou 2005; Barton et al. 2005; Prota et al. 2006; Papanicolaou et al. 2007a; Borri et al. 2009a; Nanni 2012; De Luca and Tumialan 2014; de Felice et al. 2014). The structural performance of FRCM/SRG, when externally bonded (EB) to masonry, relies on the capacity of the reinforcement to bear the tensile stress, while the compressive stress is carried by the masonry structural element. FRCM/SRG systems prove to be competitive for repair, retrofit, and rehabilitation of existing masonry structures

when compared to conventional techniques, such as steel tie rods, section enlargement, and reinforced concrete overlays. When compared to fiber-reinforced polymer (FRP) systems, the substitution of the polymeric matrix with an inorganic one overcomes some of the limitations of FRP in terms of compatibility with the masonry substrate, resistance at high temperature, vapor permeability, application on wet surfaces, and removability (possibility of being removed without significant damage in the original substrate). The advantages of FRCM/SRG composites, especially when lime-based mortars are used as matrixes, make them suitable for the rehabilitation of historic structures and architectural heritage (Valluzzi et al. 2014b).

In FRCM/SRG composites, the matrix has both roles to cover and protect the reinforcement that is embedded inside, and to ensure the stress transfer between the masonry substrate and the reinforcement. The matrix is generally made of fine-grained mortar with a combination of portland cement, silica fume, fly ash, ground-granulated blast furnace slag, and natural pozzolan as the binder (cement-based), or natural hydraulic lime (lime-based), or even of geopolymers (geopolymer-based). Organic components could be also added in the matrix to improve the bond and the workability; however, they may induce a decrease in vapor permeability and fire resistance.

The fabric consists of an open grid of yarns made of carbon, alkali-resistant (AR) glass, basalt, aramid or poly-p-aramid benzobisoxazole (PBO)-continuous fibers. Fabrics are usually arranged in two directions by means of weaving, knitting tufting, or braiding. The spacing of the yarns needs to allow the inorganic matrix to penetrate the fabric. When the reinforcement consists of steel cords or twisted wires arranged to form a unidirectional fabric the technology is known as SRG (Casadei et al. 2002; Carbon et al. 2005; Huang et al. 2005; Borri et al. 2011; De Santis and de Felice 2015a).

Based on the outcomes of the scientific research performed in the past 15 years, the structural members strengthened with FRCM and with SRG composite show analogous behavior. Therefore, the same approach can be used for the design of EB reinforcements with FRCM and SRG systems. On the other hand, some differences exist concerning durability and performance under elevated temperatures; the research on these issues is ongoing.

This guide is the outcome of the work carried out by the ACI 549-Liaison Committee between ACI Committee 549, “Thin Reinforced Cementitious Products and Ferro-cement,” and RILEM Committee TC 250-CSM (de Felice et al. 2018a), “Composites for Sustainable Strengthening of Masonry.” The joint committee provides guidance for the design of FRCM and SRG systems for repair and strengthening of masonry structures, according to both American and European approaches. The sections dealing with scientific background (Chapter 3); field application examples (Chapter 4); general design considerations (Chapter 6); and reinforcement details and drawing specification (Chapter 11) are common to the two approaches (American and European). To the contrary, a two-column format is used in the other



chapters dealing with material characteristics and systems qualification (Chapter 5), and with the design rules for out-of-plane strengthening of walls (Chapter 7), for the in-plane strengthening of walls (Chapter 8), for the confinement of columns (Chapter 9), and for the strengthening of vaults (Chapter 10), and with design examples (Chapter 12). The left column, identified by the ACI logo, is written according to the ASTM standards, the International Code Council-Evaluation Services (ICC-ES) Acceptance Criteria AC408, and ACI 549.4R. The right column, identified by the RILEM logo, is written according to the European Committee for Standardization (CEN) EN standards, RILEM TC 232-EDT (Brameshuber 2016), and RILEM TC 250-CSM (de Felice et al. 2018a) recommendations. Despite a number of names and acronyms (including TRM and FRM) used in the scientific literature when referring to externally bonded (EB) mortar-based reinforcements, as clarified in the historical development section of this guide (3.2), only FRCM and SRG are used in this guide.

1.2—Scope

Note that this guide is based on the most recent knowledge and interactions with other technical organizations, such as the working group of the Italian National Research Council (CNR), which was established for the development of guidelines for both the qualification of FRCM/SRG composites and the design of FRCM/SRG-strengthened structures. However, the scientific research on the structural behavior of FRCM/SRG-reinforced masonry structures and on design methods is still under development. Based on current knowledge, conservative values are proposed for the safety coefficients included in the design algorithms provided in this guide. The design algorithms may be subject to future update or revision, and less conservative values, or differentiated values for specific materials or applications, may be assigned to tuning coefficients, strength reduction factors, and partial coefficients based on validation with wider databases of experimental data.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

			
$A_e =$	area of the effectively confined masonry, in. ² (mm ²)	$A_e =$	area of the effectively confined masonry, mm ² (in. ²)
$A_f =$	area of the fabric effective in shear, in. ² (mm ²)	$A_f =$	area of the fabric effective in shear, mm ² (in. ²)
$A_m =$	cross-sectional area of the column, in. ² (mm ²)	$A_m =$	cross-sectional area of the column, mm ² (in. ²)
$A_s =$	area of the steel reinforcement, in. ² (mm ²)	$A_s =$	area of the steel reinforcement, mm ² (in. ²)