

IN-LB

Inch-Pound Units

SI

International System of Units

Post-Installed Mechanical Anchors in Concrete— Qualification Requirements and Commentary

Reported by ACI Committee 355

ACI CODE-355.2-24



American Concrete Institute
Always advancing



Post-Installed Mechanical Anchors in Concrete—Qualification Requirements and Commentary

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. Despite these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations regarding health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

ACI documents are written via a consensus-based process. The characteristics of ACI technical committee operations include:

- (a) Open committee membership
- (b) Balance/lack of dominance
- (c) Coordination and harmonization of information
- (d) Transparency of committee activities to public
- (e) Consideration of views and objections
- (f) Resolution through consensus process

The technical committee documents of the American Concrete Institute represent the consensus of the committee and ACI. Technical committee members are individuals who volunteer their services to ACI and specific technical committees.

American Concrete Institute
8800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Post-Installed Mechanical Anchors in Concrete— Qualification Requirements and Commentary

An ACI Standard

Reported by ACI Committee 355

Andra Hoermann-Gast, Chair

Jay Dorst, Vice Chair

F. Silva, Vice Chair

Neal S. Anderson
Jacques A. Bertrand
T. J. Bland
Rachel Chicchi Cross
Rolf Eligehausen
Werner A. F. Fuchs

Brian C. Gerber
Jan Erich Hofmann
Chiwan Wayne Hsieh
Amy S. Koleczak
Thomas A. Kolden
Anthony J. Lamanna

Giovanni Muciaccia
Daniel T. Mullins
John ...
Marina B. Rodriguez
Milton Rodriguez
Peter ... Schillinger

Howard Silverman
Luke Tavernit
Jason H. Wagner
Roman Wan-Wendner

Consulting members

Peter J. Carrato
Ronald A. Cook
Branko Galunic

Neil M. Hawkins
Christopher La Vine
Nam-Ho Lee

Lee W. Mattis
Robert R. McGlohn
Donald F. Meinheit

Conrad Paulson
Dan R. Stoppenhagen

Note: Special acknowledgment is given to K. McBride for his contribution to this Code.

This Code prescribes testing programs and evaluation requirements for post-installed mechanical anchors intended for use in structural applications addressed by ACI CODE-318 and subjected to static or seismic loads in tension, shear, or combined tension and shear. Criteria are prescribed for determining whether anchors are acceptable for use in uncracked concrete only, or in cracked as well as uncracked concrete. Performance categories for anchors are established, as are the criteria for assigning anchors to each category. The anchor performance categories are used by ACI CODE-318 to assign capacity reduction factors and other design parameters.

Keywords: anchors; cracked concrete; expansion anchors; fasteners; mechanical anchors; post-installed anchors; screw anchors; undercut anchors.

CONTENTS

CHAPTER 1—GENERAL, p. 4

- 1.1—Scope, p. 4
- 1.2—General, p. 4
- 1.3—Purpose, p. 4
- 1.4—Applicability, p. 4
- 1.5—Interpretation, p. 5

CHAPTER 2—NOTATION AND DEFINITIONS, p. 6

- 2.1—Notation, p. 6
- 2.2—Definitions, p. 10

ACI CODE-355.2-24 supersedes ACI 355.2-22 and was approved by the ACI Standards Board for publication June 2024, and published November 2024. This Code was first published in 2001 and revised in 2004, 2007, 2019, and 2022.

Copyright © 2024, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 3—REFERENCED STANDARDS, p. 13**CHAPTER 4—SIGNIFICANCE AND USE, p. 14**

4.1, p. 14

CHAPTER 5—GENERAL REQUIREMENTS, p. 18

5.1—Testing sequence and required tests for qualification, p. 18

5.2—Test samples, p. 29

5.3—Testing by independent testing and evaluation agency and by manufacturer, p. 29

5.4—Changes to product, p. 30

CHAPTER 6—REQUIREMENTS FOR TEST SPECIMENS, INSTALLING ANCHORS, AND CONDUCTING TESTS, p. 31

6.1—Concrete for test members, p. 31

6.2—Anchor installation, p. 31

6.3—Test methods, p. 39

6.4—Tests in cracked concrete, p. 39

6.5—General requirements for anchor behavior, p. 40

CHAPTER 7—REQUIREMENTS FOR ANCHOR IDENTIFICATION, p. 44

7.1—Determination of critical characteristics of anchors, p. 44

7.2—Specification of critical characteristics of anchors, p. 44

7.3—Verification of conformance to drawings and specifications, p. 44

CHAPTER 8—REFERENCE TESTS, p. 47

8.1—Purpose, p. 47

8.2—Reference tension tests for single anchors without spacing and edge effects (Table 5.1a, Tests 1, 2, and 3, or Table 5.1b, Tests 1, 2, 3, 4, and 5), p. 47

8.3—Required calculations using results of reference tests, p. 48

CHAPTER 9—RELIABILITY TESTS, p. 50

9.1—Purpose, p. 50

9.2—Reliability tests using reduced installation effort (Table 5.1a, Test 4, and Table 5.1b, Test 6), p. 50

9.3—Reliability in low-strength concrete with large drill bit (Table 5.1a, Test 5, and Table 5.1b, Test 7), p. 51

9.4—Reliability in high-strength concrete with small drill bit (Table 5.1a, Test 6, and Table 5.1b, Test 8), p. 51

9.5—Reliability under repeated load (Table 5.1a, Test 7, and Table 5.1b, Test 10 for screw anchors), p. 51

9.6—Reliability in cracked concrete where crack width is cycled (Table 5.1b, Test 9), p. 53

9.7—Reliability of screw anchors for brittle failure (Table 5.1a, Test 8, and Table 5.1b, Test 11), p. 55

9.8—Reliability tests of screw anchors to setting method (Table 5.1a, Tests 9, 10, and 11, or Table 5.1b, Tests 12, 13, and 14), p. 63

CHAPTER 10—SERVICE-CONDITION TESTS, p. 67

10.1—Purpose, p. 67

10.2—Service-condition tension test with single anchor and with two edges (corner) (Table 5.1a, Test 12, and Table 5.1b, Test 15), p. 67

10.3—Service-condition test at minimum edge distance and minimum spacing (Table 5.1a, Test 13, and Table 5.1b, Test 16), p. 68

10.4—Service-condition shear test for single anchors without spacing and edge effects (Table 5.1a, Test 14, and Table 5.1b, Test 17), p. 71

10.5—Torque tests (Table 5.1a, Test 15, and Table 5.1b, Test 18) – Optional, p. 71

10.6—Seismic tests (Table 5.1b, Tests 3a, 4a, 17, 19, 20, and 21), p. 72

10.7—Assessment of seismic tests, p. 72

10.8—Determination of seismic characteristic strengths, p. 98

10.9—Reporting of seismic attributes, p. 100

CHAPTER 11—ESTABLISHING ANCHOR CATEGORIES, p. 101

11.1, p. 101

11.2, p. 101

CHAPTER 12—PRESENTING ANCHOR DATA, p. 102

12.1—Data analysis, p. 102

12.2—Format of data sheet, p. 102

12.3—General requirements, p. 102

12.4—Contents of evaluation report, p. 102

CHAPTER 13—REQUIREMENTS FOR INDEPENDENT TESTING AND EVALUATION AGENCY, p. 105

13.1, p. 105

13.2, p. 105

CHAPTER 14—COMMENTARY REFERENCES, p. 106

Authored documents, p. 106

APPENDIX A1—REQUIREMENTS FOR NORMALIZATION OF RESULTS, p. 107

A1.1—Normalization of capacities to take account of concrete and steel strengths, p. 107

A1.2—Concrete breakout or splitting failure, p. 107

A1.3—Pullout and pull-through failure, p. 107

A1.4—Steel failure, p. 107

APPENDIX A2—REQUIREMENTS FOR ESTABLISHING CHARACTERISTIC CAPACITIES, p. 108

A2.1—Scope, p. 108

A2.2—Procedure, p. 108

APPENDIX A3—REQUIREMENTS FOR TEST MEMBERS, p. 109

- A3.1—Tests in uncracked concrete, p. 109
- A3.2—Tests in cracked concrete, p. 109
- A3.3—Casting and curing of test members, p. 110

APPENDIX B—EXAMPLE OF EVALUATION OF AN EXPANSION ANCHOR FOR USE IN UNCRACKED CONCRETE, p. 111

- B1—Anchor specifications, p. 111
- B2—Test results, p. 111
- B3—Evaluation, p. 112
- B4—Establishing anchor category, p. 117
- B5—Report of anchor data, p. 118

COMMENTARY

CHAPTER 1—GENERAL

1.1—Scope

This Code prescribes testing and evaluation requirements for post-installed mechanical anchors intended for use in concrete designed under the provisions of **ACI CODE-318**. Criteria are prescribed to determine whether anchors are acceptable for use in uncracked concrete only, or in cracked as well as uncracked concrete. Criteria are prescribed to determine the performance category for each anchor. The anchor performance categories are used by ACI CODE-318 to assign capacity reduction factors and other design parameters.

1.2—General

This Code describes the tests required to qualify a post-installed mechanical anchor or anchor system for use under the provisions of ACI CODE-318.

1.3—Purpose

This Code applies to post-installed mechanical anchors (torque-controlled expansion anchors, displacement-controlled expansion anchors, undercut anchors, and screw anchors) placed into predrilled holes and anchored within the concrete by mechanical means.

1.4—Applicability

This Code applies to expansion, undercut, and screw anchors with a minimum effective embedment depth of 1-1/2 in. (40 mm) and with a nominal diameter of 1/4 in. (6 mm) or larger. Screw anchors are limited to a maximum effective embedment of 10 d_a .

CHAPTER R1—GENERAL

R1.1—Scope

This Code prescribes the testing programs required to qualify post-installed mechanical anchors for use with the design method of ACI CODE-318 Chapter 17, where it is assumed that anchors have been tested either for use in uncracked concrete or for use in cracked and uncracked concrete. This testing is performed in concrete specimens controlled by the testing laboratory as a means of simulating concrete, both cracked and uncracked, that might occur in actual structures. Post-installed mechanical anchors exhibit a range of working principles, proprietary designs, and performance characteristics. ACI CODE-318 Chapter 17 addresses this situation by basing capacity reduction factors for anchors on anchor performance categories. This Code is intended to develop the data required by ACI CODE-318 Chapter 17 to confirm an anchor's reliability and place it in the appropriate anchor category.

ASTM E488/E488M includes some details for cracked concrete test members similar to those in this document. **ASTM E488/E488M** also has detailed test procedures for testing in cracked concrete.

R1.4—Applicability

The design method deemed to satisfy the anchor design requirements of ACI CODE-318 Chapter 17 is based on an analysis of a database of anchors with a maximum diameter of 2 in. (50 mm) and an embedment depth not greater than 25 in. (635 mm). This Code can be used for anchors with those maximum dimensions. While this Code gives no limitations on maximum anchor diameter or embedment depth, for anchors beyond these dimensions, the testing authority should decide if the tests described herein are applicable or if alternative tests and analyses are more appropriate. The minimum diameter of 1/4 in. (6 mm) is based on practical considerations regarding the limit of structural anchor applications. The current database of screw anchors contains products with an embedment up to $h_{ef} = 10d_a$ due to practical limits of manufacturing and ability to install at deep embedments. This database has been shown to satisfy the design requirements of ACI CODE-318 Chapter 17.