

An ACI Standard

Refrigerated Liquefied Gas Containment for Concrete Structures— Code Requirements and Commentary

Reported by ACI Committee 376

ACI CODE-376-23



American Concrete Institute
Always advancing



Refrigerated Liquefied Gas Containment for Concrete Structures— Code Requirements and Commentary

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. Despite these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/Document/Errata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations regarding health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

ACI documents are written via a consensus-based process. The characteristics of ACI technical committee operations include:

- (a) Open committee membership
- (b) Balance/lack of dominance
- (c) Coordination and harmonization of information
- (d) Transparency of committee activities to public
- (e) Consideration of views and objections
- (f) Resolution through consensus process

The technical committee documents of the American Concrete Institute represent the consensus of the committee and ACI. Technical committee members are individuals who volunteer their services to ACI and its specific technical committees.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Refrigerated Liquefied Gas Containment for Concrete Structures—Code Requirements and Commentary

An ACI Standard

Reported by ACI Committee 376

Kare Hjortset, Chair

Rolf P. Pawski, Vice Chair

Jeffrey C. Garrison, Secretary

Junius Allen
Thomas A. Ballard
Catherine Boucard
Hamish Douglas
Humayun Hashmi
Richard A. Hoffmann

Joseph Hoptay
Thomas R. Howe
Dajiu Jiang
Jameel U. Khalifa
Neven Krstulovic-Opara
Keith A. Mash

Sanjay S. Mehta
Piotr D. Tomcarz
Praveen K. Talbotra
Robert W. Vossmeier
William H. Oliver
John Powell

Ramanujam S. Rajan
Josef Roetzer
William E. Rushing Jr.
Eric S. Thompson
Fariborz Vossoughi
Markus Wernli

Consulting members

Robert Arvedlund
Dale Berner
Mike S. Brannan

Alex Cooperman
Charles S. Hanskat
Alan D. Hatfield

Nicholas A. Legatos
James P. Lewis
Stephen Meier

Robert W. Sward
Terry Turpin

Note: The committee would like to thank T. Shi for her contribution to this code. The first version of ACI CODE-376 was published in 2011.

Keywords: bund wall; commissioning; cryogenic; damage stability; decommissioning; earthquake design levels; fatigue; float out; floating storage unit; foundation heating; gravity gas structure; impact loads; liners; liquefied natural gas; liquid stratification; permanent ballast; purging; refrigerated liquefied gas; reinforcement (cryogenic); tanks; thermal corner protection.

CONTENTS

INTRODUCTION, p. 4

CHAPTER 1—GENERAL REQUIREMENTS, p. 5

1.1—Scope, p. 5

1.2—Quality assurance, p. 6

1.3—Engineer, p. 7

CHAPTER 2—NOTATION AND DEFINITIONS, p. 8

2.1—Notation, p. 8

2.2—Definitions, p. 9

ACI CODE-376-23 (SI Units) supersedes ACI 376M-11, and was approved by the ACI Standards Board for publication in March 2023 and published July 2023.

Copyright © 2024, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 3—REFERENCED STANDARDS, p. 16

CHAPTER 4—MATERIALS, p. 19

- 4.1—Testing of materials, p. 19
- 4.2—Cementitious materials, p. 19
- 4.3—Aggregates, p. 19
- 4.4—Water, p. 20
- 4.5—Admixtures, p. 20
- 4.6—Fibers, p. 20
- 4.7—Deformed reinforcing bars, p. 21
- 4.8—Plate steel composite with concrete, p. 22
- 4.9—Prestressed reinforcement, p. 22
- 4.10—Prestressing anchorages, p. 23
- 4.11—Post-tensioning ducts, p. 23
- 4.12—Grout, p. 23
- 4.13—Metal liners and nonstructural metal components, p. 24
- 4.14—Insulation, p. 24
- 4.15—Coating requirements, p. 25

CHAPTER 5—DESIGN LOADS, LOADING CONDITIONS, AND LOAD COMBINATIONS, p. 26

- 5.1—General, p. 26
- 5.2—Design loads, p. 26
- 5.3—Loading conditions, p. 31
- 5.4—Load combinations, p. 32

CHAPTER 6—MINIMUM PERFORMANCE REQUIREMENTS, p. 34

- 6.1—General, p. 34
- 6.2—Primary concrete container, p. 35
- 6.3—Secondary concrete container, p. 37
- 6.4—Roof performance criteria, p. 47
- 6.5—Other performance criteria, p. 47
- 6.6—Concrete quality, p. 47
- 6.7—Shotcrete, p. 52
- 6.8—Coating requirements, p. 52
- 6.9—Metal components, p. 53

CHAPTER 7—LOAD FACTORS, p. 54

- 7.1—General, p. 54
- 7.2—Load factors for ultimate limit state, p. 54
- 7.3—Load factors for serviceability limit state, p. 58

CHAPTER 8—ANALYSIS AND DESIGN, p. 59

- 8.1—Methods of analysis, p. 59
- 8.2—Container design basis, p. 66
- 8.3—Foundation design, p. 67
- 8.4—Wall design, p. 68
- 8.5—Roof design, p. 71
- 8.6—Horizontal shear transfer in composite construction, p. 73

CHAPTER 9—DETAILING, p. 74

- 9.1—General, p. 74
- 9.2—Reinforcement details, p. 74
- 9.3—Internal prestressing systems, p. 76
- 9.4—External prestressing systems, p. 77

- 9.5—Concrete containment wall, p. 77
- 9.6—Metal components, p. 79
- 9.7—Anchorage to concrete, p. 80
- 9.8—Liners and coatings, p. 81

CHAPTER 10—FOUNDATIONS, p. 83

- 10.1—General, p. 83
- 10.2—Geotechnical investigation, p. 84
- 10.3—Design requirements for shallow foundations, p. 87
- 10.4—Design requirements for deep foundations, p. 90
- 10.5—Ground improvement, p. 94
- 10.6—Foundation details, p. 95
- 10.7—Foundation performance monitoring details, p. 97
- 10.8—Monitoring frequency, p. 98
- 10.9—Inspection and testing, p. 100

CHAPTER 11—CONSTRUCTION REQUIREMENTS, p. 102

- 11.1—Construction plan, p. 102
- 11.2—Tolerances, p. 102
- 11.3—Shotcrete for external prestressing systems, p. 105
- 11.4—Post-tensioning, p. 105
- 11.5—Winding of prestressed reinforcement: wire or strand, p. 110
- 11.6—Forming, p. 111
- 11.7—Construction joints, p. 112
- 11.8—Concrete embedments, p. 113
- 11.9—Coatings, p. 113
- 11.10—Welding, p. 113

CHAPTER 12—TESTING, COMMISSIONING AND DECOMMISSIONING, p. 114

- 12.1—Scope, p. 114
- 12.2—Testing, p. 114
- 12.3—Pressure and vacuum testing, p. 118
- 12.4—Purging into service, p. 118
- 12.5—Cool-down, p. 120
- 12.6—Settlement and movement monitoring, p. 122
- 12.7—Tank fill methods, p. 123
- 12.8—Decommissioning: purging out of service and warm-up, p. 123
- 12.9—Recordkeeping, p. 125
- 12.10—Nameplate, p. 125

APPENDIX A—TANK CONFIGURATIONS, DETAILS, AND EXAMPLES, p. 127

- RA.1—Tank configurations, p. 127
- RA.2—Full-containment tanks: typical details, p. 127
- RA.3—Examples of base joint details, p. 127

APPENDIX B—OFFSHORE CONCRETE TERMINALS, p. 138

- B.1—Scope, p. 138
- B.2—General, p. 138
- B.3—Loads and load combinations, p. 139
- B.4—Concrete and reinforcement materials, p. 142
- B.5—Global and local structural analysis, p. 143

B.6—Criteria and methodology of concrete sectional design, p. 145

B.7—Fatigue performance criteria, p. 145

B.8—Design considerations during construction, transportation, and installation, p. 146

B.9—Decommissioning, p. 149

B.10—Design for accidents, p. 149

APPENDIX C—FATIGUE PERFORMANCE, p. 152

C.1—Scope, p. 152

C.2—General, p. 152

C.3—Fatigue performance criteria, p. 152

APPENDIX D—REQUIREMENTS FOR OUTER CONCRETE CONTAINER FOR MEMBRANE TANKS, p. 156

D.1—General requirements, p. 156

D.2—Notation and definitions, p. 157

D.3—Referenced standards, p. 157

D.4—Materials, p. 157

D.5—Design loads, loading conditions, and load combinations, p. 157

D.6—Minimum performance requirements, p. 158

D.7—Load factors, p. 161

D.8—Analysis and design, p. 163

D.9—Detailing, p. 163

D.10—Foundations, p. 163

D.11—Construction requirements, p. 163

D.12—Testing commissioning and decommissioning, p. 163

COMMENTARY REFERENCES, p. 164

Authored documents, p. 167

INTRODUCTION

ACI CODE-376, “Refrigerated Liquefied Gas Containment for Concrete Structures—Code Requirements and Commentary,” hereinafter called the Code or the 2023 Code and Commentary, are presented in a side by-side column format. These are two separate but coordinated documents, with Code text placed in the left column and the corresponding Commentary text aligned in the right column. Commentary section numbers are preceded by an “R” to further distinguish them from Code section numbers. The two documents are bound together solely for the user’s convenience. Each document carries a separate enforceable and distinct copyright.

ACI Committee 376 was formed and subsequently ACI 376-11 was drafted in response to a request from the National Fire Protection Association (NFPA) Technical Committee 59A on liquefied natural gas (LNG). That committee is responsible for **NFPA 59A**, which is an internationally recognized standard governing the production, storage, and handling of LNG at an operating temperature of -168°C .

NFPA 59A contains provisions for the use of reinforced concrete and prestressed concrete for two principal applications: 1) impoundment—secondary containment in conjunction with a metallic primary container; and 2) storage—primary containment. NFPA 59A is somewhat limited; it does not provide guidelines specifically tailored to concrete use at cryogenic temperatures. This limitation was the impetus for Committee 59A’s request. Although the request was related specifically to containment of LNG, this Code addresses concrete use for other refrigerated liquefied gas (RLG) as well, ranging in operating temperatures from $+4$ to -198°C . This makes the Code and commentary analogous to the American Petroleum Institute’s API 620, which governs design and construction of steel and aluminum RLG storage tanks to -198°C .

The most common use of reinforced concrete and prestressed concrete in cryogenic storage applications is for secondary containment around metal primary storage tanks. Prestressed concrete primary containment tanks were built in North America and Europe from the 1960s through the 1980s. Renewed interest in the use of concrete for primary containment and the need for a code that addressed secondary concrete containment led to the development of this Code, which includes pertinent excerpts from **ACI 318-19** and **ACI 350-20**. The commentary includes considerations by the committee in developing the Code.

The commentary is not intended to provide a complete historical background concerning development of the Code, nor is it intended to provide a detailed summary of the studies and research data reviewed by the committee in formulating its provisions. References to specific research data are provided for more in-depth study of the background materials.

ACI CODE-376 may be used as a part of a legally adopted code and, as such, must differ in form and substance from documents that provide detailed specifications, recommended practice, complete design procedures, or design aids.

Requirements more stringent than the Code provisions are desirable for unusual structures. This Code and commentary cannot replace sound engineering knowledge, experience, and judgment. A code for design and construction states the minimum requirements necessary to provide for public health and safety. ACI CODE-376 is based on this principle. For any structure, the owner and engineer may require the quality of materials and construction to be higher than the minimum requirements necessary to provide serviceability and to protect the public as stated in the Code. Lower standards, however, are not permitted.

ACI CODE-376 has no legal status unless it is adopted by regulatory bodies. Where the Code has not been adopted, it may serve as a reference to good practice. The Code provides a means of establishing minimum standards for acceptance of design and construction by a legally appointed official or designated representative. The Code and commentary are not intended for use in settling disputes between the owner, engineer, contractor, or their agents, subcontractors, material suppliers, or testing agencies. Therefore, the Code cannot define the contract responsibility of each of the parties in typical construction. General references requiring compliance with ACI CODE-376 in the job specifications should be avoided because the contractor is rarely in a position to accept responsibility for design details or construction requirements that depend on a detailed knowledge of the design. The contract documents should contain all the necessary requirements to ensure compliance with the Code, except in cases where the contractor acts as a specialty engineer that is responsible for all or part of the design and construction details. In this case, inclusion of the Code, in whole or in part, by reference in the project documents is acceptable. Other ACI publications, such as **ACI 301**, are written specifically for use as contract documents for construction and can be included in the project documents by reference.

CODE

COMMENTARY

CHAPTER 1—GENERAL REQUIREMENTS

1.1—Scope

1.1.1 This Code provides minimum requirements for design and construction of reinforced concrete and prestressed concrete structures for the storage and containment of refrigerated liquefied gases (RLGs) with service temperatures between +4 and -198°C .

1.1.2 Container design shall include the design of the container wall, its foundation (footing and floor slab), the concrete portions of its roof, and the bund wall, if applicable.

R1.1—Scope

R1.1.1 Typically, reinforced concrete and prestressed concrete structures for the containment of RLGs are classified into two main categories:

- (a) Secondary containment, which represents the most widespread use of such structures
- (b) Primary containment

In this Code, the term “concrete” is used to denote both concrete reinforced with nonprestressed reinforcement and prestressed concrete.

Appendix D has been added in this version of the Code that includes design and detailing requirements for membrane tanks. A membrane tank has a non-self-supporting thin layer (membrane) that is supported through insulation by an outer concrete tank that structurally serves as the primary container and secondary container.

This Code does not address the materials, design, or construction of steel primary or secondary tanks. Such information is further described in **API 620**.

R1.1.2 This Code has been developed with the lowest operating temperature of -198°C . Lower product temperatures could also be used, however, provided appropriate additional engineering analysis and justification is performed for each proposed application. Single-containment, double-containment, and full-containment concepts are covered by this Code.

A concrete bund wall is an open-top cylindrical wall serving as the outer boundary of an impounding area surrounding a single-containment RLG storage tank.

In a double-containment tank system, the primary container is normally a single-containment RLG storage tank with a vapor-tight shell and roof designed to contain both refrigerated liquid and the associated vapors under normal operating conditions. In this system, the secondary container is often an open-top concrete wall that serves two basic functions:

1. Provides protection to the primary container from external loads under normal operating conditions.
2. Contains the leakage from the primary container (but not the vapor generated from such leakage) under accidental-spill conditions.

In a full-containment tank system, the primary container is designed to contain the refrigerated liquid under normal operating conditions. In this system, the secondary container is a vapor-tight wall with a vapor-tight roof that spans over the inner tank. The roof may be constructed of metal, concrete, or a composite of the two materials.

Under normal operating conditions, the secondary container provides protection to the primary container from external loads. Under accidental-spill conditions, the secondary container also contains the leakage from the primary container and contains or controls the vapor generated from such leakage.