

**ACI (308-213)R-13**

**Report on Internally Cured  
Concrete Using Prewetted  
Absorptive Lightweight Aggregate**

Reported by ACI Committee 308  
and ACI Committee 213



**American Concrete Institute®**



First Printing  
June 2013

**American Concrete Institute®**  
*Advancing concrete knowledge*

## **Report on Internally Cured Concrete Using Prewetted Absorptive Lightweight Aggregate**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at [www.concrete.org/committees/errata.asp](http://www.concrete.org/committees/errata.asp). Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

**American Concrete Institute**  
**38801 Country Club Drive**  
**Farmington Hills, MI 48331**  
**U.S.A.**  
**Phone: 248-848-3700**  
**Fax: 248-848-3701**

**[www.concrete.org](http://www.concrete.org)**

ISBN-13: 978-0-87031-821-4  
ISBN: 0-87031-821-7

# Report on Internally Cured Concrete Using Prewetted Absorptive Lightweight Aggregate

Reported by ACI Committee 308 and ACI Committee 213

David M. Suchorski, Chair

John C. Hukey, Secretary

*ACI Committee 308 roster*

Dale P. Bentz  
Dianne Carey  
Jennifer K. Crisman  
Jonathan E. Dongell  
Michael Faubel  
Dale Fisher  
Sidney Freedman  
Michael G. Hernandez  
Erik Holck  
Cecil L. Jones

Frank A. Kozeliski  
Ronald J. Kozikowski  
Mauricio Lopez  
Darryl Manuel  
Steve F. McDonald  
Michael E. Murray  
John W. Roberts  
Philip A. Smith  
Lawrence Homer Taber  
Richard E. Van Horn  
Jody R. Wall

Daniel Webber  
John B. Wojakowski

*ACI Committee 308 Consulting Members roster*

Michael C. Bruno  
James N. Cornell II  
Ben E. Edwards  
Jerome H. Ford  
R. Doug Hooton  
David E. Hoyt  
James A. Lee  
W. Calvin McCall  
William S. Phelan

*This report introduces the concepts of and describes the process benefit and applications for using prewetted lightweight aggregate to increase cement hydration in internally cured concrete. It also describes mixture proportioning and absorptive material selection and discusses the benefits relating to sustainability. The materials, processes, quality control measures, and inspections described should be tested, monitored, or performed as applicable only by individuals holding the appropriate ACI certification or equivalent.*

**Keywords:** absorption; curing; desorption; durability; high performance concrete; hydration; internal curing; internally cured concrete; lightweight aggregate; outside curing; permeability; saturated-surface-dry shrinkage; strength; supplementary cementitious materials; water movement.

## CONTENTS

### CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 2

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 2

### CHAPTER 3—PROCESS, p. 2

- 3.1—General, p. 2
- 3.2—Justification, p. 3
- 3.3—Water movement, p. 3
- 3.4—Autogenous shrinkage and self-desiccation, p. 3
- 3.5—Mechanism of internal curing, p. 3
- 3.6—Water movement during hydration observed using X-ray microtomography, p. 4

### CHAPTER 4—INTERNALLY CURED CONCRETE (ICC): EFFECTS, BENEFITS, AND APPLICATIONS, p. 4

- 4.1—Early-age shrinkage reduction, p. 4
- 4.2—Crack reduction, p. 5
- 4.3—Compressive strength, p. 5
- 4.4—Overdosing prewetted lightweight aggregate (PLA), p. 6
- 4.5—Flexural strength, p. 6
- 4.6—Mitigation of warping and dimensional stability, p. 6
- 4.7—Modulus of elasticity, p. 6
- 4.8—Permeability and resistance to deicing chemicals, p. 7
- 4.9—Creep, p. 7
- 4.10—Durability, p. 8

ACI (308-213)R-13 was adopted and published June 2013.  
Copyright © 2013, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

**CHAPTER 5—BATCHING PROCEDURES, p. 8**

- 5.1—Choice of absorptive material, p. 8
- 5.2—Mixture proportioning using absorptive materials, p. 8
- 5.3—Prewetting lightweight aggregate, p. 10
- 5.4—Concrete batching, mixing, transporting, placing, and finishing, p. 10

**CHAPTER 6—SUSTAINABLE CONCRETE CONSTRUCTION USING INTERNALLY CURED CONCRETE (ICC), p. 11****CHAPTER 7—REFERENCES, p. 11****CHAPTER 1—INTRODUCTION AND SCOPE****1.1—Introduction**

Portland-cement concrete, including mixtures with supplementary cementitious materials, does not typically develop its durability, strength, and mechanical characteristics without adequate curing. This report on internally cured concrete (ICC) does not presume to change the requirement for water retention at the curing-affected zone on the concrete surface. The curing methods listed in ACI 308R-01 should be consulted for appropriate methods to prevent or mitigate moisture loss from the concrete surface.

Test trial batches should be used during initial mixture proportioning to determine and verify those concrete properties required for each project.

Internally cured concrete uses prewetted absorptive materials that contain moisture. The absorbed moisture is released as the internal humidity of the concrete drops below 100 percent to enhance and maximize the hydration of cement.

High-performance concrete typically has a low  $w/cm$  that may not supply enough water to hydrate all of the cement. Due to the reduction in permeability of high-performance concrete, even in the first 2 to 3 days, exterior water curing is limited in its ability to supply in-depth hydration to the cement as the products of hydration fill and disconnect the capillary pore network (Powers et al. 1950). In this case, the beneficial effect of external water curing is limited to the concrete surface. As a result, external water cannot penetrate the interior of the concrete to maintain a saturated capillary pore system thereby avoiding self-desiccation. One solution is to replace a portion of the normalweight aggregate with absorbent materials to deliver water to the hydrating cement. The principal improvements of supplying internal water are the maintenance of a saturated cement paste, which leads to greater hydration of the cement and more complete pozzolanic reactions.

Characteristics of high-performance concrete that may be improved by increased hydration from internally absorbed moisture include resistance to early-age cracking; higher strength; decreased permeability; decreased warping; dimensional stability; resistance to freezing-and-thawing damage, deicing chemicals, and chemical attacks; and creep.

In the past 50 years, portland cement has become finer with higher contents of tricalcium silicate and alkalis (Bentz et al. 2008). These changes have led to generally faster hydrating

cements that produce much of their strength in only a few days. Concretes made with these cements, however, can be more prone to early-age cracking due to their increased heat of hydration and significantly increased autogenous strains and stresses that can develop when self-desiccation occurs.

**1.2—Scope**

Internally cured concrete uses absorptive materials in the mixture that supplement the standard curing practices by supplying moisture to the interior of the concrete (ACI 308R-01). This process adds moisture without affecting the  $w/cm$ . The moisture is desorbed for internal moisture augmentation at the time needed to further hydrate the cement. This water addition can be achieved using several materials (Jensen and Lura 2006; Kovler and Jensen 2007), including prewetted lightweight aggregate, superabsorbent particles, wood fibers, and absorbent limestone aggregate. This report will focus primarily on the use of prewetted lightweight aggregate.

**CHAPTER 2—NOTATION AND DEFINITIONS****2.1—Notation**

- $C_f$  = cement factor (content) for concrete mixture, lb/yd<sup>3</sup> (kg/m<sup>3</sup>)
- $CS$  = chemical shrinkage of cement (mass of water/mass of cement)
- $M_{LWA}$  = mass of (dry) lightweight aggregate needed per unit volume of concrete, lb/yd<sup>3</sup> (kg/m<sup>3</sup>)
- $S$  = degree of saturation of aggregate (0 to 1, measured absorption percentage divided by the absorption percentage at which desorption was measured)
- $w_{ic}/c$  = the ratio of the water supplied by internal curing to the cement in the concrete mixture on a mass basis
- $\alpha_{max}$  = maximum expected degree of hydration of cement (0 to 1); for ordinary portland cement, the maximum expected degree of hydration of cement can be assumed to be 1 for  $w/cm \geq 0.36$  and the value of ( $w/cm$ ) divided by 0.36 for  $w/cm < 0.36$
- $\phi_{LWA}$  = desorption of lightweight aggregate from a prewetted condition down to 93 percent relative humidity (mass water/mass dry lightweight aggregate) in accordance with ASTM C1498-04

**2.2—Definitions**

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://terminology.concrete.org>. The definition provided here complements that source.

**prewetted**—wetting of the aggregate so that it contains the prescribed water content available for cement hydration.

**CHAPTER 3—PROCESS****3.1—General**

Concrete with a water-cementitious materials ratio ( $w/cm$ ) below 0.42 does not contain enough batch water to fully hydrate all of the cement (Neville 1996). In concrete with a