

ACI FPRC-330.2-17(20)

Guide for the Design and Construction of Concrete Site Paving for Industrial and Trucking Facilities

Reported by ACI Committee 330



American Concrete Institute
Always advancing



Guide for the Design and Construction of Concrete Site Paving for Industrial and Trucking Facilities

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
3800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide for the Design and Construction of Concrete Site Paving for Industrial and Trucking Facilities

Reported by ACI Committee 330

Robert L. Varner, Chair

David J. Akers
Richard O. Albright
J. Howard Allred
Bryan M. Birdwell
David W. Buzzelli
Michael W. Cook
Tim Cost
Craig M. Dahlgren

Michael S. Davy
Norbert J. Delatte
Douglas W. Deno
Bruce A. Glaspey
R. Scott Haislip
Omer Heracklis
Jerry A. Holland
Kenneth G. Kazanis*

Frank A. Kozeliski
Frank Lennox
John R. Love III
Amy Miller
Jon I. Mullarky
Scott M. Palotta
Nigel K. Parkes
Jan R. Prusinski

David Richardson
Robert A. Rodden
David M. Suchorski
Scott M. Tarr
Christopher R. Tull
Diep T. Tu
Jason D. Wimberly

*Chair of the task group that prepared this guide.

Consulting Members

D. Gene Daniel

Don J. Wade

This guide provides information useful in the design and construction of a successful site-paving project for heavy-duty industrial and trucking facilities. This information assists architects/engineers, contractors, and testing agencies with designing, detailing, constructing, repairing, and inspecting site paving. Engineers use this guide to make recommendations for the pavement support system, concrete mixture, pavement thickness, joint spacing, and load transfer devices. Thickness design tables are included for common over-the-road trucks and industrial lift trucks. Tables are also provided to check the pavement thickness for providing shear and concrete strength for bearing stress applied by loaded trailers that have been disconnected from the tractor. Contractors use this guide to understand proper ways to construct site paving with block or strip placements and avoid common mistakes made during construction. Proper placing, consolidating and finishing techniques are described to construct a durable pavement that complies

with the project documents. Inspectors and testing agencies use this guide to understand the design and be better equipped to monitor the project from stripping and grubbing of the site to concrete pavement construction. Testing and inspection included in this guide should only be done by individuals holding the appropriate certifications.

Keywords: industrial pavement; joint stability; lift truck; lug anchor; over-the-road truck; pavement support system; sustainable industrial pavement system; unreinforced concrete pavement.

CONTENTS

CHAPTER 1—GENERAL, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3
- 1.3—Background, p. 3

CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

- 2.1—Notation, p. 3
- 2.2—Definitions, p. 3

CHAPTER 3—SUBGRADES AND SUBBASES, p. 4

- 3.1—Pavement support system, p. 4
- 3.2—Subgrade/subbase failure modes, p. 5
- 3.3—Subgrade considerations, p. 5
- 3.4—Subbase considerations, p. 8

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

This ACI document contains requirements that can, at the time of the document's adoption by ACI, be satisfied practically only by use of a patented material, product, process, procedure, or apparatus. ACI does not endorse this technology. The selection of any design methodology or use of any patented technology is at the option of the user.

ACI 330.2R-17 was adopted and published May 2017

Copyright © 2020, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 4—PAVEMENT DESIGN, p. 10

- 4.1—Introduction, p. 10
- 4.2—Loads, p. 12
- 4.3—Concrete properties, p. 13
- 4.4—Jointing, p. 14
- 4.5—Reinforcement, p. 18
- 4.6—Joint stability (load transfer), p. 19
- 4.7—Thickness design, p. 24
- 4.8—Other design features, p. 30

CHAPTER 5—CONCRETE MATERIALS AND MIXTURE PROPORTIONING, p. 32

- 5.1—Introduction, p. 32
- 5.2—Cementitious materials, p. 32
- 5.3—Mixing water, p. 33
- 5.4—Aggregates, p. 33
- 5.5—Admixtures, p. 33
- 5.6—Concrete mixture design, p. 33

CHAPTER 6—CONSTRUCTION, p. 36

- 6.1—Introduction, p. 36
- 6.2—Subgrade and subbase preparation, p. 37
- 6.3—Layout for construction, p. 38
- 6.4—Forming and use of rigid screed guides, p. 39
- 6.5—Concrete placement, screeding, and finishing, p. 39
- 6.6—Installation of the different joint types, p. 44
- 6.7—Joint sealing or filling, p. 47
- 6.8—Curing, p. 47
- 6.9—Special considerations for adverse weather conditions, p. 47
- 6.10—Striping, p. 48
- 6.11—Opening to traffic, p. 48

CHAPTER 7—INSPECTION AND TESTING, p. 49

- 7.1—Introduction, p. 49
- 7.2—Site preparation and grading, p. 49
- 7.3—Subgrade and subbase, p. 49
- 7.4—Forming, p. 50
- 7.5—Reinforcing steel, p. 50
- 7.6—Concrete quality, p. 50
- 7.7—Concrete curing, p. 51
- 7.8—Jointing, p. 51
- 7.9—Surface texture, p. 51

CHAPTER 8—MAINTENANCE AND REPAIR, p. 51

- 8.1—Introduction, p. 51
- 8.2—Surface sealing, p. 51
- 8.3—Joint sealing and crack sealing, p. 52
- 8.4—Partial depth repair, p. 52
- 8.5—Full depth repair, p. 52
- 8.6—Undersealing and leveling, p. 53

CHAPTER 9—SUSTAINABILITY AND INDUSTRIAL CONCRETE PAVEMENTS, p. 53

- 9.1—Sustainability considerations, p. 53
- 9.2—Concrete as a sustainable industrial pavement system, p. 53
- 9.3—Life cycle analysis, p. 55

CHAPTER 10—REFERENCES, p. 56

- Authored documents, p. 57

APPENDIX A—SOIL CLASSIFICATIONS AND DYNAMIC CONE PENETROMETER, p. 59

- A.1—Soil classifications, p. 59
- A.2—Dynamic cone penetrometer, p. 61

APPENDIX B—THICKNESS DESIGN SOFTWARE AND THICKNESS DESIGN EXAMPLE, p. 61

- B.1—Proprietary design software, p. 61
- B.2—Thickness design example, p. 62

APPENDIX C—LOAD TRANSFER THROUGH ENHANCED AGGREGATE INTERLOCK, p. 65

- C.1—Load transfer through enhanced aggregate interlock, p. 65

APPENDIX D—DRYING AND THERMAL EXPANSION AND CONTRACTION OF CONCRETE, p. 66

- D.1—Drying and thermal expansion and contraction, p. 66
- D.2—Curling and warping, p. 66
- D.3—Factors that affect shrinkage, curling, and warping, p. 66
- D.4—Compressive strength and shrinkage, p. 67
- D.5—Relation between curing and curling and warping, p. 67
- D.6—Curling and warping stresses in relation to joint spacing, p. 67

CHAPTER 1—GENERAL**1.1—Introduction**

Concrete provides a strong and durable surface for vehicle maneuvering and storage areas, making it especially suited for site paving at industrial and trucking facilities. Concrete site paving for industrial and trucking facilities has many similarities to other types of concrete pavements, such as typical concrete parking lots, streets, and highways. Service distinctions may include traffic speed and zones dedicated specifically to multi-directional or channelized traffic flow. These facilities are often constructed to serve not only over-the-road trucks, but industrial lift trucks, such as those imposed by dolly wheels and trailer pads, tracked vehicles, other nontraditional vehicles, and other vehicular-related static loads such as trailers dropped on-site between loading and off-loading. Industrial and trucking facilities have paved areas that are generally larger in size than most parking lots. The scale of these projects and the comparatively high traffic count and special loads generally justify more attention to design than typical parking lots. These distinctions along with changing technologies initiated the development of this guide.

Note that **ACI 330R** can be used as a resource for some similarly-described facilities. Each document has been developed as a stand-alone guide that provides critical

design information and recommended construction practices for successful paving projects. Guide selection to a specific project should consider the specific traffic level to be accommodated as well as the design load types, especially if they include industrial lift trucks and other special loads, the percentage of accommodated vehicles (which are very heavy), site geotechnical considerations such as in-place subgrade character and drainage, joint spacing, and potential future uses of the facility. In general, this guide is intended for facilities with heavier design loads, nonstandard vehicles, higher volumes of heavy trucks, or both. Examples of such facilities include warehouses, factories, truck terminals, heavy equipment sales and service distribution centers, and ports. **ACI 330R** is intended for use when truck loads are generally lighter, traffic volumes lower, or both, though many successful projects accommodating higher average daily truck traffic of mixed vehicle loads have been designed using ACI 330R. Examples of typical parking lots most consistent with the intended scope of ACI 330R would include concrete pavements for apartment complexes, shopping malls, convenience stores, gas stations, banks, and office buildings.

Concrete offers many advantages over asphalt for pavements at industrial or trucking facilities. Concrete provides greater surface and pavement system durability and favorable economics with respect to life-cycle costs, and sometimes even with initial construction costs. Facility night-time illumination can be provided at a lower cost with concrete due to concrete surface reflectance. Concrete also reduces traffic load stresses imposed on subbase and subgrade soils and can be constructed with a wide variety of construction equipment, ranging from hand tools and vibratory screeds, to laser-guided screeds and large highway paving equipment. The sustainable construction benefits of concrete are also an important consideration in pavement type selection (**Chapter 9**).

The paired values stated in inch-pounds and SI units are usually not exact equivalents. Therefore, each system is to be used independently of the other. Combining values from the two systems could result in nonconformance with this guide.

1.2—Scope

This guide is based on the current knowledge and practices for the design, construction, and maintenance of concrete site pavements for industrial and trucking facilities, emphasizing the aspects of concrete pavement technology that are different from procedures used to design and construct floor slabs, parking lots, streets, and highways. This guide is neither a standard nor a specification, and it is not intended to be included by reference in construction contract documents.

Pavements for industrial and trucking facilities are designed similarly to parking lots, streets, and highways, but with a few key technical differences. Site pavements have most loads imposed on interior panels surrounded by other pavement, which provide varying degrees of panel edge support or load transfer on all sides. Other pavement applications may carry loads along and across relatively un-

ported edges, where greater deflections and stresses are not a significant concern due to lighter design traffic. Streets and highways are commonly designed to drain toward an edge where storm water can be carried away from the pavement. Site pavements are commonly designed so a portion of the storm water is collected internally and conveyed away through underground systems. Site pavements often accommodate appurtenances, such as drainage structures, lighting standards, bollards, and fuel islands. Provisions for these appurtenances should be considered in the design, layout, and construction of the crack-control (jointing) system.

1.3—Background

Design practices for concrete site pavements have often varied by local experiences and are based on guidance derived from a combination of design references covering heavy pavements and floor slabs. The unique demands of these types of facilities have made it challenging for project designers to integrate all appropriate design protocols and consider all performance influences. This document is intended to respond to the need for a single, source guide on concrete site paving for industrial and trucking facilities.

Concrete pavement thickness is one of the critical design elements for industrial and trucking facility site paving applications, just as it is for parking lots and other mixed-vehicle pavements. This is true not only for engineering economy but also for the pavement structure to reliably carry loads from nontraditional vehicles and certain static loads. For concrete site paving, proper thickness design should minimize pavement stresses and deflections along joints and pavement edges. Many types of geotechnical site conditions that can successfully accommodate light traffic pavements are not appropriate for industrial and trucking facility site pavements without enhancement of the subgrade system, inclusion of one or more subbases, or both. This type of distinction also extends to load transfer considerations.

Subgrade improvement, joint spacing and layout, and load transfer strategies are important elements of industrial and trucking site pavement design. Thickness should reflect these considerations along with pavement stress levels for all envisioned loadings. Construction planning should consider surface durability needs and appropriate tolerances.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

B_n	=	nominal bearing strength
B_u	=	factored bearing load
E_C	=	modulus of elasticity
k -value	=	modulus of subgrade reaction
M_R	=	resilient modulus
V_n	=	nominal shear strength
V_u	=	factored shear force

2.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <https://www.concrete.org/resources/terminology/>