

IN-LB

Inch-Pound Units

SI

International System of Units

# Design of Circular Concrete-Filled Fiber-Reinforced Polymer Tubes—Guide

Reported by ACI Committee 440

ACI PRC 440.14-25



American Concrete Institute  
*Always advancing*



## Design of Circular Concrete-Filled Fiber-Reinforced Polymer Tubes—Guide

© 2025 American Concrete Institute. All rights reserved.

This material may not be reproduced or copied, in whole or in part, in any form or by any means, including making copies by any photo process, or by electronic or mechanical device, printed, written, graphic, or oral, or recording for sound or visual reproduction for use in any knowledge or retrieval system or device, without the written consent of ACI. This material may not be used by data mining, robots, screen scraping, or similar data gathering and extraction tools such as artificial intelligence (“AI”) for purposes of developing or training a machine learning or AI model, conducting computer analysis or creating derivatives of this material, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. Despite these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability and fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations regarding health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

ACI documents are written via a consensus-based process. The characteristics of ACI technical committee operations include:

- (a) Open committee membership
- (b) Balance/lack of dominance
- (c) Coordination and harmonization of information
- (d) Transparency of committee activities to public
- (e) Consideration of views and objections
- (f) Resolution through consensus process

The technical committee documents of the American Concrete Institute represent the consensus of the committee and ACI. Technical committee members are individuals who volunteer their services to ACI and public technical committees.

American Concrete Institute®, ACI®, and Always Advancing® are registered trademarks of American Concrete Institute.

# Design of Circular Concrete-Filled Fiber-Reinforced Polymer Tubes—Guide

Reported by ACI Committee 440

Maria Lopez de Murphy, Chair

John J. Myers, Secretary

Ehab Ahmed  
Tarek Alkhrdaji  
Charles E. Bakis  
Abdeldjelil Belarbi  
Brahim Benmokrane  
Luke A. Bisby  
Gregg J. Blaszak  
Hakim Bouadi  
Timothy E. Bradberry  
Vicki L. Brown  
John P. Busel†  
Christian Carloni

Lijuan Dawn Cheng  
Raafat El-Hacha  
Ehab F. El-Salakawy  
Garth J. Fallis  
Amir Z. Fam\*‡  
Will J. Gold  
Nabil F. Grace  
Mark F. Green  
Doug D. Gremel  
Issam E. Harik  
Kent A. Harries  
Mark P. Henderson

Ravi Kanitkar  
Yail Jimmy Kim  
Michael W. Lee  
Eric MacFarlane  
Radhouane Masmoudi  
Antonio Nanni  
Ayman M. Okeil  
Carlos E. Ospina  
Maria Anna A. Polak  
Max L. Porter  
Hayder A. Rasheed  
Pedram Sadeghiar

Rudolf Seracino  
Venkatesh Seshappa  
Xavier Seyoum  
Carl K. Shield  
Jay Thomas  
Douglas G. Tomlinson‡  
Gustavo Tumialan  
Erbilina Vokshi  
Sarah E. Witt

\*Chair of the subcommittee who prepared this document.

†Deceased.

‡Authors of this guide.

§Subsequent Chair of the subcommittee that prepared this document.

## Consulting Member

P. N. Balaguru  
Lawrence C. Bank  
C. J. Burgoyne  
Rami M. Elhassan  
David M. Gale

Russell Gentry  
Srinivasa L. Iyer  
Koichi Kishitani  
Howard S. Kliger  
Ibrahim M. Mahfouz

Kyuichi Maruyama  
Amir Mirzaman  
Antoine E. Naaman  
Hajime Okada  
Mark A. Postma

Sami H. Rizkalla  
Rajan Sen  
Surendra P. Shah  
Mohsen Shahawy  
Yasuhisa Sonobe

Minoru Sugita  
Luc R. Taerwe  
Houssam A. Toutanji  
Taketo Uomoto  
Paul Zia†

## Section Members

Tanarat Potisuk

Scott Thomas Smith

The circular concrete-filled fiber-reinforced polymer (CFRP) tube (CFFT) system is an alternative to traditional reinforced concrete structures. The pre-cured FRP tube, which comprises layers of engineered fibers oriented in different directions, provides a corrosion-resistant stay-in-place structural form to receive freshly cast concrete that speeds up construction while at the same time provides primary reinforcement in the two orthogonal directions instead of traditional longitudinal steel reinforcement bars, ties, and stirrups. Typical applications of CFFT include piles, columns, and poles used in building and bridge construction. The FRP tube provides confinement and environmental protection of the concrete core, increasing

its strength, ductility, and durability, as well as protection of the minimum internal steel reinforcement. Due to the unique characteristics of CFFTs in which reinforcement in the orthogonal directions are integrated into one continuous membrane—namely, the tube—specific guidance on the design of members using this system is needed. This guide provides general information and background of CFFT technology, including applications and limitations, characteristics of circular FRP tubes, and the interface bond between tube and concrete. The guide provides provisions for design for flexure, axial load, shear, combined loading, connections, and a design approach aimed at mitigating the risk of accidental tube loss. This guide is based on the knowledge gained from experimental research, analytical work, and field applications of CFFTs.

ACI Committee Reports and Guides are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the information it contains. ACI disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom. Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

**Keywords:** bond; circular; concrete-filled fiber-reinforced polymer tube (CFFT); confinement; connections; fiber-reinforced polymer (FRP); stay-in-place form; tube.

ACI PRC-440.14-25 was published May 2025.

Copyright © 2025, American Concrete Institute.

This material may not be reproduced or copied, in whole or in part, in any form or by any means, including making copies by any photo process, or by electronic or mechanical device, printed, written, graphic, or oral, or recording for sound or visual reproduction for use in any knowledge or retrieval system or device, without the written consent of ACI. This material may not be used by data mining, robots, screen scraping, or similar data gathering and extraction tools such as artificial intelligence (“AI”) for purposes of developing or training a machine learning or AI model, conducting computer analysis or creating derivatives of this material, without the written consent of ACI.

## CONTENTS

**CHAPTER 1—INTRODUCTION, p. 2**

- 1.1—Scope, p. 2
- 1.2—Literature review, p. 3
- 1.3—Applications and use, p. 4
- 1.4—Limitations, p. 5

**CHAPTER 2—NOTATION AND DEFINITIONS, p. 6**

- 2.1—Notation, p. 6
- 2.2—Definitions, p. 7

**CHAPTER 3—MATERIAL PROPERTIES, p. 8**

- 3.1—FRP tube, p. 8
- 3.2—Concrete, p. 8
- 3.3—Steel reinforcement, p. 9
- 3.4—Glass FRP reinforcement, p. 9

**CHAPTER 4—LIMIT STATES, p. 9**

- 4.1—Service limit state, p. 9
- 4.2—Strength limit state, p. 9

**CHAPTER 5—DESIGN FOR FLEXURE WITH NO AXIAL COMPRESSION, p. 10**

- 5.1—Assumptions, p. 10
- 5.2—Minimum tube thickness, p. 10
- 5.3—Balanced tube thickness, p. 10
- 5.4—Design flexural strength, p. 11
- 5.5—Deflection, p. 12
- 5.6—Control of cracking, p. 12
- 5.7—Stress limit for concrete, p. 12

**CHAPTER 6—DESIGN FOR AXIAL COMPRESSION, p. 12**

- 6.1—General, p. 12
- 6.2—Assumptions, p. 12
- 6.3—Design axial compressive strength, p. 12
- 6.4—Minimum tube thickness, p. 13
- 6.5—Stress limit for concrete, p. 13

**CHAPTER 7—DESIGN FOR COMBINED FLEXURE AND AXIAL COMPRESSION, p. 13**

- 7.1—General, p. 13
- 7.2—Assumptions, p. 13
- 7.3—Design strength, p. 14
- 7.4—Evaluation of slenderness effects, p. 15
- 7.5—Minimum tube thickness, p. 15
- 7.6—Deflection, p. 15
- 7.7—Control of cracking, p. 15
- 7.8—Stress limit for concrete, p. 15

**CHAPTER 8—DESIGN FOR SHEAR, p. 15**

- 8.1—General, p. 15
- 8.2—Nominal shear strength, p. 15
- 8.3—Minimum tube thickness, p. 16

**CHAPTER 9—MINIMUM INTERNAL REINFORCEMENT, p. 16****CHAPTER 10—CONNECTIONS, p. 16****CHAPTER 11—REFERENCES, p. 17**

Authored documents, p. 17

**CHAPTER 1—INTRODUCTION**

Fiber-reinforced polymer (FRP) materials have emerged as an alternative to steel reinforcement for concrete structures. Unlike steel reinforcement, FRP reinforcement does not corrode. FRP is a versatile material that can be produced in many forms such as reinforcing bars, grids, rigid plates, flexible sheets, and structural shapes that include tubes. This guide is focused on the application of FRP in the form of pre-cured tubes used as structural stay-in-place formwork filled with concrete (Fardis and Khalili 1980; Nanni and Bradford 1995; Mirmiran and Shahawy 1996). Due to differences in the physical and mechanical properties of FRP materials as opposed to steel, particularly when used as concrete-filled tubes, specific guidance on the engineering design of structural components using this technology is needed.

Concrete-filled FRP tubes (CFFTs) are viable high-performance systems for applications subject to harsh environments. The FRP tube acts as corrosion-resistant reinforcement, increasing section capacity of the system under axial, flexural, and shear loading; provides confinement and protection of the concrete core; and functions as stay-in-place formwork to achieve rapid construction. The fiber orientations in the FRP tube are designed to provide strength and stiffness in the desired directions, which may be tailored depending on the structural application. Fibers aligned along the longitudinal axis (or near-longitudinal in compliance with 1.4.1) of the tube provide strength and stiffness under bending and combined bending and axial loads. Fibers perpendicular to the longitudinal axis (or near-perpendicular in compliance with 1.4.1) provide confinement to the concrete. This design is referred to as cross-ply or near-cross-ply laminate. Other tube designs include angle-ply laminate with fibers at large angles from the longitudinal axis, or a combination of angle-ply and cross-ply laminates in the same tube.

**1.1—Scope**

This guide provides recommendations for the design of circular CFFTs for use as structural components. Other shapes such as rectangular sections are beyond the scope of this document. The contribution of internal reinforcement exceeding the minimum needed to compensate for accidental damage of the FRP tube, discussed in **Chapter 9**, or used to prestress the CFFT is not considered in this document. Design methodologies presented in this guide allow CFFTs to be designed as flexural members, axial compression members, or members subjected to combined flexure and axial compression. CFFT components include beams, arches, columns, load-bearing piles, and mono-poles.

The design recommendations in this guide were developed based on research conducted on FRP tubes composed