

IN-LB

Inch-Pound Units

SI

International System of Units

Specifying Underground Shotcrete—Guide

Reported by ACI Committee 506

ACI PRC 506.5-22



American Concrete Institute
Always advancing



Specifying Underground Shotcrete—Guide

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Specifying Underground Shotcrete—Guide

Reported by ACI Committee 506

Simon Reny*, Chair

James A. Ragland, Secretary

Lars F. Balck
Louis-Samuel Bolduc
Chris D. Breeds*
Wern-Ping Nick Chen*
Scott R. Cumming*
William T. Drakeley Jr.*

Randle M. Emmrich
Charles S. Hanskat*
Marc Jolin*
Mark R. Lukkarilia
Axel G. Nitschke*
Ryan Oakes

Ryan E. Poole
Raymond C. Schallom*
William L. Snow Sr.
Jason P. South
Lawrence J. Totten*
Frank E. Townsend*

Matthias H. von der Hofen*
Eugene Wilson
Peter T. Yen*
Lihe Zhang†

Consulting Members

Jean-François Dufour
Richard A. Kaden

Dudley R. Morgan*
H. Celik Ozyildirim

Harvey W. Parker‡
Philip T. Seabrook

*Subcommittee members who produced this report.

†Subcommittee Chair who produced this report.

‡Deceased.

Note: The Committee acknowledges B. Edgerton, J. Lindell, J. O'Donnell Sr., and F. Sh... for their contributions to this report.

This document provides a guide for owners, contractors, designers, and testing, specifying, and inspection organizations regarding the application of shotcrete for underground support. The guide provides general information for the selection of constituent materials, and methods to proportion shotcrete. Typical methods of batching, mixing, and handling of proportioned shotcrete materials are detailed along with shotcrete placement methods and equipment.

Keywords: acceptance criteria; batching; inspection; methods of payment; mine(s); mixing; mixture proportions; placement; quality assurance; quality control; safety; shotcrete; testing; tunneling.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 3

- 1.1—Introduction, p. 3
- 1.2—Scope, p. 4

CHAPTER 2—NOTATION AND DEFINITIONS, p. 5

- 2.1—Notation, p. 5
- 2.2—Definitions, p. 5

CHAPTER 3—SUBMITTALS, p. 6

- 3.1—Submittal process, p. 6
- 3.2—Recommended specifications, p. 7

CHAPTER 4—MATERIALS, p. 7

- 4.1—Accelerators, p. 7
- 4.2—Recommended specifications, p. 8

ACI Committee Reports and Guides are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI PRC-506.5-22 supersedes ACI 506.5R-09(16) and was adopted and published in October 2022.

Copyright © 2022, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—ANCHORAGE AND REINFORCEMENT, p. 10

- 5.1—Composite support systems, p. 10
- 5.2—Shotcrete with pattern rock bolts or anchors, p. 11
- 5.3—Shotcrete with rock bolts, friction stabilizers, and welded wire reinforcement, p. 11
- 5.4—Fiber-reinforced shotcrete, p. 12
- 5.5—Shotcrete with lattice girders, p. 13
- 5.6—Shotcrete with conventional steel sets, p. 14
- 5.7—Recommended specifications, p. 14

CHAPTER 6—MATERIALS HANDLING AND STORAGE, p. 15

- 6.1—General, p. 15
- 6.2—Temperature considerations, p. 15
- 6.3—Recommended specifications, p. 16

CHAPTER 7—SHOTCRETE MIXTURE PROPORTIONING, p. 16

- 7.1—General, p. 16
- 7.2—Mixture proportions by trial batching or historical data submissions, p. 16
- 7.3—In-place mixture proportions, p. 16
- 7.4—Dry-mix shotcrete, p. 17
- 7.5—Wet-mix shotcrete, p. 18
- 7.6—Recommended specifications, p. 20

CHAPTER 8—PERFORMANCE REQUIREMENTS, p. 20

- 8.1—General, p. 20
- 8.2—Water-cementitious materials ratio, p. 20
- 8.3—Air content, p. 20
- 8.4—Slump, p. 21
- 8.5—Boiled absorption and permeable voids, p. 21
- 8.6—Compressive strength, p. 21
- 8.7—Flexural strength and toughness, p. 21
- 8.8—Early-age strength, p. 21
- 8.9—Other tests, p. 22
- 8.10—Bond strength, p. 22
- 8.11—Fire-induced explosive spalling protection, p. 22
- 8.12—Recommended specifications, p. 22

CHAPTER 9—QUALITY ASSURANCE AND QUALITY CONTROL, p. 23

- 9.1—General, p. 23
- 9.2—Recommended specifications, p. 24

CHAPTER 10—PRECONSTRUCTION TRIALS AND TESTING, p. 24

- 10.1—General, p. 24
- 10.2—Recommended specifications, p. 24

CHAPTER 11—CONSTRUCTION ACCEPTANCE INSPECTION, p. 26

- 11.1—General, p. 26
- 11.2—Acceptance inspection, p. 26
- 11.3—Specific inspection and testing quality control requirements for underground shotcrete, p. 28

- 11.4—Cold placement conditions, p. 29
- 11.5—Hot placement conditions, p. 29
- 11.6—Shotcrete acceptance and rejection, p. 29
- 11.7—Recommended specifications, p. 30
- 11.8—Recommended QC Inspection and Testing Checklist, p. 32

CHAPTER 12—BATCHING, MIXING, AND SUPPLY, p. 33

- 12.1—Handling of bulk bin-bags, p. 33
- 12.2—Quality control considerations, p. 33
- 12.3—Recommended specifications, p. 33

CHAPTER 13—PLACING EQUIPMENT, p. 35

- 13.1—General, p. 35
- 13.2—Pumps for wet-mix, p. 35
- 13.3—Guns for dry-mix, p. 35
- 13.4—Nozzle systems, p. 36
- 13.5—Remote-controlled spraying, p. 36
- 13.6—Recommended specifications, p. 37

CHAPTER 14—AUXILIARY EQUIPMENT, p. 38

- 14.1—Air supply, p. 38
- 14.2—Recommended specifications, p. 39

CHAPTER 15—SAFETY, p. 40

- 15.1—General, p. 40
- 15.2—Underground safety, p. 40
- 15.3—Required personal safety equipment, p. 40
- 15.4—View of shotcrete work, p. 41
- 15.5—Communications, p. 41
- 15.6—Nonpersonal safety equipment, p. 42
- 15.7—Recommended specifications, p. 42

CHAPTER 16—PREPARATION FOR SHOTCRETING AND GROUNDWATER CONTROL, p. 43

- 16.1—General, p. 43
- 16.2—Factors affecting shotcrete adhesion and bonding, p. 43
- 16.3—Surface preparation, p. 44
- 16.4—Groundwater, p. 44
- 16.5—Recommended specifications, p. 45

CHAPTER 17—GROUND REINFORCEMENT INSTALLATION, p. 46

- 17.1—General, p. 46
- 17.2—Rock bolt installation, p. 46
- 17.3—Steel set installation, p. 46
- 17.4—Lattice girder installation, p. 46
- 17.5—Face support, p. 47
- 17.6—Recommended specifications, p. 47

CHAPTER 18—SHOTCRETE APPLICATION, p. 47

- 18.1—Methods used to control thickness, p. 47
- 18.2—Cover, alignment, and tolerance, p. 47
- 18.3—Recommended specifications, p. 48

CHAPTER 19—CURING AND PROTECTION, p. 50

19.1—General, p. 50

19.2—Protection, p. 50

19.3—Recommended specifications, p. 51

CHAPTER 20—SHOTCRETE FOR REPAIR AND REHABILITATION OF UNDERGROUND STRUCTURES, p. 52

20.1—General, p. 52

20.2—Materials selection, p. 52

20.3—Shotcrete placement methods for repair, p. 53

20.4—Quality assurance requirements for rehabilitation of underground structures, p. 53

20.5—Repair considerations, p. 53

20.6—Recommended specifications, p. 54

CHAPTER 21—MEASUREMENT AND PAYMENT, p. 54

21.1—Basis for payment, p. 54

21.2—Recommended specifications, p. 55

CHAPTER 22—REFERENCES, p. 55

Authored documents, p. 56

CHAPTER 1—INTRODUCTION AND SCOPE**1.1—Introduction**

In North America, the term “shotcrete” is used and defined by the American Concrete Institute’s “ACI Concrete Terminology” as “concrete placed by a high-velocity pneumatic projection from a nozzle”, while in Europe, shotcrete is commonly referred to as “sprayed concrete”.

Shotcrete is ideally suited for underground applications in tunneling and mining as an initial support in soft ground as well as hard rock, as an installation method for final linings, or in underground rehabilitation or expansion projects.

The pneumatic projection of shotcrete onto a surface at high velocity provides specific quality enhancements that interact with the ground surface and prepared substrates, providing superior bond characteristics, increased density, strength, durability, and toughness. In addition, shotcrete provides the geometrical and operational flexibility required for many underground operations and—especially if sprayed using robotic equipment—provides a safer working environment, compared to other support installation methods under unsupported ground or if immediate support is needed. These qualities are desirable in ground support and lining applications and provide economic and technical advantages compared to the other initial support systems and materials.

Cast-in-place (CIP) concrete is widely used in underground tunneling for final linings, especially if a constant cross section geometry over long distances allows the use of highly mechanized formwork. However, if the geometry is changing or the tunnel is too short to justify the investment for a mechanized formwork, shotcrete has many advantages over CIP concrete for final linings due to the inherent flexibility of the method to cover a large range of opening

shapes and sizes. This allows for certain structures such as enlarged cross sections, intersections, or penetrations to be constructed with less effort in comparison to CIP concrete.

Geometrical flexibility for final linings is also a key advantage for rehabilitation and expansion projects. In addition, many of these projects are constructed under stringent operational limitations, providing, for example, very limited and strict time windows for construction. The operational flexibility of shotcrete allows for a stop-and-go installation of concrete and provides a key advantage of shotcrete over other installation methods.

Shotcrete technology has been broadly developed throughout the construction industry over the last century. The evolution of mining and civil tunneling methods has placed unique demands on the materials, equipment, and personnel that comprise current concepts of a shotcrete system for underground support and lining construction. With this gradual evolution in technology and trial and error came acceptance, adaptation, and new means and methods of successful shotcrete application.

The design, working conditions, and placement of shotcrete underground are unique, very demanding, and generally much more challenging than shotcreting above ground. The majority of underground shotcrete is installed overhead or subvertical, making the correct installation technique and strength development over time crucial.

The primary focus during shotcrete installation underground is worker safety, due to the need to provide immediate and effective ground support and to use proper installation procedures to avoid fallouts of fresh concrete. For the construction industry as a whole, the specification of a 28-day compressive strength is typically sufficient; however, the early strength performance of underground shotcrete during the first hours or days is often critical. Much of the shotcrete is applied overhead to irregular surface substrate profiles immediately following blasting or other modes of excavation. Geological and groundwater conditions are not always predictable; opening stability and rockfalls present a clear hazard to the underground workers. Conditions may be such that the window available for shotcrete application is minutes or a few hours. The use of accelerating admixtures is a unique feature of underground shotcrete application in that it provides a means of controlled and rapid strength gain immediately following application.

Tunneling or mining activities typically take place on a continuous and cyclical basis. The process of excavation, muck removal or mineral extraction, and ground support installation are repeated in every excavation and support round. To be viable and acceptable, shotcrete application should be an integral part of the overall cycle. This requires that the shotcrete system be reliable, efficient, and effective.

The underground environment can impose significant constraints and demands on the batching, mixing, handling, and placement of shotcrete. The unique logistical demands associated with underground shotcrete application may require access to the underground work area via shaft, adit, and ramp, and the subsequent use of long and restrictive haulage routes or dropping concrete through a borehole or