

# Guidance for the Development of Ultrasonic Examiner Qualification Programs

API BULLETIN 587  
FIRST EDITION, MAY 2021



American  
Petroleum  
Institute

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees, represent that use of this publication would not infringe upon privately owned rights.

Classified areas may vary depending on the location, conditions, equipment, and substances involved in any given situation. Users of this specification should consult with the appropriate authorities having jurisdiction.

Users of this standard should not rely exclusively on the information contained in this standard. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein. API is not undertaking to meet the duties of employers, service providers, or suppliers to warn and properly train and equip their employees, and others exposed, concerning health and safety risks and precautions, or in undertaking their obligations to comply with authorities having jurisdiction.

Information concerning safety and health risks and proper precautions with respect to particular materials and conditions should be obtained from the employer, the service provider or supplier of that material, or the material safety datasheet.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be used. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001-5571.

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, “can” denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001, [standards@api.org](mailto:standards@api.org).

## Contents

	Page
<b>1</b> Purpose .....	1
<b>1.1</b> Scope.....	1
<b>2</b> Normative References .....	
<b>3</b> Terms, Definitions, Acronyms, and Abbreviations .....	2
<b>3.1</b> Terms and Definitions .....	2
<b>3.2</b> Acronyms and Abbreviations .....	3
<b>4</b> Specimens for Performance Demonstration Tests.....	4
<b>4.1</b> Sample Identification .....	4
<b>4.2</b> Detection and Characterization Test Set Specimen Design .....	4
<b>4.3</b> Crack Height Sizing Test Set Specimen Design .....	6
<b>4.4</b> Alternate Specimen Designs .....	7
<b>4.5</b> Test Set Validation .....	7
<b>5</b> Exam Security.....	7
<b>5.1</b> Exam Monitoring.....	8
<b>5.2</b> Pre- and Post-Test.....	8
<b>5.3</b> During the Test.....	8
<b>6</b> Test Administration.....	9
<b>6.1</b> Pre-Test Preparation.....	9
<b>6.2</b> During the Test.....	11
<b>6.3</b> Post-Test Administration—Grading.....	12
Annex A (informative) Sample Forms for Use During Performance Demonstration Tests .....	15

## Figures

<b>1</b> Photograph of Performance Demonstration Test Sets for Detection and Characterization (left) and Crack Sizing (right).....	4
<b>2</b> Cross-sectional View of Detection and Characterization Test Set.....	5
<b>3</b> Cross-sectional View of Crack Sizing Test Set .....	6
<b>A.1</b> Equipment Inventory Form .....	16
<b>A.2</b> Phased Array Equipment Inventory Form.....	17
<b>A.3</b> Angle Beam Calibration Form.....	18
<b>A.4</b> Phased Array Calibration Form.....	19
<b>A.5</b> Single Vee Weld Indication Report Form.....	20
<b>A.6</b> Double Vee Weld Indication Report Form.....	21
<b>A.7</b> QUSE Crack Height Sizing Report Form.....	22
<b>A.8</b> QUSE-PA Crack Height Sizing Report Form .....	23

## Tables

<b>1</b> Defect Types for QUTE and QUPA Test Specimens.....	6
---	---

## Contents

	Page
2 Example of the Test Schedule .....	11
3 Required Fields for Qualification Test Program Forms .....	12
4 Flaw Characterization Groups .....	13

Currently in preview, click buy full version

# Guidance for the Development of Ultrasonic Examiner Qualification Programs

## 1 Purpose

The purpose of this publication is to provide owner/users with guidelines for developing basic in-house qualification programs to identify industry-qualified ultrasonic testing (UT) angle beam examiners that are equivalent to those possessing an ultrasonic angle beam qualification from API (e.g. API QUTE/QUSE detection and sizing tests) for inspection of pressure equipment and piping as required by API 510 and API 570. The availability of high-quality and accurate UT data is often the cornerstone for weld and base metal discontinuity detection and sizing for equipment integrity assessments. As a result, API has implemented several certification programs to assist in defining the minimum criteria for assessing the performance of UT technicians. Examinations for these programs are administered differently than other Individual Certification Program (ICP) certifications in that they are based on hands-on performance demonstration tests. It should be noted that UT certifications are issued by accredited NDE certification authorities, such as the American Society for Nondestructive Testing (ASNT), and the API UT ICP certifications are considered performance demonstration qualifications by such NDE certification schemes.

### 1.1 Scope

This publication outlines the general guidelines for the development of owner/user ultrasonic examiner qualification programs that are consistent with API performance demonstration programs for detection, characterization, and crack height sizing of weld discontinuities in weldments. The performance demonstration programs covered in this publication include the following:

#### 1.1.1 Qualification of Ultrasonic Testing Examiners for Detection and Characterization of Flaws Using Manual Angle Beam Testing: QUTE

QUTE exam description: Exam candidates use manual ultrasonic flaw-detection instruments to examine new construction carbon steel pipe and plate welds manufactured to ASME code requirements. Candidate performance measures include flaw detection, characterization, length sizing, and false calls.

#### 1.1.2 Qualification of Ultrasonic Testing Examiners for Detection and Characterization of Flaws Using Manual UT-Phased Array: QUPA

QUPA exam description: Exam candidates use manual ultrasonic phased array instrumentation to examine new construction carbon steel pipe and plate welds manufactured to ASME code requirements. Candidate performance measures include flaw detection, characterization, length sizing, and false calls.

#### 1.1.3 Qualification of Ultrasonic Testing Examiners for Manual UT-Angle Beam Crack Sizing: QUSE

QUSE exam description: Exam candidates use manual ultrasonic flaw detector instrumentation to size opposite side cracking in new construction carbon steel plate welds with and without weld crowns in place.

#### 1.1.4 Qualification of Ultrasonic Testing Examiners for Manual UT-Phased Array Crack Sizing: QUSE-PA

QUSE-PA exam description: Exam candidates use manual ultrasonic phased array instrumentation to size opposite side cracking in new construction carbon steel plate welds with and without weld crowns in place.

1.2 Weld specimens for the QUTE, QUPA, QUSE, and QUSE-PA exams are single- or double-bevel carbon steel plate or pipe welds 0.50 in.–1.00 in. (12.5 mm–25 mm) in thickness. See Section 4 for specimen details.

## 2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.