

Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe, and Line Pipe Properties

API BULLETIN 5C3
SIXTH EDITION, OCTOBER 1, 1994

Contains ISO 10400:1993

**Petroleum and natural gas industries—Formulae and calculations for casing,
tubing, drill pipe and line pipe properties**

American Petroleum Institute
1220 L Street, Northwest
Washington, D.C. 20005



Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe, and Line Pipe Properties

Exploration and Production Department

API BULLETIN 5C3
SIXTH EDITION, OCTOBER 1, 1994

**American
Petroleum
Institute**



SPECIAL NOTES

Note: This section is not part of ISO 10400:1993.

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

API is not undertaking to meet the duties of employers, manufacturers, or suppliers to warn and properly train and equip their employees, and others exposed, concerning health and safety risks and precautions, nor undertaking their obligations under local, state, or federal laws.

Information concerning safety and health risks and proper precautions with respect to particular materials and conditions should be obtained from the employer, the manufacturer or supplier of that material, or the material safety data sheet.

Nothing contained in any API publication is to be construed as granting any right, implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. Sometimes a one-time extension of up to two years will be added to this review cycle. This publication will no longer be in effect five years after its publication date as an operative API standard or, where an extension has been granted upon republication. Status of the publication can be ascertained from the API Authoring Department [telephone (214) 953-1101]. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the development process and is designated as an API *standard*. Questions concerning the interpretation of the content of this standard or comments and questions concerning the procedure under which this standard was developed should be directed in writing to the director of the Exploration and Production Department, American Petroleum Institute, 700 North Pearl, Suite 1840, Dallas, Texas 75201. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or the violation of any federal, state, or municipal regulation with which this publication may conflict.

API standards are published to facilitate the broad availability of proven, sound engineering and operating practices. These standards are not intended to obviate the need for applying sound engineering judgment regarding when and where these standards should be utilized. The formulation and publication of API standards is not intended in any way to inhibit anyone from using any other practices.

Every manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Copyright © 1994 American Petroleum Institute

CONTENTS

FOREWORD	vii
1 SCOPE	1
2 COLLAPSE PRESSURE	1
2.1 Collapse Pressure Formulas	1
2.2 Derivation of Collapse Pressure Formulas	6
2.3 Collapse Testing Procedure	11
2.4 Application of Collapse Pressure Formulas to Line Pipe	13
3 PIPE BODY YIELD STRENGTH	14
3.1 Pipe Body Yield Strength	14
3.2 Application of Pipe Body Yield Strength Formula to Line Pipe	14
4 INTERNAL PRESSURE RESISTANCE	14
4.1 Internal Yield Pressure	14
4.2 Internal Pressure Leak Resistance at E_1 or E_7 Plane	15
4.3 Application of Internal Pressure Resistance Formulas to Line Pipe	16
5 JOINT STRENGTH	16
5.1 Round Thread Casing Joint Strength	16
5.2 Buttress Thread Casing Joint Strength	17
5.3 Extreme-Line Casing Joint Strength	18
5.4 Tubing Joint Strength	19
5.5 Joint Strength of Round Thread Casing With Combined Bending and Internal Pressure	20
5.6 Line Pipe Joint Strength	21
6 WEIGHTS	21
6.1 Nominal Weight	21
6.2 Calculated Plain-End Weight	22
6.3 Calculated Threaded and Coupled Weight	22
6.4 Calculated Upset and Threaded Weight for Integral Joint Tubing and Extreme-Line Casing	23
6.5 Calculated Upset Weight	23
6.6 Weight Gain Due to End Finishing	24
6.7 Calculated Coupling Weight	24
6.8 Calculated Weight Removed in Threading	27
6.9 Calculated Weight of External Upsets	30
6.10 Calculated Weight of Internal Upsets	31
6.11 Calculated Weight of External-Internal Upsets	31
6.12 Calculated Weight of Extreme-Line Upsets	31
7 ELONGATION	33
8 FLATTENING TESTS	33
8.1 Flattening Tests for Casing and Tubing	33
8.2 Flattening Tests for Line Pipe	33
9 HYDROSTATIC TEST PRESSURES	33
9.1 Hydrostatic Test Pressures for Plain-End Pipe, Extreme-Line Casing, and Integral-Joint Tubing	33
9.2 Hydrostatic Test Pressure for Threaded and Coupled Pipe	34
10 MAKEUP TORQUE FOR ROUND THREAD CASING AND TUBING	36

11	GUIDED BEND TESTS FOR SUBMERGED ARC WELDED LINE PIPE	37
12	DETERMINATION OF MINIMUM IMPACT SPECIMEN SIZE FOR API COUPLINGS AND PIPE	38
12.1	Critical Thickness	38
12.2	Calculated Coupling Blank Thickness	38
12.3	Calculated Wall Thickness for Transverse Specimens	38
12.4	Calculated Wall Thickness for Longitudinal Specimens	39
12.5	Minimum Specimen Size for API Couplings	39
12.6	Impact Specimen Size for Pipe	40
12.7	Larger Size Specimens	40
12.8	Reference Information	40
13	METRICATION	44
13.1	Metric Conversions and Calculations	44
13.2	Rounding of Metric Units	44
14	CALCULATION ACCURACY AND ROUNDING	45
14.1	Accuracy	45
14.2	Intermediate Rounding	45
14.3	Final Rounding	45
Figures		
1	—Grade N-80 Transition Collapse Formula Derivation	10
2	—Ovality Gauge	13
3	—Coupled Pipe	22
4	—Upset Pipe	23
5	—Upset Pipe—Both Ends	23
6	—Pipe Coupling	25
7	—Pipe Coupling With Special Bevel	26
8	—Weight Calculations for Buttress Thread Couplings	27
9	—Round Threads and Line Pipe Threads	27
10	—Buttress Threads	28
11	—Extreme-Line Thread	28
12	—Integral Joint Tubing	29
13	—Extreme-Line Casing	30
14	—External Upset	30
15	—Internal Upset	31
16	—Pin Upset	32
17	—Box Upset	32
18	—Guided Bend Test Jig	37
Tables		
1	—Yield Collapse Pressure Formula Range	2
2	—Formula Factors and D/t Range for Plastic Collapse	3
3	—Formula Factors and D/t Range for Transition Collapse	4
4	— D/t Range for Elastic Collapse	5
5	—Average Plastic Collapse Pressure Regression Formulas	7
6	—Tolerance Limit C to Be Subtracted From Average Collapse Formulas to Convert to a Minimum Base	9
7	—Flattening Tests—Distance Between Plates	34
8	—Factors for Test Pressure Formulas	35
9	—Critical Thickness of Various API Couplings	39
10	—Calculated Coupling Blank Thickness for API Couplings	40
11	—Transverse Impact Specimen Size Required for API Couplings	41
12	—Longitudinal Impact Specimen Size Required for API Couplings	42

13—Minimum Size Transverse Charpy Impact Test Specimens for Various API Couplings	43
14—Minimum Size Longitudinal Charpy Impact Test Specimens for API Couplings for All Pipe Less Than 3½-Inch Outside Diameter and for Larger Sizes Where Transverse Test Specimens One-Half Size or Larger Are Not Possible	43
15—Number of Decimals to Be Shown in Metric Units	44

Currently in preview, click buy full version

FOREWORD

Note: This section is not part of ISO 10400:1993.

API Bulletin 5C3 serves as the basis for ISO 10400:1993. The complete text of both the API and ISO standards is contained in this document. Some differences exist between the API version and the ISO version of this standard; for example:

- The Special Notes and Foreword are not part of ISO 10400:1993.
- Section 12 is not part of ISO 10400:1993.

Language that is unique to the ISO version is shown in ***bold oblique type*** in the text or, where extensive, is identified by a note under the title of the section. Language that is unique to the API version is identified by a note under the title of the section or is shaded. The bar notations identify parts of this publication that have been changed from the previous API edition.

This standard is under the jurisdiction of the Committee on Standardization of Tubular Goods.

This standard shall become effective on the date printed on the cover but may be used voluntarily from the date of distribution.

Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe, and Line Pipe Properties

1 Scope

The purpose of this bulletin is to show the formulas used in the calculation of the various pipe properties given in API standards, including background information regarding their development and use. This bulletin is under the jurisdiction of the Committee on Standardization of Tubular Goods.

2 Collapse Pressure

2.1 COLLAPSE PRESSURE FORMULAS

The minimum collapse pressures given in API Bulletin 5C2 are calculated by means of Formulas 1, 3, 5, and 7, adopted at the 1968 Standardization Conference and reported in API Circular PS-1360 dated September 1968.

Formulas 2, 4, and 6 for the intersections between the four collapse pressure formulas have been determined algebraically and used for calculating the applicable D/t range for each collapse pressure formula. Factors A, B, C, F, and G have been calculated using Formulas 21, 22, 23, 26, and 27. When determining the appropriate formula to be used for calculating collapse resistance for a particular D/t ratio and minimum yield strength, the D/t ranges determined by Formulas 2, 4, and 6 govern, rather than the collapse formula that gives the lowest collapse pressure. The D/t ranges are given in Tables 1, 2, 3, and 4.

The collapse pressures for API Bulletin 5C2 are calculated using the specified values for D and t , rounding D/t to two decimals carrying eight digits in all intermediate calculations and rounding the collapse pressure to the nearest 10 pounds per square inch.

Theoretical studies of the effect of ovality on tubular collapse resistance consistently indicate that an ovality of 1 to 2 percent can effect a reduction in collapse resistance on the order of 25 percent. However, experimental/empirical investigations indicate a much smaller effect. Test data indicate that ovality is only one of many pipe parameters that influence collapse (including residual stress, isotropy, shape of stress-strain curve/microstructure, and yield strength). A thorough review of industry collapse data indicates that the influence of ovality does not warrant singling out the ovality as a dominant parameter. A work group on collapse resistance concluded the effect of ovality on tubular collapse has been handled during the adjustment of average collapse predictions to minimum performance values and ovality should not be awarded the status of an independent variable in an API formula for collapse performance.

2.1.1 Yield Strength Collapse Pressure Formula

The yield strength collapse pressure is not a true collapse pressure, but rather the external pressure, P_{Y_p} , that generates minimum yield stress, Y_p , on the inside wall of a tube as calculated by Formula 1.

$$P_{Y_p} = 2Y_p \left[\frac{(D/t) - 1}{(D/t)^2} \right] \quad (1)$$

Formula 1 for yield strength collapse pressure is applicable for D/t values up to the value of D/t corresponding to the intersection with the plastic collapse Formula 3. This intersection is calculated by Formula 2 as follows: