

Recommended Practice for Testing Well Cements

**ANSI/API Recommended Practice 10B-2 (Formerly 10B)
First Edition, July 2005
Identical to ISO 10426-2:2003 including
ISO 10426-2:2005/FDAM 1:2005**

ISO 10426-2, Petroleum and natural gas industries—Cements and materials for well cementing—Part 2: Testing of well cements

AMENDMENT 1: Water-wetting capability testing



API

American Petroleum Institute

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

These materials are subject to copyright claims of ISO, ANSI and API.

All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.

Copyright © 2005 American Petroleum Institute

API Foreword

This standard API RP 10B-2, *Recommended Practice for Testing Well Cements*, replaces API RP 10B 22nd edition of the same title. The designation change is to align with the ISO designation.

This standard shall become effective on the date printed on the cover but may be used voluntarily from the date of distribution.

Standards referenced herein may be replaced by other international or national standards that can be shown to meet or exceed the requirements of the referenced standard.

This American National Standard is under the jurisdiction of the API Subcommittee on Well Cements, SC10. This standard is considered identical to the English version of ISO 10426-2. ISO 10426-2 was prepared by Technical Committee ISO/TC 67 Materials, equipment and offshore structures for petroleum and natural gas industries, SC 3 Drilling and completion fluids, and well cements.

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards and Publications Department, API, 1220 L Street, NW, Washington, DC 20005, standards@api.org.

Petroleum and natural gas industries — Cements and materials for well cementing — Part 2: Testing of well cements

AMENDMENT 1: Water-wetting capability testing

Page 6, clause 3.1

Add the following term/definition:

3.1.52

water-wetting capability

capability of a fluid to alter the quality or state of being water-wetted

NOTE A fully water-wet state is considered most desirable to provide cement bonding.

Page 96, add the following new clause 16.8:

16.8 Water-wetting capability testing (WWCT)

16.8.1 Introduction

The water-wetting capability testing (WWCT) procedure is intended for use in determining the degree of compatibility of wellbore fluids in cementing operations. By the use of this procedure, the selection of proper preflushes and/or spacers, and/or surfactant components may be made when required. User discretion should be exercised in the selection of the portion(s) of the procedure needed.

The WWCT procedure is specific to evaluation of water-wetting capability of spacers and/or preflushes designed to water-wet the surfaces after these surfaces have been exposed to non-aqueous fluids, specifically oil- and synthetic-based drilling fluids. The apparent water-wetting capability of various mud/spacer interface volumes and the apparent wettability of spacer systems against oil-wetted surfaces may be evaluated using this method. This procedure does not address bulk displacement issues, nor does it directly address spacer/mud compatibility issues.

The procedure is applicable to aqueous spacer systems only. This procedure is not suitable for evaluating non-aqueous or non-conductive systems or mixtures of surfactants in base oils.

16.8.2 Method and apparatus

The apparatus provides a continuous measurement of the electrical conductivity between electrode surfaces. From the conductivity measurements, the emulsion state and apparent wettability of the fluid can be inferred if the titrating spacer fluid is conductive and the titrated drilling fluid is not. Normally, oil-external fluids are not electrically conductive. Water-based or water-external emulsion spacers are electrically conductive with the actual conductivity dependent on the solution chemistry.

16.8.3 Procedure

Observe all usual laboratory safety requirements pertaining to working with oil, synthetic, and solvent-based fluids. Note the flash points of all fluids before testing and ensure proper ventilation in the work area. All safe-handling procedures for the fluids being tested shall be observed.

16.8.4 Sample preparation

- 1) Prepare a mud sample according to instructions from the supplier. Laboratory-prepared mud samples may require additional preparation such as static aging or hot-rolling to more fully simulate field mud properties.
- 2) Mix the spacers and/or preflush fluids to be evaluated according to manufacturer's procedures. A 500-ml volume is normally sufficient to run a single test.
- 3) Condition all spacer fluids at anticipated Bottom Hole Circulating Temperature (BHCT) to ensure that fluids are stable and all chemicals have been conditioned and are in solution. If desired, the fluids may be conditioned for an additional 30 min \pm 0,5 min at BHCT. Condition fluids under pressure using high-temperature, high-pressure (HTHP) equipment if conditioning at temperatures above 90°C (194°F). Fluids should be cooled below 90° (194°F) before releasing pressure. Observe all handling procedures for fluids being tested. This is a test conducted at atmospheric pressure. The test shall not be performed at temperatures exceeding 90°C (194°F).

16.8.5 Equipment set-up

- 1) Prepare equipment according to instructions from supplier.
- 2) Clean and dry test equipment before starting.
- 3) Add the mud sample to the container.
- 4) Heat the container to testing conditions to maintain the temperature of the test fluids. Use a stirring rate sufficient to quickly homogenise added fluids and prevent static areas. Avoid excessive shear, as it will cause air-entrainment that may affect readings and surfactant performance.

16.8.6 Test procedure and reporting

- 1) Evaluate the interaction of the spacer with the drilling fluid according to manufacturer's instructions. Observe safety precautions with respect to fluid temperatures and operator safety.
- 2) Record the starting volume of mud, volume of titrant (surfactant, flush, spacer), fluid conditioning procedure (time, temperature, etc.) and titration temperature. Slowly titrate into the mud while stirring the fluid in the test apparatus. Continue titrating until a stable conductivity measurement is reached. This indicates a water-continuous phase has been formed which is characteristic of a water-wetting state.
- 3) Report test results as the volume percentage of spacer in the mud-spacer mixture that exhibits conductivity measurements indicative of complete water wetting according to the formula:

$$V\% = V_s / (V_s + V_m) \times 100$$

where:

V_s is the volume of spacer required to change from oil to water continuous phase

V_m is the volume of mud initially in the test cell

For example, if 150 ml of spacer must be added to a starting mud volume of 200 ml in order to obtain a full-span reading, the result should be reported as 43 % (150 ml /350 ml).

Contents

	Page
API Foreword	ii
AMENDMENT 1: Water-wetting capability testing	iii
Foreword	iii
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions and symbols	1
3.1 Terms and definitions	1
3.2 Symbols	7
4 Sampling	8
4.1 General	8
4.2 Sampling cement at field location	8
4.3 Sampling cement blends at field location	8
4.4 Sampling dry cement additives at field location	8
4.5 Sampling liquid cement additives at field location	8
4.6 Sampling mixing water	8
4.7 Shipping and storage	10
4.8 Sample preparation prior to testing	10
4.9 Sample disposal	10
5 Preparation of slurry	10
5.1 General	10
5.2 Apparatus	10
5.3 Procedure	12
6 Determination of slurry density	14
6.1 Preferred apparatus	14
6.2 Calibration	14
6.3 Procedure	14
6.4 Alternative apparatus and procedure	16
7 Well-simulation compressive strength tests	16
7.1 General	16
7.2 Sampling	16
7.3 Preparation of slurry	17
7.4 Apparatus	17
7.5 Procedure	18
7.6 Determination of cement compressive strength at the top of long cement columns	20
8 Non-destructive sonic testing of cement	26
8.1 General	26
8.2 Apparatus	26
8.3 Sampling	26
8.4 Preparation of slurry	26
8.5 Procedure	26
8.6 Curing time	26
8.7 Curing schedules	26
8.8 Data reporting	27
9 Well-simulation thickening-time tests	27
9.1 General	27
9.2 Apparatus and material	27
9.3 Calibration	28
9.4 Test procedure	30

9.5	Determination of test schedule.....	32
10	Static fluid-loss tests	38
10.1	General	38
10.2	Apparatus.....	38
10.3	Safety.....	39
10.4	Mixing procedure.....	39
10.5	Conditioning procedures.....	39
10.6	Procedures for testing at temperatures ≤ 88 °C (190 °F).....	39
10.7	Procedures for testing at temperatures > 88 °C (190 °F).....	40
10.8	Filling the static fluid-loss cell	42
10.9	Fluid loss test	43
10.10	Test completion and clean-up.....	43
11	Permeability tests.....	45
11.1	General	45
11.2	Apparatus.....	45
11.3	Sample preparation.....	46
11.4	Liquid permeability (cement permeameter).....	46
11.5	Alternative procedure (core permeameter) for liquid permeability.....	47
11.6	Calculating liquid permeability	50
11.7	Gas permeability (core permeameter).....	50
11.8	Calculating gas permeability.....	51
12	Determination of rheological properties and gel strength using a rotational viscometer	52
12.1	General	52
12.2	Apparatus.....	52
12.3	Calibration.....	54
12.4	Determination of rheological properties	54
12.5	Determination of gel strength	56
12.6	Modelling of the rheological behaviour	57
13	Calculation of pressure drop and flow regime for cement slurries in pipes and annuli	65
13.1	General	65
13.2	Newtonian fluids.....	67
13.3	Power Law fluids.....	71
13.4	Bingham Plastic fluids.....	77
13.5	Conversion factors.....	87
14	Test procedure for arctic cementing slurries.....	87
14.1	General	87
14.2	Preparation of cement slurry.....	87
14.3	Fluid fraction.....	87
14.4	Thickening time	87
14.5	Compressive strength	87
14.6	Freeze-thaw cycling at atmospheric pressure	88
14.7	Compressive strength cyclic testing.....	88
15	Well-simulation slurry stability tests.....	88
15.1	Introduction.....	88
15.2	Slurry mixing.....	89
15.3	Slurry conditioning.....	89
15.4	Free fluid test with heated static period	89
15.5	Free fluid test with ambient temperature static period	90
15.6	Sedimentation test	90
16	Compatibility of wellbore fluids	94
16.1	General	94
16.2	Preparation of test fluids	94
16.3	Rheology	95
16.4	Thickening time	95
16.5	Compressive strength	95
16.6	Solids suspension and static gel strength	96

16.7	Fluid loss	96
17	Pozzolans	98
17.1	General	98
17.2	Types of pozzolan	98
17.3	Physical and chemical properties	98
17.4	Slurry calculations	99
17.5	Bulk volume of a blend	100
Annex A (normative) Procedure for preparation of large slurry volumes		102
Annex B (normative) Calibration procedures for thermocouples, temperature-measuring systems and controllers		104
Annex C (informative) Additional information relating to temperature determination		106
Annex D (normative) Alternative apparatus for well thickening-time tests		113
Annex E (informative) Cementing schedules		116
Bibliography		171

Foreword

ISO (the International Organisation for Standardisation) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organisations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardisation.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10426-2 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids and well cements*.

ISO 10426 consists of the following parts, under the general title *Petroleum and natural gas industries — Cements and materials for well cementing*:

- *Part 1: Specification*
- *Part 2: Testing of well cements*
- *Part 3: Testing of deepwater well cement formulations*
- *Part 4: Preparation and testing of foamed cement slurries at atmospheric pressure*

The following part is under preparation:

- *Part 5: Determination of shrinkage and expansion of well cement formulations at atmospheric pressure*

Introduction

This part of ISO 10426 is based on API RP 10B, 22nd edition, December 1997, addendum 1, October 1999.

Users of this part of ISO 10426 should be aware that further or differing requirements may be needed for individual applications. This part of ISO 10426 is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this part of ISO 10426 and provide details.

In this part of ISO 10426, where practical, US Customary units are included in brackets for information.

Well cement classes and grades are defined in ISO 10426-1.

Petroleum and natural gas industries — Cements and materials for well cementing —

Part 2: Testing of well cements

1 Scope

This part of ISO 10426 specifies requirements and gives recommendations for the testing of cement slurries and related materials under simulated well conditions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10414-1, *Petroleum and natural gas industries — Field testing of drilling fluids — Part 1: Water-based fluids*

API RP 13J, *Testing of heavy brines (second edition), March 1996*

ASTM C 109, *Standard test method for compressive strength of hydraulic cement mortars (using 2 in. or [50 mm] cube specimens)*

ASTM C 188, *Standard test method for density of hydraulic cement*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

absolute volume

reciprocal of absolute density

NOTE It is expressed as volume per unit mass.

3.1.2

additive

material added to a cement slurry to modify or enhance some desired property

NOTE Common properties that are modified include: setting time (by use of retarders or accelerators), fluid loss control, viscosity, etc.