

# Recommended Practice for Testing Well Cements

API RECOMMENDED PRACTICE 10B-2  
THIRD EDITION, JULY 2024



American  
Petroleum  
Institute

Currently in preview, click buy full version

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue NW, Suite 1100, Washington, DC 20001.

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard. Can: As used in a standard, “can” denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue NW, Suite 1100, Washington, DC 20001, [standards@api.org](mailto:standards@api.org).

Currently in preview, click buy full version

# Contents

	Page
1	Scope ..... 1
2	Normative References ..... 1
3	Terms, Definitions, Acronyms, Abbreviations, and Symbols ..... 1
3.1	Terms and Definitions ..... 1
3.2	Symbols, Acronyms, and Abbreviations ..... 6
4	Sampling ..... 10
4.1	General ..... 10
4.2	Sampling Cement at a Field Location ..... 10
4.3	Sampling Cement Blends at a Blending Facility ..... 10
4.4	Sampling Dry Cement Additives ..... 10
4.5	Sampling Liquid Cement Additives ..... 11
4.6	Sampling Mix Water ..... 11
4.7	Shipping and Storage ..... 12
4.8	Sample Preparation Prior to Testing ..... 12
4.9	Sample Disposal ..... 12
5	Preparation of Slurry ..... 12
5.1	General ..... 12
5.2	Apparatus ..... 13
5.3	Procedure ..... 14
5.4	Test Fluid Conditioning ..... 24
6	Determination of Slurry Density ..... 26
6.1	Apparatus ..... 26
6.2	Procedure ..... 26
7	Well-simulation Compressive-strength Tests ..... 27
7.1	General ..... 27
7.2	Sampling ..... 27
7.3	Apparatus ..... 28
7.4	Procedure ..... 30
7.5	Determination of Cement Strength at the Top of a Long Cement Column ..... 34
8	Nondestructive Sonic Correlation of Compressive Strength of Cement ..... 40
8.1	General ..... 40
8.2	Apparatus ..... 40
8.3	Sampling ..... 40
8.4	Preparation of Slurry ..... 40
8.5	Procedure ..... 40
8.6	Curing Time ..... 40
8.7	Curing Schedules ..... 40
8.8	Data Recording, Calculating, and Optional Crush Verification ..... 41
9	Well-simulation Thickening-time Tests ..... 41
9.1	General ..... 41
9.2	Apparatus and Material ..... 42
9.3	Thickening-time Test Procedure ..... 43
9.4	Determination of Thickening-time Test Schedules ..... 45
10	Static Fluid-loss Tests ..... 55
10.1	General ..... 55
10.2	Apparatus ..... 55
10.3	Safety ..... 57
10.4	Performing Static Fluid-loss Test Using Non-stirred Fluid-loss Cell ..... 57
10.5	Performing a Static Fluid-loss Test Using Stirred Fluid-loss Apparatus ..... 61

10.6	Fluid-loss Results and Reporting .....	65
11	Determination of Rheological Properties and Gel Strength at Atmospheric Pressure Using a Rotational Viscometer.....	67
11.1	General.....	67
11.2	Apparatus .....	67
11.3	Determination of Rheological Properties.....	71
11.4	Determination of Gel Strength .....	74
11.5	Characterization of Rheological Behavior .....	75
12	Well-simulation Slurry Stability Tests .....	77
12.1	Introduction.....	77
12.2	Slurry Mixing and Conditioning .....	77
12.3	Free-fluid Test at Atmospheric Pressure with Static Period at Ambient Temperature or Temperature Equal or Less than 88 °C (190 °F) .....	77
12.4	Free-fluid Tests Under Pressure with Static Temperature Greater than 88 °C (190 °F) .....	79
12.5	Sedimentation Test.....	80
13	Compatibility of Wellbore Fluids.....	86
13.1	General.....	86
13.2	Preparation of Test Fluids .....	86
13.3	Rheological Properties.....	90
13.4	Thickening Time .....	92
13.5	Compressive or Sonic Strength.....	92
13.6	Solids Suspension and Gel Strength .....	92
13.7	Spacer Surfactant Screening Test (SSST) .....	93
13.8	Compatibility of Wellbore Fluids—Interpretation.....	95
14	Test Procedure for Arctic Cementing Slurries .....	97
14.1	General.....	97
14.2	Preparation of Cement Slurry.....	98
14.3	Thickening Time .....	98
14.4	Compressive Strength .....	98
14.5	Strength After Freeze–Thaw Cycling at Atmospheric Pressure .....	99
	Annex A (normative) Procedure for Preparation of Large Slurry Volumes.....	100
	Annex B (normative) Calibration and Verification of Well Cement Testing Equipment.....	102
	Annex C (normative) Alternative Apparatus for Well-simulation Thickening-time Tests .....	123
	Annex D (informative) Cementing Temperatures and Schedules—Not Applicable to Deepwater or Non-vertical Wells.....	126
	Annex E (informative) Determination of Bulk Density of Solids.....	128
	Annex F (informative) Determination of Rheological Properties and Gel Strength Using a Pressurized Rotational Viscometer .....	131
	Annex G (informative) Alternative Slurry Mixing Procedures.....	137
	Annex H (informative) Pozzolan and Fly Ash Materials .....	145
	Bibliography .....	149
	Figures	
1	Commonly Used Sampling Devices .....	11
2	Example of a Typical Cement-mixing Device .....	13
3	Common Blade Assembly .....	14
4	Typical Pressurized Fluid Density Balance .....	27
5	Diagram of Mold Preparation .....	30
6	Typical Pressurized Consistometer.....	42
7	Typical Hesitation-pumping Squeeze-cementing Pressure and Temperature Schedule .....	52

8	Common HPHT, Non-stirred Fluid-loss Cells .....	58
9	Common Screwed-cap Type, HPHT, Double-ended Fluid-loss Cell.....	58
10	Typical Stirred Fluid-loss Apparatus.....	62
11	Cell and Components of a Typical Stirred Fluid-loss Apparatus .....	62
12	Typical Rotational Viscometer Schematic .....	68
13	R1 Rotor and B1 Bob Dimensions .....	69
14	Uncertainty Range of Measurements of Couette Viscometer .....	73
15	Typical Sedimentation Tube.....	81
16	Compatibility Testing Flowchart .....	88
17	Typical Conductivity Titration vs Fresh Water Spacer Volume in SSST Apparatus .....	97
A.1	Example of a Common Cement-mixing Device for Large Volumes .....	100
B.1	Worn Blade (right) Compared to a New One (left).....	103
B.2	Common Calibrating Device for Pressurized Consistometer Potentiometer.....	105
B.3	Fixture for Calibration of Upper Density Range .....	110
B.4	Typical Fluid-loss Screen Tester Cell.....	119
C.1	Alternative Consistometer Design for Well-simulation Thickening Time: Example 1 .....	124
C.2	Alternative Consistometer Design for Well-simulation Thickening Time: Example 2 .....	125
G.1	Pressure Effects on Specific Gravity of Various Hollow Microspheres .....	138
G.2	Example of De-airing Mixing Container.....	143

#### Tables

1	Symbols .....	6
2	Well-simulation API Test Schedules for Curing Strength Specimens (SI Units).....	36
3	Well-simulation API Test Schedules for Curing Strength Specimens (USC Units).....	38
4	Vapor Pressure and Volume Expansion of Water at Temperatures Between 100 °C (212 °F) and 316 °C (600 °F).....	59
5	Fluid-loss Results Reporting Form.....	66
6	Dimensions of Rotors and Bobs .....	69
7	Shear Rate Conversion for Rotor–Bob Configuration.....	70
8	Shear Stress per Degree of Dial Deflection .....	70
9	Example Rheological Data Report.....	74
10	Optional Free-fluid and Sedimentation Results Report Form.....	85
11	Drilling Fluid or Cement Slurry to Spacer Mixtures for Compatibility Testing .....	89
12	Combination Fresh Fluids and Previously Tested Mixtures for Compatibility Testing .....	90
13	Rheological Compatibility of Mud, Cement Slurry, and Spacer .....	91
B.1	Equipment Calibration Requirements .....	103
B.2	Calibration and Verification of Well Cement Testing Equipment .....	104
B.3	Permissible Variation in Mass of Weights (Routine Usage).....	108
B.4	Viscometer Calibration .....	113
B.5	Slurry Consistency's Equivalent Torque (for Potentiometer with Radius of 52 mm ±1 mm).....	115
B.6	Dimensions for 50-mm (2-in.) Cube Molds in Use.....	116
B.7	Density of Distilled Water as a Function of Temperature.....	122
D.1	TPBHC for Casing and Liner Well-simulation Tests .....	126
D.2	TPCP for Squeeze-cementing Well-simulation Tests .....	127
F.1	Dimensions of Rotors and Bobs .....	132
F.2	Shear Rate for Rotor–Bob Configuration.....	133
F.3	Shear Stress per Degree of Dial Deflection .....	133
F.4	Example Rheological Data Report with Dial Readings.....	136

Currently in preview, click buy full version

# Recommended Practice for Testing Well Cements

## 1 Scope

This standard specifies methods and gives recommendations for the testing of cement slurries and related materials under simulated well conditions.

## 2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Specification 10A, *Cements and Materials for Well Cementing*

API Recommended Practice 13I, *Laboratory Testing of Drilling Fluids*

ASTM C109/C109M<sup>1</sup>, *Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)*

ASTM C188, *Standard Test Method for Density of Hydraulic Cement*

## 3 Terms, Definitions, Acronyms, Abbreviations, and Symbols

### 3.1 Terms and Definitions

For the purposes of this document, the following definitions apply.

#### 3.1.1

##### **absolute volume**

The volume occupied by a material, not including the intergranular space in the case of a solid.

NOTE Absolute volume corresponds to the inverse of the density.

#### 3.1.2

##### **additive**

Material incorporated in a cement slurry to modify or enhance some desired property.

#### 3.1.3

##### **annulus**

Space between the pipe and the wellbore wall or an outer pipe.

#### 3.1.4

##### **atmospheric consistometer**

Device used to condition fluids prior to some tests and for determining the thickening time of arctic slurries at atmospheric pressure.

#### 3.1.5

##### **batch mix**

Process of mixing the entire volume of cement slurry prior to placement in the wellbore.

---

<sup>1</sup> ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428, [www.astm.org](http://www.astm.org).