

# Assessment and Management of Pipeline Dents

API RECOMMENDED PRACTICE 1183  
FIRST EDITION, NOVEMBER 2020

ERRATA 1, JANUARY 2021  
ADDENDUM 1, MAY 2024



American  
Petroleum  
Institute

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Copyright © 2020 American Petroleum Institute. All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, “can” denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, Suite 1100, Washington, DC 20001, [standards@api.org](mailto:standards@api.org).

Currently in preview, click buy full version

# Contents

	Page
1 Scope.....	1
2 Normative References .....	2
3 Terms, Definitions, Acronyms, and Abbreviations.....	3
3.1 Terms and Definitions.....	3
3.2 Acronyms and Abbreviations .....	8
4 Guiding Principles.....	10
4.1 General .....	10
4.2 Dent Background .....	12
5 Dent Integrity Management Process .....	14
5.1 Overview.....	14
5.2 Dent Integrity Management Process Overview .....	15
5.3 Significant Parameters .....	21
5.4 Pipeline Service.....	22
5.5 Coincident Features.....	24
6 Pipeline Dent and Operational Condition Characterization.....	24
6.1 Pipe and Dent Geometry.....	24
6.2 Dent Geometry Profile Characterization .....	25
6.3 Identification of Dents with In-Line Inspection Data .....	30
6.4 Restraint Condition .....	32
6.5 Coincident Features and Interacting Defects.....	34
6.6 Operating Condition Severity.....	39
6.7 Material Properties .....	45
7 Dent Screening .....	46
7.1 Qualitative Risk Screening.....	47
7.2 Indentation Formation Strain .....	47
7.3 Failure Pressure .....	49
7.4 Fatigue Life Dent Screening.....	49
7.5 Finite Element Modeling Screening .....	54
8 Detailed Fitness-For-Service Assessment Approaches .....	54
8.1 Dent Failure Assessment .....	55
8.2 Dent Formation Induced Cracking Potential (Dent Strain Assessment).....	57
8.3 Dent Fatigue Life Assessment .....	63
8.4 Safety Factors/Conservatism.....	71
8.5 Probabilistic Assessment .....	72
9 Field Guidance.....	72
9.1 Excavation.....	72
9.2 In-Service Monitoring and Inspection .....	74
9.3 Documentation and Feedback .....	76
9.4 Cutting and Removal .....	77
10 Mitigation and Repair Action Guidance .....	78
10.1 Mitigative Actions.....	78
10.2 Pressure Reduction .....	79
10.3 Re-Evaluation of Operational Pressure History .....	79
10.4 Managing Pressure Cycles.....	79
10.5 Coincident Feature and Interacting Defect Mitigation.....	79
10.6 Repair .....	81
Annex A (informative) Sample Calculations .....	86
Annex B (informative) Dent Crack Initiation Surface, Location, Orientation, and Form .....	101

Annex C (informative) Field Guidance Listing.....	102
Annex D.....	107
Annex E (informative) Capabilities of the In-line Inspections Systems for Plain Dents and Specific Types of Coincident Features.....	108
Annex F (informative) PRCI Dent Fatigue Shape Parameters.....	112
Annex G (informative) Scaling Factors for Unrestrained Dent Shape Factors in Equation (23)....	115
Annex H (informative) Gas Pipeline—Sample Semi-Quantitative Screening Tool for Dents.....	117
Bibliography .....	121

## Figures

1 PDCA Cycle Applied to Dent Management Program.....	11
2 Illustrative Dent Formation Process Stages.....	13
3 Elements of a Dent Management Program.....	16
4 Example of an Acceptable Smoothed Dent Profile, (a) Axial Profile, (b) Transverse Profile..	26
5 Schematic Showing 10 % Axial Length and Area and 75 % Axial and Transverse Length and Area .....	29
6 Spline Interpolation for Cases where No Data Point is Available at a Specified Deformed Pipe Wall Position in the Dent.....	30
7 Dent Definition Parameters .....	31
8 Interaction Zone Definition for Spiral Weld Seams .....	36
9 Dent Fatigue Interaction Zone Definition for Corrosion Features.....	37
10 Criteria for Multiple Dent Interaction.....	39
11 Operational Sample Pressure Time History and Pressure Range Histogram from SCADA System.....	41
12 Range-Mean Operational Pressure Histogram.....	44
13 Spectrum Severity Indicator Description.....	45
14 Local Dent Gouge Geometry Definition.....	57
15 Specimen Initial Radius $r_0$ , and Radius of Neck, $r$ .....	60
16 Specimen Initial Radius $r_0$ , and Radius of Neck, $r$ .....	61
17 Dent Angle Estimation.....	65
18 Dent Manual Field Measurement Setup .....	76
A.1 Hypothetical Dent Axial Profile.....	87
A.2 Hypothetical Dent Transverse Profile .....	87
A.3 Spectrum Severity Indicator Description.....	96
A.4 Sample 1-Year Discharge Pressure Time History.....	97
A.5 Pressure Range Histogram—1-Year Time History .....	98
B.1 Photographs Showing Fatigue Crack Location and Orientation Relative to the Total Dent Deformation Depth and Restraint Condition of a Dent .....	101
H.1 Main Process .....	118
H.2 Process to Estimate the Type of Metal Loss.....	118
H.3 Process to Determine the Severity of a Dent .....	119
H.4 Process to Determine the Response to Dent with Gouge in a Gas Pipeline .....	120

## Tables

1 Relationship Between Program Elements and Parameters.....	23
---	----

2	Single-peak Dent Geometric Parameters Required to Capture Dent Shape at Dent Peak and the Restraint Parameter and the Shape Parameter Calculation .....	27
3	Coefficients for Dent Girth Weld Interaction .....	35
4	Parameters for Dent Longitudinal Seam Weld Interaction .....	35
5	Liquid Pipeline Cyclic Operational Pressure Range Interpolation Model Constants .....	43
6	Dent Fatigue Life Spectrum Severity Criteria.....	50
7	Quadratic Function Constants for Equation (15) for the Pipe Geometries .....	53
8	Constants $a_{ij}$ for Regression Equation (16) .....	54
9	Excavation Pressure Reduction Assessment.....	71
10	Acceptable Dent Repair Methods .....	85
A.1	Characteristic Length and Area of the Example Dent.....	86
A.2	Pipe Characteristics for Example 2.....	88
A.3	Pressure Cycles for Example 3.....	89
A.4	Quadratic Function Constants for Equation (A.6) for Various the Pipe Geometries .....	90
A.5	Calculated Level 0.5 Maximum Stress Magnification Factor for Example 3 .....	91
A.6	Pipe Characteristics for the Level 2 Example Case.....	92
A.7	Dent Geometric Lengths and Areas for Example Dent .....	92
A.8	Hypothetical Pressure Cycle.....	92
A.9	Shape Factor and Shape Parameter Coefficients.....	93
A.10	Damage Calculation .....	94
A.11	Sample Pressure Range Histogram .....	94
A.12	1-Year Damage Accumulation Calculation .....	99
F.1	Shape Parameter Coefficients for Deep Restrained Dents.....	112
F.2	Shape Parameter Coefficients for Shallow Restrained Dents .....	113
F.3	Shape Parameter Coefficients for Unrestrained Dents .....	114
G.1	Scale Factors for the Truncated Mean Pressure (TMP) = 10 .....	116
G.2	Scale Factors for the Truncated Mean Pressure (TMP) = 20 .....	116
G.3	Scale Factors for the Truncated Mean Pressure (TMP) = 30 .....	116
G.4	Scale Factors for the Truncated Mean Pressure (TMP) = 40 .....	116
G.5	Scale Factors for the Truncated Mean Pressure (TMP) = 50 .....	116
G.6	Scale Factors for the Truncated Mean Pressure (TMP) = 60 .....	116
G.7	Scale Factors for the Truncated Mean Pressure (TMP) = 70 .....	116

## Introduction

This Recommended Practice (RP) provides guidance to the pipeline industry for assessing and managing dents present in pipeline systems as a result of mechanical contact by rocks, machinery, or other forces. Emphasis is placed on conditions where dents are either closely aligned or coincident with other threats, and the applicable data screening and assessment methods available to guide decision making on mitigation, remediation, or repair. Additional emphasis is placed on the pipeline operational parameters and the influence of those parameters on dent fatigue.

The RP presents comprehensive guidance for developing a dent assessment and management program including:

- 1) Selecting suitable methods for inspecting and characterizing the condition of the pipeline with respect to dents;
- 2) Establishing data screening processes to evaluate dents relative to extent and degree of deformation and operational severity;
- 3) Provide response criteria for dents based upon the dent shape and profile as determined by in-line inspection;
- 4) Applying engineering assessment methods to evaluate fitness-for-service of dents including reassessment interval;
- 5) Presenting remediation and repair options to address dents;
- 6) Developing preventive and mitigative measures for dents in lieu of, or in addition to, periodic dent integrity assessment, including pressure reductions and pressure cycle management.

This document provides guidance on elements of an engineering critical assessment for dents to determine fitness-for-service.

This RP may be used to supplement requirements included in 49 *CFR* 195, 49 *CFR* 192, CSA Z662, SOR/99-294, and other integrity management codes and standards. The RP provides the process and tools to conduct screening and engineering assessment (e.g., fitness for purpose, engineering critical assessment) for dents. These processes and tools represent criteria for the assessment of dents accounting for the factors that lead to pipeline failures caused by dents.

While this RP is generally applicable to all pipeline systems, it does not:

- include detailed requirements for new construction to prevent dents. For information on this, reference API 1169 and API 1171,
- provide guidance on prevention of dents in-service,
- outline design precautions for preventing and limiting susceptibility to denting,
- provide guidance on the assessment of wrinkles, ripples, long seam misalignment, ovalized bends, or buckles, and
- explicitly identify the differences between onshore and offshore pipeline systems.

This RP is intended for use by pipeline operators to support planning, developing, implementing, and improving a pipeline dent management program. This RP is closely aligned with and augments the API 1160 RP for liquid hazardous pipeline integrity management. It is also equally applicable to natural gas pipeline systems, and is written as a framework for both hazard liquid and gas pipelines.

This RP provides guidance based upon an understanding of the current state of industry knowledge and expertise. Research to improve upon the current state of knowledge continues and it is expected that this RP will be updated to incorporate future enhancements in industry knowledge and expertise.

A prior API publication, API Publication 1156, described the effects of dents on liquid petroleum pipelines but was issued prior to the hazardous liquids pipeline integrity management rule. The RP provides the current industry understanding of dent formation and post-formation behavior and response to environmental and operational factors. This understanding is based on the practical experience of pipeline operators that have been managing dents under the pipeline integrity management regulations included in 49 CFR §192 and §195 and integration of over 20 years of research on dents through work completed by the pipeline industry.

# Assessment and Management of Pipeline Dents

## 1 Scope

This recommended practice (RP) is applicable to any pipeline system used to transport hazardous liquid or natural gas. This RP includes detailed technical discussion on dent formation, strain and fatigue, and failure modes and mechanisms. These details are provided to give pipeline operators the information and knowledge necessary to make informed integrity management decisions regarding the management of dents on their systems. This RP describes preventive and mitigative measures that pipeline operators can apply to manage dents after detection. The in-service response of dents to a range of loading conditions is discussed in detail.

Mechanisms that promote denting are discussed, methods to inspect dents are described, and approaches and tools to estimate dent fitness-for-service (i.e., dent formation induced cracking, failure pressure, and pressure cycling fatigue life) are presented. Selection of the appropriate dent integrity assessment methods and integration of pipeline operating data is also discussed.

This RP is specifically designed to provide the operator with guidelines on industry-proven practices in the integrity management of dents. The guidance is largely targeted to the line pipe along the right-of-way, but some of the processes and approaches can be applied to pipeline facilities, including pipeline stations, terminals, and delivery facilities associated with pipeline systems.

This RP includes a review of currently available in-line inspection (ILI) technologies for detecting and characterizing dents, and provides guidelines for collecting data in the ditch when excavation is performed based on ILI data review and the pipeline and dent sizes exposed. Data integration practices are also addressed. Mitigation and repair techniques and approaches are discussed.

This RP provides general information on the dent formation process and describes approaches to evaluate fitness-for-service of dents regarding their potential to reach a structural limit state. A limit state represents an operator-defined condition where the pipe is no longer fit for purpose. This document provides tools to address three primary limit states: formation strain, failure pressure, and fatigue damage. The document provides screening tools and detailed assessment methods to address each of these limit states. This methodology is consistent with other design and fitness-for-service codes that address both static and fatigue limit states<sup>1</sup>.

In the context of plain dents, the assessment of formation strain is considered to be an indication of the potential for cracking due to dent formation, and has been included as part of ASME B31.8 since 2006.

The assessment of failure pressure is typically not performed for most dents. Plain dents regardless of shape with depths up to 10 % of the pipe diameter, without coincident features such as metal loss, welds, or cracks have been shown in testing to have the same failure pressure as plain line pipe<sup>2</sup>. Consequently, failure pressure is typically addressed for dents with coincident features or in detailed fitness-for-service assessments.

---

<sup>1</sup> ASME *Boiler and Pressure Vessel Code*

<sup>2</sup> Bood, R., Gali, M., Marewski, U., Steiner, M., Zarea, M., "EPRG Methods for Assessing the Tolerance of and Resistance of Pipelines to External Damage (Parts 1 + 2)," European Pipeline Research Group (EPRG)