

Care, Maintenance, and Inspection of Coiled Tubing

API RECOMMENDED PRACTICE 5C8
FIRST EDITION, JANUARY 2017



AMERICAN PETROLEUM INSTITUTE

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Users of this recommended practice should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein.

Copyright reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, NW, Washington, DC 20005.

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this recommended practice are as follows:

- the term “shall” denotes a minimum requirement in order to conform to the recommended practice;
- the term “should” denotes a recommendation or that which is advised but not required in order to conform to the recommended practice;
- the term “may” is used to express permission or a provision that is optional; and
- the term “can” is used to express possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, DC 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 1220 L Street, NW, Washington, DC 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, DC 20005, standards@api.org.

Currently in preview, click buy full version

Contents

	Page
1 Scope	1
2 Normative References	1
3 Terms, Definitions, Acronyms, and Abbreviations	1
3.1 Terms and Definitions	1
3.2 Acronyms and Abbreviations	5
4 General Information	6
4.1 Applications of Coiled Tubing	6
4.2 Responsibility of the Purchaser	7
4.3 Naturally Occurring Radioactive Materials (NORMs)	7
4.4 Properties of Coiled Tubing	8
5 Welding Coiled Tubing	8
5.1 General	8
5.2 Type of Welds Used in CT Products	8
5.3 Welding Processes	9
5.4 Welding Procedure and Qualification	9
5.5 Tube-to-Tube Weld Procedure Specification	11
5.6 Tube to End-fitting WPS	12
5.7 Qualifying Weld Procedure Specifications	13
5.8 Welder and Welding Operator Qualification	14
5.9 Inspection of Coiled Tubular Welds	16
5.10 Field Management of Coiled Tubular Welds	17
5.11 Welds in CT Product for Sour Service	18
5.12 Butt Welds and Fittings	18
6 Corrosion—Effects and Mitigation in Steel Coiled Tubing	19
6.1 General	19
6.2 General Comments	19
6.3 Corrosion and Environmental Cracking (EC) of Coiled Tubing	19
6.4 Effects of Corrosion on Coiled Tubing Serviceability	21
6.5 Corrosive Fluids in Coiled Tubing Service	22
6.6 Environmental Cracking	22
6.7 Specific Guidelines to Reduce the Risk of Coiled Tubing Environmental Cracking Failures in Wet Sour Wells	24
6.8 Corrosion Related to Inserts	25
7 String Protection	25
7.1 Protection for Coiled Tubing	25
7.2 Coiled Tubular Reel Dimension Effects	26
8 Inspection	27
8.1 New Coiled Tubulars	27
8.2 Drilling of Used Coiled Tubing	28
8.3 Lift Ball Standoff for Flash-free Coiled Tubing ($S_{R,O}$)	29
8.4 Pressure Testing of Used Strings	30
8.5 Imperfections in Coiled Tubing	30
8.6 Mechanical Testing Procedures for Used Coiled Tubing	36
9 Nondestructive Inspection and Testing of Used Coiled Tubing	37
9.1 General	37

Contents

	Page
9.2 Test Equipment	38
9.3 Qualification of Nondestructive Inspection Personnel	39
9.4 Light Levels	40
9.5 Visual and Dimensional Inspection	40
9.6 Length	41
9.7 Wall Thickness Measurement Using Ultrasonic Compression Waves	41
9.8 Wall Thickness Measurement Using Electromagnetic and Gamma Ray Methods	43
9.9 Transverse Imperfection Detection by Electromagnetic Methods	44
9.10 Longitudinal Imperfection Detection	45
9.11 Ovality Measurement	46
9.12 Prove-up of Indications	46
9.13 Magnetic Particle Inspection	47
9.14 X-radiography of Tube-to-Tube Welds or Other Sections	48
9.15 Radiographic Procedures	49
9.16 Ultrasonic Inspection of Tube Welds and Other Tube Sections	50
9.17 Ultrasonic Inspection of Seam Weld Area	51
9.18 Ultrasonic Inspection of Skelp-end Welds	51
9.19 Ultrasonic Inspection of Tube-to-Tube and Pipe-to-Pipe Butt Welds	51
9.20 Liquid Penetrant Inspection	52
9.21 Removal of Surface Imperfections	52
10 Assessment of Coiled Tubing	53
10.1 General	53
10.2 Fatigue Life and Fatigue Management of Coiled Tubing	53
10.3 Theoretical Calculated Fatigue Life	54
10.4 Review of String Records	54
10.5 Examples of Effective Repair on Coiled Tubing	54
10.6 Record Keeping	55
11 Coil Tubing Fatigue Testing and Requirement	56
11.1 Objectives of Full-scale Coiled Tubing Fatigue Testing	56
11.2 Recommended Standard Fatigue Testing Machine	56
11.3 Recommended Standard Coiled Tubing Fatigue Testing Procedure	58
11.4 Recommended Testing Matrices	61
11.5 Final Recommendation	61
Annex A (informative) Coiled Tubing Properties	62
Annex B (informative) Collapse of Coiled Tubing	65
Annex C (informative) Reference Tables	74
Annex D (informative) In-service Imperfections Found in Coiled Tubing	81
Annex E (informative) Example Forms	104
Radiography	110
Figures	
1 SSC Zoning (Excluding Tube-to-Tube Welds)	24
2 Drift-ball Standoff in Perfectly Round Coiled Tubing	29
3 Drift-ball in Ovaled Coiled Tubing	30
4 Cycles to Failure for CT-100 (1.25 in. × 0.109 in.)	53

Contents

	Page
5	The Standard Bending Machine Concept 57
6	Profile of the Straight and Curved Mandrels 57
7	Curvature of a 1.75 in. Reference Tube Fully Wrapped onto a Standard Bending Form 57
A.1	Typical Measurement Locations for Coiled Tubing Outer Diameter and Wall Thickness Measurements (OD Readings at AA, BB, CC, and DD) 63
B.1	Calculated Collapse Pressure Ratings for Various D/t_{min} Ratios of As-manufactured Coiled Tubing . . 66
D.1	Acid Corrosion at a Butt Weld 81
D.2	Pitting that Occurred from Acid During Storage (Transversely Oriented Fatigue Cracks at Base of Pitting Inside Tubing at Location of Storage Corrosion) 81
D.3	Mild and Deeper Corrosion Occurring at the Lowest Point on the ID of Stored Tubing 82
D.4	Corrosion Pit on ID with Fatigue Cracks 83
D.5	Carbon Dioxide Pitting in Hang-off Tubing 83
D.6	Microbial Corrosion Pitting Inside Tubing 84
D.7	Example of Sulphide Stress Cracking 84
D.8	Hydrogen-induced Cracking 85
D.9	Stress-oriented Hydrogen-induced Cracking 85
D.10	Fatigue Pinhole 86
D.11	Fatigue Crack Originating with High Pressure Inside the Tubing 86
D.12	Fatigue Break at a Factory Skelp-end Weld 86
D.13	Ductile Tensile Fracture (Showing “Necking” and a 45° Shear Lip) 87
D.14	Tensile Failures with Brittle Fractures 87
D.15	Separation Caused by Tensile Overload Under Flexure 88
D.16	Relatively Shallow Plough Marks on the Outer Surface of Coiled Tubing 88
D.17	Deep Plough Marks Resulting in Fatigue Cracks 89
D.18	Transversely Oriented “Chatter” (“Fish-scale”) Marks That Generally Accompany “Plough” Marks 90
D.19	Longitudinal Gouge 90
D.20	Gouges with Transverse Orientation 91
D.21	Elongated Gouges with Chatter Marks 92
D.22	Gouges with Large Transverse Component 92
D.23	Longitudinal Scratches 93
D.24	Scoring Marks on the Tube Outside Diameter 93
D.25	Wall Thinning on the Curved Diameter (left) and Internal Erosion from Sand (right) 94
D.26	Erosion of the Inside Surface from Sand That Can Result in Serious Wall Loss 94
D.27	Wear with Galling 95
D.28	Impingement Erosion 95
D.29	Burst at Thin Wall Area in Tubing 96
D.30	Burst Failures at Seam Weld (Possibly from a “Cold Weld”) 96
D.31	Example of Dents 97
D.32	Examples of Dimple Dents 98
D.33	Example of Multiple Types of Dents 98
D.34	Laboratory-manufactured Dent with Fatigue Cracks 99
D.35	Elongated Dent 99
D.36	Buckled Tubing 100
D.37	Collapse in Two and Three Directions (One Node Is the Seam Weld) due to Tension and High External Pressure 101
D.38	Gripper Marks 102
D.39	Gripper Block Mark with Fatigue Crack 102
D.40	Injector Ring Damage 103
E.1	Example Form for Visual and Dimensional Inspection Report 104

Contents

	Page
E.2 Example Form for Electromagnetic NDT Report (Part 1)	105
E.3 Example Form for Electromagnetic NDT Inspection Report (Part 2)	106
E.4 Example Form for Preservation of Coiled Tubing Checklist	107
E.5 Example Form for Preservation of Coiled Tubing Equipment Offshore	108
E.6 Example Form for Fatigue Testing Data Collection Sheet	109

Tables

1 Welds with Filler Metal (Tube-to-Tube Weld)	8
2 Recommended Maximum Intervals Between Recalibration/Recertification	38
3 Actual Sample Radius of Curvature on a Standard Bending Form	58
B.1 Collapse Values for API 5ST Coiled Tubing Grades	67
B.2 Coiled Tubing Collapse Pressure Factors for Various Amounts of Utilization	73
C.1 Values for Coiled Tubing Calculations on Wall Thickness and Capabilities	75
C.2 Coiled Tubing Gauge Parameters	78
C.3 Dimensions for Yield Radius, Reel, and Guide Arch	80

Care, Maintenance, and Inspection of Coiled Tubing

1 Scope

This recommended practice covers the care, maintenance, and inspection of used low alloy carbon steel coiled tubing. Commonly manufactured coiled tubing outside diameters range from 25.4 mm (1.000 in.) to 88.9 mm (3.5 in.).

2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Specification 5ST, *Specification for Coiled Tubing*

ASTM A370¹, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

H. Haga, K. Aoki, and T. Sato (1980a), Welding Phenomena and Welding Mechanisms in High Frequency Electric Resistance Welding—1st Report, *Welding Journal* 59(7), pp. 208–212

H. Haga, K. Aoki, and T. Sato (1980b), The Mechanisms of Formation of Metal Defects in High-Frequency Electric Resistance Welds, *Welding Journal* 59(7), pp. 103s–109s

For a list of other documents associated with this standard, see the Bibliography.

3 Terms, Definitions, Acronyms, and Abbreviations

3.1 Terms and Definitions

For the purpose of this document, the following definitions apply.

3.1.1

Bauschinger Effect

A phenomenon that occurs in polycrystalline metals (including steel), that results in a decrease of the yield strength in one direction due to plastic deformation in another direction such as is caused by service loads, coiling, or straightening.

3.1.2

bed wrap

The wraps of coiled tubing that are adjacent to the cylindrical core of the shipping or usage reel.

3.1.3

cold work

Plastic deformation at such temperatures and rates that substantial increases occur in the strength and hardness of the metal.

NOTE Visible structural changes include changes in grain shape and, in some instances, mechanical twinning or banding.

3.1.4

critical weld(s)

Primary connections in coiled tubing where failure would jeopardize the safety of personnel or equipment and/or be detrimental to the integrity of the coiled tubing string or operation.

NOTE Critical welds include, but are not necessarily limited to, tube-to-tube girth joints and high-pressure end-fitting welds for union connections to swivel joints on coiled tubing reels.

¹ ASTM International, 100 Barr Harbor Drive, West Conshohocken, Pennsylvania 19428, www.astm.org.