

Application, Care, and Use of Wire Rope for Oil Field Service

API RECOMMENDED PRACTICE 9B
FOURTEENTH EDITION, OCTOBER 2015

ADDENDUM 1, SEPTEMBER 2020



American
Petroleum
Institute

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Copyright © 2015 American Petroleum Institute. All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the specification.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the Director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001, standards@api.org.

Contents

	Page
1 Scope	1
2 Field Care and use of Wire Rope	1
2.1 Handling on Reel	3
2.2 Handling During Installation	3
2.3 Care of Wire Rope	4
2.4 Seizing	10
2.5 Poured Sockets	11
2.6 Attachment of Clips	12
2.7 Casing-line and Drilling-line Reeving Practice	15
3 Recommended Design Features	20
3.1 Importance of Design	20
3.2 Socket Baskets	20
3.3 Material for Sheave Grooves	20
3.4 Bearings	20
3.5 Diameter of Drums	20
3.6 Drum Grooves	20
3.7 Diameter of Sheaves	20
3.8 Sheave Grooves	22
4 Evaluation of Rotary Drilling Line	25
4.1 Total Service Performed	25
4.2 Round-trip Operations	26
4.3 Drilling Operations	28
4.4 Coring Operations	29
4.5 Setting Casing Operations	29
4.6 Short Trip Operations	30
4.7 Other Operations	30
4.8 Evaluation of Service	30
4.9 Rotary Drilling Line Ton-Mile Calculators	31
4.10 Rotary Drilling Line Service Record Form	31
5 Cutoff Practice for Rotary Drilling Lines	33
5.1 Service Life	33
5.2 Initial Length of Line	33
5.3 Service Goals	33
5.4 Variations in Line Services	33
5.5 Cutoff Length	33
6 Inspection and Retirement	34
6.1 Inspection Requirements	34
6.2 Wire Rope Removal Criteria	36
7 Common Types of Wire Rope Deterioration	37
7.1 General	37
7.2 Wire Wear	38
7.3 Broken Wires	39

Contents

	Page
7.4 Drum Wear	40
7.5 Corrosion	41
7.6 Rope Distortion	42
7.7 Lay Length	44
7.8 Diameter Reductions	45
7.9 Heat Damage	46
7.10 Extraordinary Wear/Damage	47
8 Field Troubles and Their Causes	47
Bibliography	49
Figures	
1 Efficiency of Wire Rope Reeving for Multiple Sheave Blocks Cases A, B, and C (Fast Line and Efficiency Factors for Derricks, Booms, etc.)	6
2 Efficiency of Wire Rope Reeving for Multiple Sheave Blocks Cases D and E (Fast Line and Efficiency Factors for Derricks, Booms, etc.)	7
3 Efficiencies of Wire Ropes Bent Around Stationary Sheaves (Static Stresses Only)	9
4 Fatigue Fractures in Outer Wires Caused by the Formation of Martensite	9
5 Putting a Seizing on a Wire Rope	11
6 Correct Method of Attaching Clips to Wire Rope	14
7 Incorrect Methods of Attaching Clips to Wire Rope	14
8 Typical Reeving Diagram for a 14-Line String-up with 8-Sheave Crown Block and 7-Sheave Traveling Block: Left Hand Reeving (See Arrangement No. 1 in Table 5)	16
9 Fleet Angle from Drum to Sheave and Sheave to Drum	19
10 Relative Service for Various D_T/d Ratios for Sheaves	23
11 New Sheave Grooves	25
12 Use of Sheave Gage	26
13 Facsimile of Rotary Drilling Line Service Record Form	32
14 Relationship between Rotary Line Initial Length and Service Life	34
15 Example of Abrasion of the Outer Wires	38
16 Example of Peening of the Outer Wires	38
17 Example of Single Broken Wire on the Crown of a Wire Rope	39
18 Example of Valley Wire Breaks that are Displaced from their Unbroken Position	39
19 Example of External Damage Resulting in Broken Wires	40
20 Example of Pattern of Drum Crushing	41
21 Example of Crushing on a Wire Rope	41
22 Example of Surface Corrosion on a Wire Rope	42
23 Example of Pitting Corrosion on a Wire Rope	42
24 Example of Fretting Corrosion in a Wire Rope	42
25 Example of a Kink in a Wire Rope	43
26 Example of a Permanent Bend in a Wire Rope	43
27 Example of Waviness in a Wire Rope	44
28 Diagram Showing the Lay Length of a 6-Strand Wire Rope	44

Contents

	Page
29 Diagram Showing Correct and Incorrect Ways to Measure Wire Rope Diameter	45
30 Example of Loss of Core Support Resulting in Localized Diameter Reduction	46
31 Example of Electrical Arc Causing Severe Wire Rope Damage.....	47
Tables	
1 Typical Sizes and Construction of Wire Rope for Oilfield Service	2
2 Minimum Design Factors	4
3 Attachment of Clips.....	12
4 Attachment of Double Saddle Clips	13
5 Typical Reeving Arrangements for 14, 12, 10, 9, and 6-Line String-ups Using 8-Sheave Crown Blocks with 7-Sheave Traveling Blocks, 7-Sheave Crown Blocks with 6-Sheave Traveling Blocks, and 6-Sheave Crown Blocks with 5-Sheave Traveling Blocks.....	17
6 Sheave-Diameter Factors	21
7 Relative Bending Life Factors for Various Construction	22
8 Groove Radii for Sheaves.....	23
9 Ton-Mile Goal per Foot of Rope.....	35
10 Field Troubles and Their Causes.....	47

Application, Care, and Use of Wire Rope for Oil Field Service

1 Scope

This recommended practice (RP) covers typical wire rope applications for the oil and gas industry.

Typical practices in the application of wire rope to oil field service are indicated in Table 1, which shows the sizes and constructions commonly used. Because of the variety of equipment designs, the selection of constructions other than those shown is justifiable.

In oilfield service, wire rope is often referred to as wire line or cable. For the purpose of clarity, these various expressions are incorporated in this recommended practice.

2 Field Care and use of Wire Rope

2.1 Handling on Reel

2.1.1 Use of Binding or Lifting Chain

When handling wire rope on a reel with a binding or lifting chain, wooden blocks should always be used between the rope and the chain to prevent damage to the wire or distortion of the strands in the rope.

2.1.2 Use of Bars

Bars for moving the reel should be used against the reel flange, and not against the rope.

2.1.3 Sharp Objects

The reel should not be rolled over or dropped on any hard, sharp object in such a manner that the rope will be damaged.

2.1.4 Dropping

The reel should not be dropped. This may cause damage to the rope as well as break the reel.

2.1.5 Mud, Dirt, or Cinders

Rolling the reel in or allowing it to stand in any medium harmful to steel such as mud, dirt, or cinders should be avoided. Planking or cribbing will be of assistance in handling the reel as well as in protecting the rope against damage.

2.1.6 Lifting the Reel

The preferred method for lifting a reel with slings is to use a spreader bar that is of sufficient length to keep the sling legs from contacting the reel. This will prevent the flanges of the reel from being bent, distorted, broken, or damaged in any way by the slings.

2.1.7 Shaft through Arbor Holes

When lifting reels of wire rope, care must be taken that the shaft through the reel is of adequate length for the task, plus its wall thickness and diameter are of sufficient strength and size respectively to safely support the weight without damaging the center holes of the two flanges of the reel.