

Specification for Corrosion-resistant Alloy Seamless Tubes for Use as Casing, Tubing, and Coupling Stock

ANSI/API SPECIFICATION 5CRA
FIRST EDITION, FEBRUARY 2010

EFFECTIVE DATE: AUGUST 1, 2010

ERRATA , AUGUST 2011

REAFFIRMED, JANUARY 2021

ISO 13680:2010 (Identical), Petroleum and natural gas industries—Corrosion-resistant alloy seamless tubes for use as casing, tubing, and coupling stock—Technical delivery conditions



American
Petroleum
Institute



Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

Classified areas may vary depending on the location, conditions, equipment, and substances involved in any given situation. Users of this specification should consult with the appropriate authorities having jurisdiction.

Users of this specification should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Copyright © 2010 American Petroleum Institute. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

API Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Shall: As used in a standard, "shall" denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, "should" denotes a recommendation or that which is advised but not required in order to conform to the specification.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001, standards@api.org.

Contents

Page

API Foreword	ii
Foreword	
Introduction.....	1
1 Scope.....	1
2 Conformance.....	2
2.1 Dual normative references	2
2.2 Units of measurement.....	2
3 Normative references.....	2
4 Terms, abbreviated terms, symbols and definitions	4
4.1 Terms and definitions	4
4.2 Symbols.....	6
4.3 Abbreviated terms	7
5 Information to be supplied by the purchaser	8
6 Manufacturing process	9
6.1 Manufacturing of corrosion-resistant alloys	9
6.2 Product manufacturing process	9
6.3 Pipe end sizing	9
6.4 Straightening.....	9
6.5 Processes requiring validation	10
6.6 Traceability.....	10
7 Material requirements	10
7.1 Chemical composition	10
7.2 Tensile properties.....	10
7.3 Hardness properties.....	10
7.4 Charpy V-notch test properties – General requirements.....	11
7.5 Charpy V-notch — Absorbed energy requirements for coupling stock – All grades.....	12
7.6 Charpy V-notch — Absorbed energy requirements for pipe — All grades	12
7.7 Flattening requirements	13
7.8 Corrosion properties	14
7.9 Microstructure properties.....	14
7.10 Surface condition	14
7.11 Defects.....	14
7.12 Hydrostatic test	15
8 Dimensions, masses and tolerances	15
8.1 Outside diameter, wall thickness and mass	15
8.2 Length.....	15
8.3 Tolerances.....	16
8.4 Product ends.....	16
9 Inspection and testing	16
9.1 Test equipment.....	16
9.2 Type and frequency of tests.....	16
9.3 Testing of chemical composition.....	17
9.4 Testing of mechanical characteristics	17
9.5 Tensile test.....	18
9.6 Hardness test.....	18
9.7 Impact or flattening test.....	19
9.8 Microstructural examination	21

9.9	Dimensional testing.....	22
9.10	Drift test	22
9.11	Length	23
9.12	Straightness	23
9.13	Mass determination	23
9.14	Hydrostatic test.....	23
9.15	Visual inspection	24
9.16	Non-destructive examination	24
10	Surface treatment	29
10.1	Group 1	29
10.2	Groups 2, 3 and 4.....	29
11	Marking	30
11.1	General.....	30
11.2	Marking on the product.....	30
11.3	Date of manufacture	31
12	Surface protection — Group 1.....	31
13	Documents	32
13.1	Electronic media	32
13.2	Retention of records.....	32
14	Handling, packaging and storage	33
14.1	General.....	33
14.2	Handling.....	33
14.3	Packaging.....	33
14.4	Storage.....	33
Annex A (normative) Tables in SI units		34
Annex B (normative) Figures in SI (USC) Units		54
Annex C (normative) Tables in USC units		59
Annex D (normative) Purchaser inspection		79
Annex E (normative) Cleanliness requirements		80
Annex F (informative) Marking instructions for API licenses — API monogram.....		82
Annex G (normative) Product specification level 1 (PSL-2)		85
Bibliography		87

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13680 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Casing, tubing and drill pipe*.

This third edition cancels and replaces the second edition (ISO 13680:2008), which has been technically revised, after the six-month overlap period. (It also incorporates the Technical corrigenda ISO 13680:2000/Cor.1:2002 and ISO 13680:2000/Cor.2:2004, which were covered in the second edition.)

It is the intent of ISO/TC 67 that the first and second editions of ISO 13680 both be applicable, at the option of the purchaser, for a period of six months from the first day of the calendar quarter immediately following the date of publication of this second edition, after which period the first edition will no longer be applicable.

Introduction

Users of this International Standard should be aware that further or differing requirements may be needed for individual applications. This International Standard is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this International Standard and provide details.

This International Standard includes requirements of various nature. These are identified by the use of certain verbal forms:

SHALL is used to indicate that a provision is MANDATORY;

SHOULD is used to indicate that a provision is not mandatory, but RECOMMENDED as good practice;

MAY is used to indicate that a provision is OPTIONAL.

Petroleum and natural gas industries — Corrosion-resistant alloy seamless tubes for use as casing, tubing and coupling stock — Technical delivery conditions

WARNING — It is the purchaser's responsibility to specify the product specification level (PSL), corrosion-resistant alloy (CRA) group, category, grade, delivery conditions and any other requirements in addition to those specified herewith to ensure that the product is adequate for the intended service environment. ISO 15156 (all parts) or NACE MR0175/ISO 15156 should be considered when making specific requirements for H₂S containing environment (see Annex G).

1 Scope

This International Standard specifies the technical delivery conditions for corrosion-resistant alloy seamless tubulars for casing, tubing and coupling stock for two product specification levels:

- PSL-1, which is the basis of this International Standard;
- PSL-2, which provides additional requirements for a product that is intended to be both corrosion resistant and cracking resistant for the environments and qualification method specified in ISO 15156-3 and Annex G of this International Standard.

At the option of the manufacturer, PSL-2 product can be provided in lieu of PSL-1.

NOTE 1 The corrosion-resistant alloys included in this International Standard are special alloys in accordance with ISO 4948-1 and ISO 4948-2.

This International Standard is applicable to the following four groups of product:

- a) group 1, which is comprised of stainless alloys with a martensitic or martensitic/ferritic structure;
- b) group 2, which is comprised of stainless alloys with a ferritic-austenitic structure, such as duplex and superduplex stainless alloys;
- c) group 3, which is comprised of stainless alloys with an austenitic structure (iron base);
- d) group 4, which is comprised of nickel-based alloys with an austenitic structure (nickel base).

This International Standard contains no provisions relating to the connection of individual lengths of pipe.

NOTE 2 The connection or joining method can influence the corrosion performance of the materials specified in this International Standard.

NOTE 3 It is necessary to recognize that not all PSL-1 categories and grades can be made cracking resistant per ISO 15156-3 and are, therefore, not included in PSL-2.