

Specification for Subsea Pipeline Valves

API SPECIFICATION 6DSS
THIRD EDITION, AUGUST 2017

API MONOGRAM PROGRAM EFFECTIVE DATE: AUGUST 1, 2018

ERRATA 1, MAY 2018
ERRATA 2, JULY 2018

ADDENDUM 1, APRIL 2019
(API MONOGRAM PROGRAM EFFECTIVE DATE: JULY 1, 2019)



AMERICAN PETROLEUM INSTITUTE

Currently in preview, click buy full version

Date of Issue: April 2019

Affected Publication: API Specification 6DSS, *Specification for Subsea Pipeline Valves*, Third Edition, August 2017

Addendum 1

Section 3.1, Terms and Definitions: The following term and definition shall be added to the section:

3.1.61

test coupon

TC

Sample of material representing the properties after heat treatment, inclusive of simulated post-weld heat treatment when required, of the material comprising the production parts it qualifies.

Section 5.6.6: The final bullet shall be changed to the following:

- self-locking capability provided by the operator or the valve.

Section 6.2: The final two paragraphs, including the NOTES, shall be changed to the following:

If the results of the tensile test(s) do not satisfy the applicable requirements, two additional tests from the same TC with no additional heat treatment shall be performed in an effort to qualify the material. The results of both additional tensile tests shall exhibit the minimum applicable requirements.

NOTE 2 Depending on the hardenability of a given material, the TC results might not always correspond to the properties of the actual parts at all locations throughout their cross-section.

NOTE 3 API 6HT provides guidance and good practice for heat treatment of parts with large cross-section, with the goal of achieving the required mechanical properties at the depth below the surface established by the manufacturer.

Section 6.6, 8th paragraph: The first two bullets shall be changed to the following:

- Material taken from the TC after the final heat treatment cycle shall be corrosion tested in accordance with ASTM G48 (latest revision).
- Method A. If the TC is a solid block, one ASTM G48 test specimen shall be taken from the center of the block. If the TC has a hole, two ASTM G48 test specimens shall be taken. One shall be taken adjacent to the inside surface and one from the center of the thickest cross-section. The specimen surface shall be parallel to the internal surface (for the TCs with a hole). Sides of the test specimen shall be ground to a 120-grit finish (or better) with the edges rounded.

Section 6.9: The 2nd paragraph shall be changed to the following:

The manufacturer shall ensure electrical continuity between all parts, including bolting.

Section 6.9: The NOTE shall be changed to the following:

NOTE Design stress levels per DNVGL ST F101 and DNV RP F112 are available for guidance.

Section 6.13.4: The section shall be changed to the following:

The controlling and recording instruments used for the heat treatment processes shall be accurate to $\pm 1\%$ of full-scale range.

Section 6.13.5: The 2nd paragraph shall be changed to the following:

Equipment used to calibrate the production equipment shall be accurate to $\pm 0.25\%$ of full-scale range.

Section 10.4.1: The section shall be changed to the following:

The measured torque or thrust results shall be recorded and shall not exceed the manufacturer's documented calculated breakaway torque/thrust. The valve shall be operated for each appropriate condition defined in 10.5.4.

Section 10.4.2: The 2nd paragraph shall be changed to the following:

Valves requiring input forces exceeding that specified in 5.20.1, or that fail to seal after operation, shall be rejected.

Section 10.4.3: The 2nd paragraph shall be changed to the following:

The thrust or torque shall be measured. Valves requiring thrust or torque exceeding the design torque specified in 5.20.1, or that fail to seal after operation, shall be rejected.

Section 10.6.1: The section shall be changed to the following:

If the valve has a cavity relief system other than self-relieving seats, testing shall be performed in accordance with a documented procedure by agreement.

Each valve shall be tested, except valves that cannot trap pressure in the cavity.

For valves where cavity overpressure relief is provided via one or more self-relieving seats, this shall be demonstrated by one of the cavity relief tests in 10.6.2.

For trunnion-mounted ball valves with self-relieving seats, selection of one of the two procedures in 10.6.2 shall be by agreement.

Section 10.6.2.1: Item c) and item e) shall be changed to the following:

- c) Close both branch vents.
- e) Failure to relieve at a differential pressure less than 33 % the valve pressure rating shall be cause for rejection.

Section 10.6.2.2: The section shall be changed to the following:

The procedure for cavity-relief testing of trunnion-mounted ball valves with one or more self-relieving seats shall be conducted using the following.

- a) Fill the valve in the half-open position with water.
- b) Close the valve.
- c) Pressurize both sides of the valve and the valve cavity simultaneously, up to 1.1 times rated working pressure (RWP).
- d) Isolate both sides of the valve and the valve cavity from pressure source.
- e) Slowly decrease pressure on one side while monitoring the valve cavity pressure. Record pressure on that side required to activate SPE seat seal relief (point at which valve cavity pressure decreases).
- f) Repeat Steps a) to d) for the other side, if it has a self-relieving seat.
- g) Failure to relieve at a differential pressure less than 33 % the valve pressure rating shall be cause for rejection.

Pressure-temperature ratings for class-rated valves shall be in accordance with the applicable rating table for the appropriate material group in ASME B16.34.

Section 10.6.3: The section shall be changed to the following:

10.6.3 Through-conduit Slab Gate Valves with Self-relieving Seats

Slab gate valves one or more self-relieving seats that are either upstream and/or downstream shall internally relieve the excess cavity pressure.

The procedure for cavity-relief testing of through-conduit slab gate valves with internal-relieving seats shall be as follows.

- a) Fill the valve in the half-open position with water and purge any trapped air.
- b) Close the valve (see Note 1).
- c) Close both branch vents.
- d) Apply design pressure (or other pressure agreed with the purchaser) via one of the valve branches with the opposite branch vented to atmosphere.

- e) Apply pressure to the valve cavity until the pressure in the pressurized branch starts to rise and the seat relieves the cavity pressure into the valve end; record this relief pressure.
- f) Failure to relieve at a differential pressure less than 33 % the valve pressure rating over the valve pressure rating shall be cause for rejection.

NOTE 1 For through-conduit gate valves with rising stem, water volume may need to be adjusted during the closing stroke.

NOTE 2 For downstream sealing through-conduit gate valves, a center cavity pressure port will be required.

Section 10.15: The 3rd paragraph shall be changed to the following:

The measured resistance shall not exceed 0.1 Ω . A calibrated meter in accordance with 8.2.1 shall be used to measure the resistance.

Section 11. The last paragraph shall be changed to the following:

No corrosion protection (rust inhibitor) shall be applied to corrosion-resistant surfaces, unless by agreement.

Annex Section F.9.1: The section shall be changed to the following:

The temperature shall be measured at the defined location by one of the methods below:

Method 1:

- On the outside surface of the valve in the seat area, and
- On the bonnet adjacent to the stem seal.
- Thermal analysis shall be performed to establish the outside surface temperature that corresponds to the required temperature for the internal parts. Hold periods shall start after the external temperature as defined by the analysis has been achieved.

Method 2:

- If the body wall thickness is greater than 0.5 in. (13 mm), drill a hole from the outside surface of the body in the seat area within 0.5 in. (13 mm) of the surface wetted by the retained fluid.
- If the bonnet wall thickness is greater than 0.5 in. (13 mm), drill a hole from the outside surface of the bonnet to within 0.5 in. (13 mm) adjacent to the stem seal.

Temperature shall be considered stabilized when the rate of change is less than 0.5 °C/min (1 °F/min). The temperature shall remain at or beyond the extreme during the hold period, but should not go beyond the upper and lower temperatures by more than 11 °C (20 °F).

Bibliography: The following entries shall be added:

- [7] API Recommended Practice 6HT, *Heat Treatment and Testing of Carbon and Low Alloy Steel Large Cross Section and Critical Section Components*

[10] DNVGL-ST-F101, *Submarine Pipeline Systems – rules and standards*

Bibliography: The following entry shall replace the entry for DNV-RP-F112:

[11] DNVGL-RP-F112¹¹, *Duplex stainless steel – design against hydrogen induced stress cracking*

Currently in preview, click buy full version

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Copyright © 2017 American Petroleum Institute. All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

The verbal forms used to express the provisions in this document are as follows.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the standard.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the standard.

May: As used in a standard, “may” denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, “can” denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

For API Monogram Program licensees and APIQR Program registrants, this standard shall become effective on the program date printed on the cover but may be used voluntarily from the date of publication.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-2000. A catalog of API publications and materials is published annually by API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001, standards@api.org.

Contents

	Page
1 Scope	1
2 Normative References	1
3 Terms, Definitions, Acronyms, Abbreviations, Symbols, and Units	3
3.1 Terms and Definitions	3
3.2 Acronyms, Abbreviations, Symbols, and Units	10
4 Valve Types and Configurations	12
4.1 Valve Types	12
4.2 Valve Configurations	13
5 Design	15
5.1 Design Standards and Calculations	15
5.2 Pressure and Temperature Rating	15
5.3 Sizes	16
5.4 Face-to-face and End-to-end Dimensions	16
5.5 Valve Operation	16
5.6 Operator Information	17
5.7 Pigging	19
5.8 Valve Ends	19
5.9 Valve Cavity Pressure Relief	21
5.10 Drains, Vents, Body Test Ports, Seal Test Port, and Body Connections	21
5.11 Stem/Seat and Cavity Injection Points	22
5.12 Drain, Sealant, and Vent Valves	22
5.13 Hand-wheels and Wrenches—Levers	22
5.14 Position of the Obturator	22
5.15 Position Indicators	23
5.16 Travel Stops	23
5.17 Valve Operator Interface Requirements	23
5.18 ROT System	24
5.19 Lifting Points and Supports	24
5.20 Drive Trains	24
5.21 Stem Retention	26
5.22 Body and Stem Seals	26
5.23 Valve Stem Seal Integrity Verification	26
5.24 Overpressure Protection	26
5.25 Pressure Cap	26
5.26 Stem/Shaft Protector	26
5.27 Hydraulic Lock	26
5.28 Corrosion/Erosion	26
5.29 Design Validation	27
5.30 Hydraulic Performance	27
6 Materials	27
6.1 Material Specification	27
6.2 Tensile Test Requirements	28
6.3 Service Compatibility	28
6.4 Cast Material	28
6.5 Forged Material	29
6.6 Composition Limits	29

Contents

	Page
6.7 Impact Test Requirements	30
6.8 Bolting	31
6.9 Cathodic Protection	32
6.10 Sour Service	32
6.11 Hydrogen-induced Cracking	32
6.12 Drain Connections	32
6.13 Heat Treating Equipment Qualification	32
7 Welding	34
7.1 Welding Consumables	34
7.2 Welding Procedure and Welder/Welding Operator Qualifications	34
7.3 Impact Testing	35
7.4 Hardness Testing	36
7.5 Repairs	36
8 Quality Control	37
8.1 Quality Control Procedures	37
8.2 NDE Requirements	37
8.3 Measuring and Test Equipment	37
8.4 Qualification of Personnel	38
8.5 Welding Inspectors	39
8.6 NDE of Repairs	39
8.7 Production Material Hardness Testing on Critical Parts	39
8.8 Marking, Age Control, and Storage for Nonmetallic Seals	40
9 Valve Assembly	41
10 Factory Acceptance Testing (FAT)	41
10.1 General	41
10.2 Stem Backseat Test	42
10.3 Hydrostatic Shell Test	43
10.4 Operational/Functional Test	43
10.5 Hydrostatic Seat Test	44
10.6 Cavity Relief Test	46
10.7 Draining	48
10.8 Low-pressure Gas Seat Test	48
10.9 High-pressure Gas Shell Test	48
10.10 High-pressure Stem Seal Integrity Testing	49
10.11 High-pressure Gas Seat Test	49
10.12 Check Valves	49
10.13 Installation of Body Connections After Testing	50
10.14 Testing of Body Connections	50
10.15 CP Continuity Test	50
10.16 Post-testing Corrosion Protection	50
11 Coating/Painting	50
12 Marking	51
13 Preparation for Shipment	53
14 Documentation	54
14.1 Minimum Documentation and Retention	54

Contents

	Page
14.2 Documentation Provided with the Valve	54
14.3 Supplementary Documentation	55
15 Facility Requirements	55
15.1 Minimum Facility Requirements for the Assembler/manufacturer Category of Manufacturing	55
15.2 Conformance with Specification	56
15.3 Processes Requiring Validation	56
16 Purchasing Guidelines	56
Annex A (informative) Use of API Monogram by Licensees	57
Annex B (informative) Valve Configurations	60
Annex C (normative) Valve End-to-End and Face-to-Face Dimensions	71
Annex D (informative) Actuator—Gearbox Requirements	88
Annex E (informative) Guidance for Travel Stops by Valve Type	89
Annex F (informative) Design Validation	90
Annex G (informative) Hyperbaric Validation Testing	102
Annex H (normative) Pressure Boundary Bolting	106
Annex I (informative) Pressure-containing Castings and Forgings	107
Annex J (normative) Qualification of Heat Treating Equipment	108
Annex K (normative) Requirements for Nondestructive Examination	110
Annex L (informative) Supplementary Test Requirements	115
Annex M (informative) Isolation Valve Features	117
Annex N (normative) External Coating for End Connections	120
Annex O (informative) Marking Example	122
Annex P (informative) Supplementary Documentation Requirements	124
Annex Q (informative) Purchasing Guidelines	125
Bibliography	128
Figures	
1 Typical Flange Dimensions	20
2 Bolt Hole Misalignment	21
3 Charpy V-notch WM Specimen Location	35
4 Charpy V-notch HAZ Specimen Location	35
5 Typical Identification Plate for a Valve with One Seat Unidirectional and One Seat Bidirectional	53
B.1 Expanding Gate/Rising Stem Gate Valve	61
B.2 Slab Gate/Through-conduit Rising Stem Gate Valve	62
B.3 Plug Valve	63
B.4 Top Entry Trunnion-mounted Ball Valve	64
B.5 Two-piece Bolted Ball Valve	65
B.6 Two-piece Welded Ball Valve	66
B.7 Full-opening Cast Swing Check Valve	67

Contents

Page

B.8	Full-opening Forged Swing Check Valve	68
B.9	Axial-flow Check Valve	69
B.10	Axial On-off Valve	70
F.1	Test Procedure for Pressure Temperature Cycle	100
J.1	Thermocouple Location—Rectangular Furnace (Working Zone)	109
J.2	Thermocouple Location—Cylindrical Furnace (Working Zone)	109
M.1	Block and Bleed—Type A	118
M.2	Block and Bleed—Type B	118
M.3	Double Block and Bleed—Type A	118
M.4	Double Block and Bleed—Type B	119
M.5	Double Isolation and Bleed—Type A	119
M.6	Double Isolation and Bleed—Type B	119
N.1	Raised Face	120
N.2	Ring Type Joint or Raised Face Ring Type Joint	120
N.3	Weld Face	121
N.4	Pipe Pup Weld Ends	121

Tables

1	Minimum Bore for Full-opening Valves	14
2	Minimum V-notch Impact Requirements for Carbon and Low-alloy Steels (Full-size Specimen)	31
3	Minimum V-notch Impact Requirements for Duplex and Super Duplex Stainless Steel (Full-size Specimen)	31
4	Chemical Composition of Nickel-based Alloy UNS N06625	34
5	Minimum Duration of Stem Backseat Tests	42
6	Valve Marking	52
7	Minimum Facility Requirements	55
C.1	Gate Valves—Face-to-face (<i>A</i>) and End-to-end (<i>B</i> and <i>C</i>) Dimensions	72
C.2	Plug Valves—Face-to-face (<i>A</i>) and End-to-end (<i>B</i> and <i>C</i>) Dimensions	75
C.3	Ball Valves—Face-to-face (<i>A</i>) and End-to-end (<i>B</i> and <i>C</i>) Dimensions	80
C.4	Check Valves—Face-to-face (<i>A</i>) and End-to-end (<i>B</i> and <i>C</i>) Dimensions	84
C.5	Axial On-off Valves—Face-to-face (<i>A</i>) and End-to-end (<i>B</i> and <i>C</i>) Dimensions	87
E.1	Valve Travel Stops	89
F.1	Design Validation for Valves	96
F.2	Room Temperature Gas Leakage Acceptance Criteria	97
G.1	Hyperbaric Qualification Test	102
K.1	NDE Requirements	111
K.2	Extent, Method, and Acceptance Criteria of NDE/item Examination Code	112
M.1	Isolation Valve Types	117
Q.1	Valve Datasheet	126

Introduction

This specification is the result of updating the requirements from API Specification 6DSS, Second Edition, including Errata¹.

The revision of API 6DSS, Third Edition, is developed based on input from the API 6DSS Task Group technical experts. The technical revisions have been made in order to accommodate the needs of industry and to move this specification to a higher level of service to the petroleum and natural gas industry.

In this specification, data are expressed in both U.S. customary (USC) and metric (SI) units.

Except as otherwise required by this specification, to determine conformance with the specified requirements, observed or calculated values are to be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding method of ASTM E29 or ISO 80000-1, Annex B, Rule A.

This specification is not intended to inhibit a manufacturer from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology.

Specification for Subsea Pipeline Valves

1 Scope

This specification defines the requirements for the design, manufacturing, quality control, assembly, testing, and documentation of ball, check, gate, plug, and axial on–off valves for application in subsea pipeline systems for the petroleum and natural gas industries.

This specification is not applicable to valves for pressure ratings exceeding Class 2500.

If product is supplied bearing the API Monogram and manufactured at a facility licensed by API, the requirements of Annex A apply.

2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies.

For undated references, the latest edition of the referenced document (including any amendments) applies, except that new editions may be used on issue and shall become mandatory upon the effective date specified by the publisher or 6 months from the date of the revision (where no effective date is specified).

API Technical Report 17TR11, *Pressure Effects on Subsea Hardware During Flowline Pressure Testing in Deep Water*

API Specification 20E, *Alloy and Carbon Steel Bolting for Use in the Petroleum and Natural Gas Industries*

API Specification 20F, *Corrosion Resistant Bolting for Use in the Petroleum and Natural Gas Industries*

ASME B16.5¹, *Pipe Flanges and Flanged Fittings: NPS 1/2 Through 24 Metric/Inch Standard*

ASME B16.10, *Face-to-Face and End-to-End Dimensions of Valves*

ASME B16.25, *Buttwelding Ends*

ASME B16.34, *Valves—Flanged, Threaded, and Welding End*

ASME B16.47, *Large Diameter Steel Flanges: NPS 26 Through NPS 60 Metric/Inch Standard*

ASME B31.4, *Pipeline Transportation Systems for Liquids and Slurries*

ASME B31.8, *Gas Transmission and Distribution Piping Systems*

ASME *Boiler and Pressure Vessel Code (BPVC), Section II: Materials, Part D: Properties*

ASME *Boiler and Pressure Vessel Code (BPVC), Section V: Nondestructive Examination*

ASME *Boiler and Pressure Vessel Code (BPVC), Section VIII: Pressure Vessels; Division 1: Rules for Construction of Pressure Vessels*

ASME *Boiler and Pressure Vessel Code (BPVC), Section VIII: Pressure Vessels; Division 2: Alternative Rules*

ASME *Boiler and Pressure Vessel Code (BPVC), Section IX: Welding and Brazing Qualifications*

¹ ASME International, 2 Park Avenue, New York, New York 10016-5990, www.asme.org.