

# Age-hardened Nickel-based Alloys for Oil and Gas Drilling and Production Equipment

API STANDARD 6ACRA  
FIRST EDITION, AUGUST 2015

ADDENDUM 3, FEBRUARY 2019  
ADDENDUM 2, SEPTEMBER 2018  
ADDENDUM 1, SEPTEMBER 2017  
ERRATA 2, FEBRUARY 2018  
ERRATA 1, OCTOBER 2015



AMERICAN PETROLEUM INSTITUTE

## Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Classified areas may vary depending on the location, conditions, equipment, and substances involved in any given situation. Users of this Standard should consult with the appropriate authorities having jurisdiction.

Users of this Standard should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, NW, Washington, DC 20005.

## Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in this publication be construed as insuring anyone against liability for infringement of letters patent.

Shall: As used in a standard, "shall" denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, "should" denotes a recommendation or that which is advised but not required in order to conform to the specification.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, DC 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 1220 L Street, NW, Washington, DC 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).

Date of Issue: February 2019

Affected Publication: API Standard 6ACRA, *Age-hardened Nickel-based Alloys for Oil and Gas Drilling and Production Equipment*, First Edition, August 2015

### Addendum 3

Section 1.1 shall be replaced with the following:

#### 1.1 Purpose

This document provides requirements for age-hardened nickel-base alloys that are intended to supplement the existing requirements of API 6A. For downhole applications, refer to API 5CRA.

These additional requirements include detailed process control requirements and detailed testing requirements. The purpose of these additional requirements is to ensure that the age-hardened nickel-base alloys used in the manufacture of API 6A pressure-containing and pressure-controlling components are not embrittled by the presence of an excessive level of deleterious phases and meet the minimum metallurgical quality requirements.

NOTE Failures attributed to hydrogen-induced stress cracking (HISC) have been reported in production equipment and early in the life of subsea equipment made from age-hardened nickel-base alloys. Some age-hardened nickel-base alloys that meet the requirements of NACE MR0175 and API 6ACRA may be susceptible to HISC. Sources of hydrogen charging include but are not limited to galvanic coupling to a more active material, direct exposure to seawater with cathodic protection (CP), and decomposition of brines. The industry is evaluating alternate test methods and/or acceptance criteria to identify material with susceptibility to HISC.

In the table of contents, the entries for figures A.10 through A.17 shall be amended to the following:

<b>A.10 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725</b> .....	<b>28</b>
<b>A.11 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Isolated Grain Boundary Precipitation</b> .....	<b>29</b>
<b>A.12 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>30</b>
<b>A.13 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>31</b>
<b>A.14 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Full Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>32</b>
<b>A.15 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Acicular Grain Boundary Precipitates</b> .....	<b>33</b>
<b>A.16 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Due To Acicular Precipitates</b> ...	<b>34</b>
<b>A.17 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Grain Boundary Precipitates</b> .....	<b>35</b>

Table 1: Replace Table 1 with the following:

Table 1—Chemical Composition <sup>c,d</sup>

Element	UNS Number							
	N07716	N07718	N07725	N09925	N09935	N09945	N09946	N09955
Ni	59.0 to 63.0	50.0 to 55.0	55.0 to 59.0	42.0 to 46.0	35.0 to 38.0	46.5 to 48.0	52.0 to 55.0	55.0 to 60.0
Cr	19.0 to 22.0	17.0 to 21.0	19.0 to 22.5	19.5 to 22.5	19.5 to 22.0	19.5 to 23.0	19.5 to 22.5	20.0 to 24.0
Fe <sup>a</sup>	Balance	Balance	Balance	22 min	Balance	Balance	Balance	Balance
Nb	2.75 to 4.00	—	2.75 to 4.00	0.08 to 0.50	0.20 to 1.00	2.80 to 3.50	3.80 to 4.50	4.0 to 5.5
Cb(Nb) + Ta	—	4.87 to 5.20	—	—	—	—	—	—
Mo	7.00 to 9.50	2.80 to 3.30	7.00 to 9.50	2.50 to 3.50	3.00 to 5.00	3.00 to 4.00	3.00 to 4.00	5.5 to 7
Ti	1.00 to 1.60	0.80 to 1.15	1.00 to 1.70	1.90 to 2.40	1.80 to 2.50	0.50 to 2.50	0.50 to 2.50	0.50 to 1.00
Al	0.35 max	0.40 to 0.60	0.35 max	0.10 to 0.50	0.50 max	0.01 to 0.70	0.01 to 0.70	0.25 to 0.80
C	0.030 max	0.045 max	0.030 max	0.025 max	0.030 max	0.005 to 0.040	0.005 to 0.030	0.030 max
Co	—	1.00 max	—	—	1.00 max	—	—	1.00 max
Mn	0.20 max	0.35 max	0.35 max	1.00 max	1.00 max	1.00 max	1.00 max	0.50 max
Si	0.20 max	0.35 max	0.20 max	0.35 max	0.35 max	0.50 max	0.50 max	0.50 max
P	0.015 max	0.010 max	0.015 max	0.020 max	0.025 max	0.020 max	0.020 max	0.015 max
S	0.010 max	0.010 max	0.010 max	0.003 max	0.001 max	0.010 max	0.010 max	0.0010 max
B	0.006 max	0.0060 max	—	—	—	—	—	0.0060 max
Cu	0.23 max	0.23 max	—	0.50 to 0.00	1.00 to 2.00	1.50 to 3.00	1.50 to 3.00	0.044 max
Pb	0.001 max	0.0010 max	—	—	—	—	—	—
Se	—	0.0005 max	—	—	—	—	—	—
Bi	—	0.001 max	—	—	—	—	—	—
Ca <sup>b</sup>	—	0.005 max	—	—	—	—	—	—
Mg <sup>b</sup>	—	0.0060 max	—	—	—	—	—	—
W	—	—	—	—	1.00 max	—	—	—

<sup>a</sup> Shall be determined arithmetically by difference or by direct measurement.

<sup>b</sup> To be determined if intentionally added.

<sup>c</sup> Some limits are more restrictive than the UNS chemistry.

— Not required

Section 4.1.2.1.3: Replace the section header with the following:

**4.1.2.1.3 UNS N09925, UNS N09935, UNS N09945, UNS N09946, and UNS N09955**

Table 2: The table shall be updated as indicated by the red boxes:

**Table 2—Heat Treatment Procedures**

UNS	Material Designation	Solution Annealing		Age Hardening
		Material Temperature	Time (hours)	Material Temperature and Time
N07716	120K 140K	1875 °F–1925 °F (1024 °C–1052 °C)	0.5 to 4 <sup>b</sup>	1310 °F–1455 °F (710 °C–791 °C) for 4–9 hours, furnace cool to 1125 °F–1275 °F (607 °C–691 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N07718	120K	1870 °F–1925 °F (1021 °C–1052 °C)	1 to 2.5 <sup>a</sup>	1425 °F–1475 °F (774 °C–802 °C) for 6–8 hours <sup>b</sup>
	140K	1870 °F–1925 °F (1021 °C–1052 °C)	1 to 2.5 <sup>a</sup>	1400 °F–1475 °F (760 °C–802 °C) for 6–8 hours <sup>b</sup>
	150K	1870 °F–1925 °F (1021 °C–1052 °C)	1 to 2.5 <sup>c</sup>	1292 °F–1382 °F (700 °C–750 °C) for 1 hour minimum, furnace cool to 1112 °F–1202 °F (600 °C–650 °C), and hold for 8 hours minimum <sup>d</sup>
N07725	120K	1875 °F–1950 °F (1024 °C–1066 °C)	0.5 to 4 <sup>b</sup>	1325 °F–1425 °F (718 °C–774 °C) for 4–9 hours, furnace cool to 1125 °F–1275 °F (607 °C–691 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09925	110K	1825 °F–1925 °F (996 °C–1052 °C)	0.5 to 4 <sup>a</sup>	1325 °F–1400 °F (718 °C–760 °C) for 4–9 hours, furnace cool to 1115 °F–1220 °F (607 °C–660 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09935	110K	1870 °F–1975 °F (1021 °C–1079 °C)	0.5 to 4 <sup>a</sup>	1115 °F–1435 °F (729 °C–779 °C) for 4–9 hours, furnace cool to 1165 °F–1255 °F (629 °C–679 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09945	125K	1800 °F–1950 °F (982 °C–1066 °C)	0.5 to 4 <sup>a</sup>	1250 °F–1350 °F (677 °C–732 °C) for 4–9 hours, furnace cool to 1110 °F–1190 °F (599 °C–643 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09955	120K	1868 °F–1976 °F (1020 °C–1080 °C)	0.5 to 6 <sup>a</sup>	1328 °F–1436 °F (720 °C–780 °C) for 4–8 hours <sup>d</sup>
N09955	140K	1868 °F–1976 °F (1020 °C–1080 °C)	0.5 to 6 <sup>a</sup>	1328 °F–1436 °F (720 °C–780 °C) for 4–8 hours, air cooling to room temperature, heating at 1112 °F to 1202 °F (600 °C–650 °C) and hold for a combined total aging time for both cycles of 10 hours minimum <sup>d</sup>
N09946	140K	1800 °F–1950 °F (982 °C–1066 °C)	0.5 to 4 <sup>a</sup>	1250 °F–1350 °F (677 °C–732 °C) for 4–9 hours, furnace cool to 1110 °F–1190 °F (599 °C–643 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09946	150K	1800 °F–1925 °F (982 °C–1052 °C)	0.5 to 4 <sup>a</sup>	1250 °F–1350 °F (677 °C–732 °C) for 4–9 hours, furnace cool to 1110 °F–1190 °F (599 °C–643 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>
N09946	160K	1825 °F–1950 °F (996 °C–1066 °C)	0.5 to 4 <sup>a</sup>	1250 °F–1350 °F (677 °C–732 °C) for 4–9 hours, furnace cool to 1110 °F–1190 °F (599 °C–643 °C), and hold for total aging time of 12 hours minimum <sup>b</sup>

<sup>a</sup> Cool in air, inert gas, water, polymer, or oil to ambient temperature. Air cooling or inert gas cooling of section thickness greater than 3 inches shall only be upon agreement between purchaser, manufacturer, and end user.

<sup>b</sup> Cool in air, inert gas, water, polymer, or oil to ambient temperature.

<sup>c</sup> Air cool or faster.

<sup>d</sup> Air cool.

Table 5: The table shall be updated as indicated by the red boxes:

Table 5—Tensile Requirements

UNS number	Material Designation	QTC Cross-section Thickness * in. (mm)	0.2% Yield Strength Min. ksi (MPa)	0.2% Yield Strength Max. ksi (MPa)	Tensile Strength Min. ksi (MPa)	Elongation in 4D Min. %	Reduction of Area Min. %
N07716	120K	≤10 (254)	120 (827)	150 (1034)	150 (1034)	20	35
		>10 (254)	120 (827)	150 (1034)	150 (1034)	20	25
	140K	≤10 (254)	140 (965)	160 (1103)	165 (1138)	18	30
		>10 (254)	140 (965)	160 (1103)	165 (1138)	18	20
N07718	120K	≤10 (254)	120 (827)	145 (1000)	150 (1034)	20	35
		>10 (254)	120 (827)	145 (1000)	150 (1034)	20	25
	140K	≤10 (254)	140 (965)	150 (1034)	165 (1138)	20	35
		>10 (254)	140 (965)	150 (1034)	165 (1138)	20	25
	150K	≤10 (254)	150 (1034)	175 (1207)	175 (1207)	20	35
		>10 (254)	150 (1034)	175 (1207)	175 (1207)	20	25
N07725	120K	≤10 (254)	120 (827)	150 (1034)	150 (1034)	20	35
		>10 (254)	120 (827)	150 (1034)	150 (1034)	20	25
N09925	110K	≤10 (254)	110 (758)	140 (965)	140 (965)	18	25
		>10 (254)	110 (758)	140 (965)	140 (965)	18	20
N09935	110K	≤10 (254)	110 (758)	140 (965)	140 (965)	18	25
		>10 (254)	110 (758)	140 (965)	140 (965)	18	20
N09945	125K	≤10 (254)	125 (862)	155 (1069)	160 (1138)	18	25
		>10 (254)	125 (862)	155 (1069)	150 (1034)	18	20
N09955	120K	≤10 (254)	120 (827)	145 (1000)	150 (1034)	25	45
		>10 (254)	120 (827)	145 (1000)	150 (1034)	25	40
	140K	≤10 (254)	140 (965)	155 (1069)	165 (1138)	20	40
		>10 (254)	140 (965)	155 (1069)	165 (1138)	20	35
N09946	140K	≤10 (254)	140 (965)	165 (1138)	165 (1138)	18	25
		>10 (254)	140 (965)	165 (1138)	165 (1138)	18	20
	150K	≤10 (254)	150 (1034)	170 (1172)	170 (1172)	18	25
		>10 (254)	150 (1034)	170 (1172)	170 (1172)	18	20
	160K	≤10 (254)	160 (1103)	180 (1241)	180 (1241)	18	25
		>10 (254)	160 (1103)	180 (1241)	180 (1241)	18	20

\* QTC cross-section thickness at time of heat treatment.

Table 6: The table shall be updated as indicated by the red boxes:

**Table 6—Charpy V-notch Impact Toughness Requirements (10 mm x 10 mm)**

UNS Number	Material Designation	QTC Cross-section <sup>a</sup> Thickness in. (mm)	Orientation <sup>b</sup>	Minimum Average ft-lbs (J)	Minimum Single ft-lbs (J)	Minimum Lateral Expansion in. (mm)
N07716	120K	< 3 (76)	Longitudinal	40 (54)	35 (47)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	37 (50)	32 (43)	0.015 (0.38)
		> 10 (254)	Transverse	32 (43)	27 (37)	0.015 (0.38)
	140K	< 3 (76)	Longitudinal	40 (54)	35 (47)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
N07718	120K	< 3 (76)	Longitudinal	50 (68)	45 (61)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
	140K	< 3 (76)	Longitudinal	50 (68)	45 (61)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
	150K	< 3 (76)	Longitudinal	50 (68)	45 (61)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
N07725	120K	< 3 (76)	Longitudinal	40 (54)	35 (47)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	37 (50)	32 (43)	0.015 (0.38)
		> 10 (254)	Transverse	32 (43)	27 (37)	0.015 (0.38)
N09925	110K	< 3 (76)	Longitudinal	35 (47)	32 (43)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	32 (43)	0.015 (0.38)
		> 10 (254)	Transverse	35 (47)	32 (43)	0.015 (0.38)
N09935	110K	< 3 (76)	Longitudinal	35 (47)	30 (41)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	30 (41)	25 (34)	0.015 (0.38)
		> 10 (254)	Transverse	25 (34)	20 (27)	0.015 (0.38)
N09945	125K	< 3 (76)	Longitudinal	50 (68)	45 (61)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	40 (54)	35 (47)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
N09946	140K	< 3 (76)	Longitudinal	45 (61)	40 (54)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
	150K	< 3 (76)	Longitudinal	45 (61)	40 (54)	0.015 (0.38)
		≥ 3 (76) through 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		> 10 (254)	Transverse	30 (41)	27 (37)	0.015 (0.38)
	160K	≥ 3 (76) through 10 (254)	Transverse	27 (37)	25 (34)	0.015 (0.38)
		> 10 (254)	Transverse	27 (37)	25 (34)	0.015 (0.38)
		< 3 (76)	Longitudinal	70 (95)	65 (88)	0.025 (0.64)
N09955	120K	≥ 3 (76) through 10 (254)	Transverse	50 (68)	45 (61)	0.025 (0.64)
		> 10 (254)	Transverse	45 (61)	40 (54)	0.020 (0.51)
		< 3 (76)	Longitudinal	60 (81)	55 (75)	0.020 (0.51)
	140K	≥ 3 (76) through 10 (254)	Transverse	40 (54)	35 (47)	0.015 (0.38)
		> 10 (254)	Transverse	35 (47)	30 (41)	0.015 (0.38)
		< 3 (76)	Longitudinal	40 (54)	35 (47)	0.015 (0.38)

<sup>a</sup> QTC cross-section thickness at time of heat treatment.

<sup>b</sup> See 4.4.1 for specific requirements regarding the orientation.

Table 7: The table shall be updated as indicated by the red boxes:

Table 7—Hardness Requirements

UNS number	Material Designation	Minimum Hardness HRC (HBW)	Maximum Hardness HRC (HBW)
N07716	120K	32 <sup>(a)</sup>	43 <sup>(a)c</sup>
	140K	34 <sup>(a)</sup>	43 <sup>(a)c</sup>
N07718	120K	32 <sup>(a)</sup>	40 <sup>(a)b</sup>
	140K	34 <sup>(a)</sup>	40 <sup>(a)b</sup>
	150K	35 <sup>(a)</sup>	45 <sup>(a)b</sup>
N07725	120K	32 <sup>(a)</sup>	43 <sup>(a)c</sup>
N09925	110K	26 <sup>(a)</sup>	38 <sup>(a)b</sup>
N09935	110K	24 <sup>(a)</sup>	34 <sup>(a)b</sup>
N09945	125K	32 <sup>(a)</sup>	42 <sup>(a)b</sup>
N09946	140K	34 <sup>(a)</sup>	42 <sup>(a)b</sup>
	150K	35 <sup>(a)</sup>	46 <sup>(a)c</sup>
	160K	36 <sup>(a)</sup>	46 <sup>(a)c</sup>
N09955	120K	32 <sup>(a)</sup>	40 <sup>(a)b</sup>
	140K	34 <sup>(a)</sup>	42 <sup>(a)b</sup>

<sup>a</sup> The conversion of hardness readings to or from other scales is material-dependent. The Rockwell C scale is the preferred hardness method for hardness testing the family of alloys covered by ASTM B6ACRA since compliance with ANSI/NACE MR0175 is frequently required and ANSI/NACE MR0175 specifies the maximum acceptable hardness limits using the Rockwell C scale. When conversions from other hardness scales to the Rockwell C scale are required or vice versa, one of two methods shall be used:

- a hardness conversion agreed to by the equipment manufacturer and the end user;
- ASTM E140 conversion.

When a conflict exists between Rockwell C scale hardness numbers and Brinell hardness numbers, the Rockwell C scale shall be the referee method.

When a conversion other than the ASTM E140 conversion is utilized, the conversion method shall be documented and traceable to test results.

In accordance with ASTM E140, when reporting converted hardness numbers, the measured hardness and test scale shall be reported in parentheses. For example, 20.0 HRC (228 HBW), where 20.0 HRC is the converted hardness value and 228 HBW is the original measurement value and test scale.

<sup>b</sup> Maximum hardness limits shall be in accordance with ANSI/NACE MR0175.

<sup>c</sup> These values represent the least-restrictive hardness limits presented in ANSI/NACE MR0175 for the individual alloys. See ANSI/NACE MR0175 for hardness limits for specific temperature and/or elemental sulfur environments.

*The captions for Figures A.10 through A.17 shall be replaced by the following:*

**Figure A.10—Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725**

**Figure A.11—Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Isolated Grain Boundary Precipitation**

**Figure A.12—Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles**

**Figure A.13—Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles**

**Figure A.14—Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Full Coverage of Grain Boundaries with Second Phase Particles**

**Figure A.15—Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Acicular Grain Boundary Precipitates**

**Figure A.16—Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Due To Acicular Precipitates**

**Figure A.17—Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Grain Boundary Precipitates**

## Contents

	Page
<b>1 Scope</b> .....	<b>1</b>
<b>1.1 Purpose</b> .....	<b>1</b>
<b>1.2 Applicability</b> .....	<b>1</b>
<b>2 Normative References</b> .....	<b>1</b>
<b>3 Terms, Definitions, and Abbreviated Terms</b> .....	<b>2</b>
<b>3.1 Terms and Definitions</b> .....	<b>2</b>
<b>3.2 Abbreviated Terms</b> .....	<b>3</b>
<b>4 Requirements for Age-hardened Nickel-based Alloys</b> .....	<b>3</b>
<b>4.1 Process Control Requirements</b> .....	<b>3</b>
<b>4.2 Testing Requirements</b> .....	<b>9</b>
<b>5 Certification</b> .....	<b>18</b>
<b>6 Marking</b> .....	<b>19</b>
<b>7 Addition of New Alloys and/or New Material Designations</b> .....	<b>19</b>
<b>Annex A (informative) Reference Microstructures</b> .....	<b>20</b>
<b>Annex B (normative) Criteria for Consideration of a New Alloy and/or Alloy Material Designation</b> .....	<b>38</b>

## Figures

<b>A.1 Acceptable Microstructure for UNS N07718</b> .....	<b>21</b>
<b>A.2 Acceptable Microstructure for UNS N07718</b> .....	<b>22</b>
<b>A.3 Acceptable Microstructure for UNS N07718 Showing Isolated Grain Boundary Precipitates</b> .....	<b>23</b>
<b>A.4 Acceptable Microstructure for UNS N07718 Showing Isolated Acicular Grain Boundary Precipitates</b> ..	<b>24</b>
<b>A.5 Unacceptable Microstructure for UNS N07718 Showing Acicular Grain Boundary Precipitates</b> .....	<b>25</b>
<b>A.6 Unacceptable Microstructure for UNS N07718 Showing Acicular Grain Boundary Precipitates</b> .....	<b>26</b>
<b>A.7 Unacceptable Microstructure for UNS N07718 Showing Acicular Grain Boundary Precipitates</b> .....	<b>27</b>
<b>A.8 Unacceptable Microstructure for UNS N07718 Showing Acicular Grain Boundary Precipitates</b> .....	<b>28</b>
<b>A.9 Unacceptable Microstructure for UNS N07718 Showing Grain Boundary Precipitates</b> .....	<b>29</b>
<b>A.10 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725</b> .....	<b>30</b>
<b>A.11 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Isolated Grain Boundary Precipitation</b> .....	<b>31</b>
<b>A.12 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>32</b>
<b>A.13 Acceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Partial Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>33</b>
<b>A.14 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Full Coverage of Grain Boundaries with Second Phase Particles</b> .....	<b>34</b>
<b>A.15 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Acicular Grain Boundary Precipitates</b> .....	<b>35</b>

## Contents

Page

<b>A.16 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Due To Acicular Precipitates . . . . .</b>	<b>36</b>
<b>A.17 Unacceptable Microstructure for UNS N09925, UNS N09935, UNS N09945, UNS N09946, UNS N09955, UNS N07716, and UNS N07725 Showing Grain Boundary Precipitates . . . . .</b>	<b>37</b>

### Tables

<b>1 Chemical Composition . . . . .</b>	<b>5</b>
<b>2 Heat Treatment Procedures . . . . .</b>	<b>8</b>
<b>3 Etchants Used for Macroetch Examination . . . . .</b>	<b>9</b>
<b>4 Etchants Used for Microstructure Examination . . . . .</b>	<b>10</b>
<b>5 Tensile Requirements . . . . .</b>	<b>13</b>
<b>6 Charpy V-notch Impact Toughness Requirements (10 mm × 10 mm). . . . .</b>	<b>15</b>
<b>7 Hardness Requirements . . . . .</b>	<b>17</b>

## Introduction

This standard for Age-Hardened Nickel-Based Alloys was formulated by the API Committee on Standardization of Oilfield Equipment and Materials (CSOEM), Subcommittee on Valves and Wellhead Equipment (SC6), Materials Task Group. It is based on the conclusions of a task group evaluation of requirements needed for Age-Hardened Nickel-Based Alloys to supplement the existing requirements of API Specification 6A, *Specification for Wellhead and Christmas Tree Equipment*.

# Age-hardened Nickel-based Alloys for Oil and Gas Drilling and Production Equipment

## 1 Scope

### 1.1 Purpose

This document provides requirements for age-hardened nickel-base alloys that are intended to supplement the existing requirements of API 6A. For downhole applications, refer to API 5CRA.

These additional requirements include detailed process control requirements and detailed testing requirements. The purpose of these additional requirements is to ensure that the age-hardened nickel-base alloys used in the manufacture of API 6A pressure-containing and pressure-controlling components are not embrittled by the presence of an excessive level of deleterious phases and meet the minimum metallurgical quality requirements.

NOTE Failures attributed to hydrogen-induced stress cracking (HISC) have been reported in production equipment and early in the life of subsea equipment made from age-hardened nickel-base alloys. Some age-hardened nickel-base alloys that meet the requirements of NACE MR0175 and API 6ACRA may be susceptible to HISC. Sources of hydrogen charging include but are not limited to galvanic coupling to a more active material, direct exposure to seawater with cathodic protection (CP), and decomposition of brines. The industry is evaluating alternate test methods and/or acceptance criteria to identify material with susceptibility to HISC.

### 1.2 Applicability

This standard is intended to apply to pressure-containing and pressure-controlling components as defined in API 6A. Requirements of this standard may be applied by voluntary conformance by a manufacturer, normative reference in API 6A or other product specification(s), or by contractual agreement.

## 2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Specification 6A, *Specification for Wellhead and Christmas Tree Equipment*

ASTM A370<sup>1</sup>, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

ASTM A604, *Standard Practice for Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets*

ASTM B880, *Standard Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys*

ASTM E10, *Standard Test Method for Brinell Hardness Test of Metallic Materials*

ASTM E18, *Standard Test Methods for Rockwell Hardness of Metallic Materials*

ASTM E29, *Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications*

ASTM E110, *Standard Test Method for Rockwell and Brinell Hardness of Metallic Materials by Portable Hardness Testers*

---

<sup>1</sup> ASTM International, 100 Barr Harbor Drive, West Conshohocken, Pennsylvania 19428-2959. [www.astm.org](http://www.astm.org)