

Refractory Insulating Castables with Permanent Linear Change Anomaly— Case Study

API TECHNICAL REPORT 983
FIRST EDITION, MARCH 2025



American
Petroleum
Institute

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed. The use of API publications is voluntary. In some cases, third parties or authorities having jurisdiction may choose to incorporate API standards by reference and may mandate compliance.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be used. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 200 Massachusetts Avenue, NW, Suite 1100, Washington, DC 20001-5571.

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Suggested revisions are invited and should be submitted to the Standards Department, API, 200 Massachusetts Avenue NW, Suite 1100, Washington, DC 20001, standards@api.org.

Currently in preview, click buy full version

Currently in preview, click buy full version

Contents

	Page
1 Scope.....	1
2 Normative References	1
3 Terms, Definitions, Abbreviations, and Acronyms	1
3.1 Terms and Definitions	1
3.2 Abbreviations and Acronyms	2
4 Background.....	2
4.1 General	2
4.2 Why is This a Problem?	2
4.3 API Sponsored Study	2
5 Test Procedure.....	3
5.1 General	3
5.2 Refractory Material	3
5.3 Sample Preparation	3
5.4 Sample Testing	4
6 Results	4
7 Discussion of Results	6
8 Conclusions	6
9 Recommendations	7
Annex A (informative) Tabulated Test Results	8
Bibliography.....	10

Figures

1 Dried to Fired PLC (2300 °F to 1500 °F) vs. Curing Time	5
2 MOR After Firing to 816 °C (1500 °F) Curing Time.....	5
3 CCS After Firing to 816 °C (1500 °F) vs. Curing Time.....	6
4 Density after Firing to 816 °C (1500 °F) vs. Curing Time.....	6

Tables

1 Generic 2300 °F Insulating Castable (API-1).....	3
2 Cure Times	4

Currently in preview, click buy full version

Refractory Insulating Castables with Permanent Linear Change Anomaly— Case Study

1 Scope

This technical report documents an observed anomaly with the permanent linear change (PLC) of insulating castables with a density less than 1280 kg/m³ (80 pcf). The curing time is shown to impact the permanent linear change when samples are subsequently fired to 816 °C (1500 °F). The sample preparation and testing were performed by an independent laboratory on behalf of the API Refractory Projects Group.

Disclaimer: This report only reviews the data from one castable material, which was only tested by one laboratory. Therefore, it may not be conclusive that this anomaly is applicable to all castables with a density less than 80 pcf. While originally adapted from fired refractory brick testing, it should be noted that PLC has been a long-standing physical property measurement for castables to monitor and control the permanent linear shrinkage. Over this extended period of commercial practice, the test has proven to be an effective tool to monitor excessive shrinkage cracking during initial heating of newly installed castable linings without time-factoring for the anomaly before firing. Further study is required to determine if this anomaly is unique to the refractory formulation or more widely relevant to the overall population of lightweight, castable refractories being manufactured from a wide range of raw materials and additives to make products that otherwise appear similar.

2 Normative References

No other document is identified as indispensable or required for the application of this report. A list of documents associated with API 983 are included in the bibliography.

3 Terms, Definitions, Abbreviations, and Acronyms

3.1 Terms and Definitions

3.1.1

castable (refractory)

A combination of refractory grain (aggregate) and suitable bonding agent that, after the addition of a proper liquid, is installed into place to form a monolithic shape or structure that becomes rigid because of thermal or chemical action.

3.1.2

cement (refractory)

A powdery substance that is mixed with water and will harden by itself hydraulically and generally bind larger aggregates into a refractory system. Refractory cements are higher-temperature materials and generally are based on calcium aluminates, but can include other materials, such as hydrated alumina.

3.1.3

curing

The process of bond formation in a newly installed monolithic refractory.

NOTE For hydraulic bonded castables, curing occurs at room temperature and is facilitated by an excess of water being present to react with the cement component. For phosphate-bonded plastic refractories, heating to 500 °F to 700 °F (260 °C to 370 °C) is required to form the bond.

3.1.4

density

The mass of a unit volume of a substance, usually expressed in kilograms per cubic meter (kg/m³), grams per cubic centimeter (g/cm³), or pounds per cubic foot (lb/ft³).