

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 11: Coal—Forms of sulfur**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 31 October 2002 and published on 13 November 2002.

---

The following are represented on Committee MN-001:

Australasian Institute of Mining and Metallurgy  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
CSIRO Energy Technology  
Coalfield Geology Council of N.S.W.  
Department of Natural Resources and Mines, Qld  
Electricity Supply Association of Australia  
Institution of Engineers Australia  
Minerals Council of Australia  
University of Newcastle  
University of New South Wales  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the online catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 11: Coal—Forms of sulfur**

Originated as AS K152.11—1965.  
Previous edition AS 1038.11—1993.  
Fourth edition 2002.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4916 X

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-001, Coal and Coke, to supersede AS 1038.11—1993, *Coal and coke—Analysis and testing Part 11: Coal—Forms of sulfur*.

This Standard confirms the methods for the determination of the different forms of sulfur and has been editorially updated to be consistent with the other parts of the AS 1038 series.

The term ‘informative’ has been used in this Standard to define the application of the appendix to which it applies. An ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD .....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE .....	5
1.2 REFERENCED DOCUMENTS .....	5
1.3 DEFINITIONS .....	5
1.4 PRINCIPLE .....	6
1.5 SAFETY .....	6
1.6 SAMPLE .....	6
1.7 REPORTING OF RESULTS .....	7
1.8 PRECISION .....	7
1.9 TEST REPORT .....	7
SECTION 2 DETERMINATION OF SULFATE SULFUR	
2.1 PRINCIPLE .....	8
2.2 REAGENTS .....	8
2.3 APPARATUS .....	8
2.4 PROCEDURE .....	9
2.5 CALCULATION .....	10
SECTION 3 DETERMINATION OF PYRITIC SULFUR	
3.1 PRINCIPLE .....	11
3.2 EXTRACTION OF THE PYRITIC IRON .....	11
3.3 DETERMINATION OF PYRITIC IRON—TITRIMETRIC METHOD .....	12
3.4 DETERMINATION OF PYRITIC IRON—SPECTROPHOTOMETRIC METHOD .....	14
3.5 DETERMINATION OF PYRITIC IRON—ATOMIC ABSORPTION SPECTROMETRIC METHOD .....	16
SECTION 4 ORGANIC SULFUR .....	18
APPENDIX A DERIVATION OF FACTORS USED IN THE CALCULATIONS .....	19

## FOREWORD

Sulfur in coal is present in organic combination as part of the coal substance, as pyrite or less frequently marcasite, and as sulfates. The pyritic and marcasite forms of sulfur have the same chemical composition ( $\text{FeS}_2$ ) but have different crystalline forms, pyrite being isometric and marcasite orthorhombic. In this Standard no distinction is made between sulfur present in pyrite and marcasite.

Non-pyritic sulfide sulfur occurs in some coals, predominantly as sphalerite (zinc sulfide). In Australian coals, the concentration of sphalerite is generally less than 0.1%. The occurrence of a significant concentration of non-pyritic sulfide sulfur can be determined by the detection of the objectionable odour of hydrogen sulfide gas on addition of hydrochloric acid to the coal.

Sulfate sulfur is present in coal primarily as either gypsum or iron sulfate. The former is present in fresh coal and the latter results with weathering of coal, although iron sulfates may be present in fresh coal in small amounts. Sulfate sulfur can be extracted from the coal by treatment with hydrochloric acid.

In the determination of pyritic sulfur, the coal is first extracted with hydrochloric acid to remove sulfate and non-pyritic sulfide sulfur, and non-pyritic iron. The residue is then extracted with nitric acid to decompose the pyritic sulfur, which is determined indirectly by measuring the pyritic iron concentration.

Organic sulfur is chemically linked to the coal structure and generally cannot be removed by physical methods. Organic sulfur is determined by difference after subtracting pyritic and sulfate sulfur from the total sulfur.

## STANDARDS AUSTRALIA

### Australian Standard Coal and coke—Analysis and testing

#### Part 11: Coal—Forms of sulfur

## SECTION 1 SCOPE AND GENERAL

### 1.1 SCOPE

This Standard sets out methods for the determination of sulfate sulfur, pyritic sulfur and organic sulfur in coal.

The methods are as follows:

- Sulfate sulfur is determined directly as a sulfate in a hydrochloric acid extract of the sample.
- Pyritic sulfur is calculated from the determination of iron soluble in nitric acid following removal of non-pyritic iron by hydrochloric acid.
- Organic sulfur is obtained by subtracting the sum of the pyritic sulfur and sulfate sulfur from the total sulfur, determined by one of the methods given in AS 1038.6.3.

### 1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1038	Coal and coke—Analysis and testing
1038.3	Part 3: Proximate analysis of higher rank coal
1038.6.3	Part 6.3: Ultimate analysis of higher rank coal—Total sulfur (series)
1038.16	Part 16: Assessment and reporting of results
2134	Recommended practice for chemical analysis by atomic absorption spectrometry
2134.1	Part 1: Flame atomic absorption spectrometry
2243	Safety in laboratories (series)
2418	Coal and coke—Glossary of terms
2508	Safe storage and handling information card
4264	Coal and coke—Sampling
4264.1	Part 1: Higher rank coal—Sampling procedures
2706	Numerical values—Rounding and interpretation of limiting values
3753	Recommended practice for chemical analysis by ultraviolet/visible spectrophotometry
ISO	
157	Coal—Determination of forms of sulfur

### 1.3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2418 apply.