

Australian Standard<sup>®</sup>

---

**Coal and coke—Analysis and testing**

**Part 12.3: Higher rank coal—  
Caking and coking properties—  
Dilatation**

---

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 10 September 1993 and published on 13 December 1993.

---

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy  
Australian Chamber of Commerce and Industry  
Australian Coal Association  
Australian Coal Industry Research Laboratories  
Australian Coal Preparation Society  
Australian Institute of Energy  
Australian Mining Industry Council  
Bureau of Steel Manufacturers of Australia  
CSIRO, Division of Coal and Energy Technology  
Department of Resource Industries, Queensland  
Electricity Supply Association of Australia  
Institution of Engineers, Australia  
National Association of Testing Authorities Australia  
Queensland Coal Board  
Royal Australian Chemical Institute  
Standing Committee on Coalfield Geology of New South Wales  
University of Newcastle  
University of New South Wales  
University of Queensland

---

**Revision of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

Australian Standard<sup>®</sup>

---

**Coal and coke—Analysis and testing**

**Part 12.3: Higher rank coal—  
Caking and coking properties—  
Dilatation**

---

First published as AS 1038.12.3—1984.  
Second edition 1993.

Incorporating:  
Amdt 1—1999

PUBLISHED BY STANDARDS AUSTRALIA  
(STANDARDS ASSOCIATION OF AUSTRALIA)  
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 8587 0

## PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Coal Evaluation, under the supervision of the Committee on Coal and Coke and the direction of the Multitechnics Standards Policy Board, as a revision of AS 1038.12.3—1984, *Methods for the analysis and testing of coal and coke, Part 12.3: Determination of the dilatometer characteristics of higher rank coal*. It describes procedures for determining the dilatometer characteristics of higher rank coal using a metal-core furnace. It is based on ISO 8264:1989, *Hard coal—Determination of the swelling properties using a dilatometer* and BS 1016, *Methods for analysis and testing of coal and coke, Section 107.3:1990, Determination of swelling properties using a dilatometer*, both of which are Ruhr dilatometer methods. Solid core furnaces are specified in all these standard methods.

This Standard is one of a series of Standards for assessing physical properties of coal. The other parts of this series are as follows:

- Part 12.1: Crucible swelling number
- Part 12.2: Gray-King coke type
- Part 12.4: Plasticity—Gieseler method

The precision data reported in Clause 10 have been taken directly from ISO 8264.

The changes from the previous edition of this Standard are as follows.

- (a) Deletion of use of an air-core furnace, due to inherent problems in achieving the designated temperature characteristics of the furnace.
- (b) Inclusion of a measuring device for checking mould dimensions.
- (c) Addition of checking for wear on the retorts.
- (d) Alignment of precision with that given in ISO 8264.

The term 'normative' has been used in this Standard to define the application of the appendix to which it applies. A 'normative' appendix is an integral part of a Standard.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## CONTENTS

	<i>Page</i>
1 SCOPE .....	4
2 REFERENCED DOCUMENTS .....	4
3 DEFINITIONS .....	4
4 PRINCIPLE .....	5
5 SAFETY .....	5
6 APPARATUS .....	5
7 PREPARATION OF COAL PENCIL .....	7
8 DILATATION TEST PROCEDURE .....	8
9 REPORTING OF RESULTS .....	9
10 PRECISION .....	9
11 TEST REPORT .....	9
APPENDIX A INSPECTION OF DILATOMETER RETORTS .....	16

## STANDARDS AUSTRALIA

## Australian Standard

## Coal and coke—Analysis and testing

Part 12.3: Higher rank coal—Caking and coking  
properties—Dilatation

**1 SCOPE** This Standard sets out a method for obtaining a quantitative measure of the dilatation of higher rank coal.

**2 REFERENCED DOCUMENTS** The following documents are referred to in this Standard:

AS

1038 Coal and coke—Analysis and testing

1038.16 Part 16: Acceptance and reporting of results

1152 Test sieves

2096 Classification and coding systems for Australian coal

2243 Safety in laboratories

2418 Glossary of terms relating to solid mineral fuels

2508 Safe storage and handling information cards for hazardous materials

2646 Sampling of solid mineral fuels

2646.6 Part 6: Hard coal—Preparation of samples

**3 DEFINITIONS** For the purpose of this Standard, the definitions given in AS 2418 and those below apply.

**3.1 Duplicate dilatation tests**—tests carried out at different times on two coal pencils prepared before each heating cycle from a single coal sample and treated in the same retort in the same furnace in independent heating cycles by the same operator.

**3.2 Higher rank coal** (as defined in AS 2096)—coal having a gross specific energy of 21.00 MJ/kg or greater on an ash-free, moist basis *and* a gross specific energy of 27.00 MJ/kg or greater on a dry, ash-free basis.

**3.3 Maximum contraction**—the maximum downward movement of the dilatometer piston, measured from the zero point and expressed as a percentage of the initial pencil length (see Figure 1(c)). However, if the final trace of the curve is not truly horizontal but slopes downward, the maximum contraction is the value observed at 500°C (see Figure 1(d)).

**3.4 Maximum dilatation**—the maximum upward movement of the dilatometer piston after contraction, measured from the zero point and expressed as a percentage of the initial pencil length. The value can be either positive or negative (see Figure 1).

**3.5 Temperature of initial contraction**—the temperature at which the downward movement of the dilatometer piston is 0.5 mm (see  $T_1$  in Figure 1).

**3.6 Reference retort and piston**—a retort and piston assembly used less than 25 times.

**3.7 Parallel dilatation tests**—tests carried out simultaneously on two coal pencils prepared at the same time from a single coal sample and treated in two retorts in the same furnace during a single heating cycle.