

Dup.
Superseded by AS 1038.14.2-1995
Under Revision see DR93323

AS 1038.14.2—1985
UDC [662.66 + 662.74]:620.16

Australian Standard[®] 1038.14.2—1985

**METHODS FOR THE ANALYSIS AND
TESTING OF COAL AND COKE**

**Part 14.2—ANALYSIS OF
HIGHER RANK COAL
ASH AND COKE ASH
(ACID DIGESTION—
FLAME ATOMIC
ABSORPTION
SPECTROMETRIC
METHOD)**



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter



This Australian standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of the Standards Association of Australia on 4 September 1985 and published on 4 October 1985.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Industry Research Laboratories Ltd
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Coal Preparation Societies of New South Wales and Queensland
Confederation of Australian Industry
CSIRO, Division of Fossil Fuels
Department of Mineral Resources, N.S.W.
Department of Mines, Qld
Department of National Development
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
Queensland Coal Board
Royal Australian Chemical Institute
Standing Committee on Coalfield Geology, N.S.W.
State Chemical Laboratories, N.S.W.
Universities

Revision of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and of any amendments thereto.

Further details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 84242.

AUSTRALIAN STANDARD

**METHODS FOR THE ANALYSIS AND
TESTING OF COAL AND COKE**

Part 14.2

**ANALYSIS OF HIGHER RANK
COAL ASH AND COKE ASH
(ACID DIGESTION—FLAME
ATOMIC ABSORPTION
SPECTROMETRIC METHOD)**

AS 1038.14.2—1985

First published 1985

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 A'ROTHUR ST, NORTH SYDNEY, N.S.W.



ISBN 0 7262 3938 0

PREFACE

This standard was prepared by the Association's Committee on Coal and Coke, as a companion standard to AS 1038, Part 14.1, Analysis of Coal Ash, Coke Ash and Mineral Matter (Borate Fusion—Flame Atomic Absorption Spectrometric Method). Whereas Part 14.1 specifies decomposition of the ash by borate fusion, this standard sets out a bomb digestion procedure using a hydrochloric acid/hydrofluoric acid mixture for the decomposition of higher rank coal ash and coke ash, followed by flame atomic absorption spectrometry for the determination of various elements in the ash.

By convention, both phosphorus and sulphur are included in the normal ash constituent analysis.

Phosphorus is determined spectrophotometrically in the solution prepared from the ash, while sulphur can be determined by the high temperature or gravimetric procedures.

The Committee organized an inter-laboratory test program to obtain information on the repeatability and reproducibility of the method. The following laboratories participated in the test program:

Australian Coal Industry Research Laboratories Ltd
 Cargo Superintendents Co. (A/Asia) Pty Ltd
 Newcastle Wallsend Coal Co. Pty Ltd
 R.W. Miller and Company Pty Limited
 SGS Australia Pty Ltd

CONTENTS

	<i>Page</i>
1 Scope	3
2 Application	3
3 Referenced Documents	3
4 Principle	3
5 Apparatus	3
6 Reagents	4
7 Sample Preparation	6
8 Determination of Aluminium, Calcium, Iron, Magnesium, Manganese, Potassium, Silicon, Sodium, and Titanium	6
9 Determination of Phosphorus	9
10 Calculation and Expression of Results	9
11 Test Report	10
APPENDIX A. PRECISION DATA FOR ELEMENTAL ANALYSIS OF COAL ASH AND COKE ASH	11

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1985

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

METHODS FOR THE ANALYSIS AND TESTING OF COAL AND COKE

Part 14.2—ANALYSIS OF HIGHER RANK COAL ASH AND COKE ASH
(ACID DIGESTION—FLAME ATOMIC ABSORPTION SPECTROMETRIC METHOD)

1 SCOPE. This standard sets out methods for the determination of aluminium, calcium, iron, magnesium, manganese, potassium, silicon, sodium and titanium in higher rank coal ash and coke ash by flame atomic absorption spectrometry, and for the determination of phosphorus in higher rank coal ash and coke ash by spectrophotometry. Higher rank coal is defined as coal having a gross specific energy of 27 MJ/kg or greater on a dry, ash-free basis.

NOTE: Although a volumetric approach has been specified for solution preparation, a gravimetric alternative may be used.

2 APPLICATION. This method is applicable to the determination of the elements listed in Clause 1 (expressed as oxides), in the concentration ranges specified in Table 1.

Table 1 has been devised to accommodate any type of ash which is likely to arise from Australian higher rank coals or cokes. The results in Appendix A have been obtained from test work carried out on the available samples. Although testing was not carried out with a comprehensive range of likely coal compositions, the method is expected to apply over the wider range covered by the calibration standards and indicated in Table 1.

TABLE 1
CONCENTRATION RANGES

Element	Reported as oxide	Range, percent
Silicon	SiO ₂	20 to 85
Aluminium	Al ₂ O ₃	10 to 50
Iron	Fe ₂ O ₃	0.1 to 15
Calcium	CaO	0.05 to 25
Magnesium	MgO	0.05 to 25
Sodium	Na ₂ O	0.05 to 12.5
Potassium	K ₂ O	0.05 to 12.5
Titanium	TiO ₂	0.1 to 5
Manganese	Mn ₂ O ₃	0.005 to 0.6
Phosphorus	P ₂ O ₅	0.01 to 5

3 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

- AS 1038 Methods for the Analysis and Testing of Coal and Coke
Part 3—Proximate Analysis of Hard Coal
Part 16—Reporting of Results*
- AS 1152 Test Sieves
- AS 2134 Chemical Analysis of Materials by Flame Atomic Absorption Spectroscopy
- AS CK19 Code of Recommended Practice for the Chemical Analysis of Materials by Ultraviolet/Visible Spectrophotometry
- ISO 5725 Precision of Test Methods—Determination of Repeatability and Reproducibility by Inter-laboratory Tests

4 PRINCIPLE. The sample is decomposed by digestion with hydrofluoric acid/hydrochloric acid mixture in a PTFE-lined bomb or polypropylene bottle. Boric acid is added to the digestion mixture to complex excess fluoride and the resulting solution is aspirated into an atomic absorption spectrometer after the appropriate dilutions have been made.

Phosphorus is determined spectrophotometrically on an aliquot of the diluted solution.

5 APPARATUS. The following apparatus is required:

5.1 Glassware. Grade A volumetric glassware shall be used throughout.

5.2 Atomic absorption spectrometer. The instrument and its usage shall comply with AS 2134. The instrument shall have burners suitable for use with air/acetylene and nitrous oxide/acetylene flames. The suggested flames and wavelengths are given in Table 2. Other parameters shall be adjusted in accordance with the manufacturer's instructions.

* In course of revision.