

Australian Standard™

Coal and coke—Analysis and testing

**Part 14.2: Higher rank coal ash and
coke ash—Major and minor elements—
Acid digestion/flame atomic absorption
spectrometric method**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 22 September 2003 and published on 14 November 2003.

The following are represented on Committee MN-001:

Australasian Institute of Mining and Metallurgy
Australian Building Codes Board
Australian Coal Association
Australian Coal Preparation Society
Australian Institute of Energy
Coalfield Geology Council of N.S.W.
CSIRO, Energy Technology
Department of Natural Resources and Mines, Qld
Electricity Supply Association of Australia
Minerals Council of Australia
University of Newcastle
University of New South Wales
University of Queensland

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia website at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 03380.

Australian Standard™

Coal and coke—Analysis and testing

**Part 14.2: Higher rank coal ash and
coke ash—Major and minor elements—
Acid digestion/flame atomic absorption
spectrometric method**

Formulated as AS 1038.14.2—1985.
Previous edition AS 1038.14.2—1995.
Third edition 2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5573 9

PREFACE

This Standard was prepared by the Standards Australia Subcommittee MN-00-01, Coal Evaluation, under the supervision of Committee MN-001. Coal and Coke, as a revision of AS 1038.14.2—1995, *Coal and coke—Analysis and testing, Part 14.2: Higher rank coal ash and coke ash—Major and minor elements—Acid digestion/flame atomic absorption spectrometric method*. It is a companion to AS 1038.14.1, *Coal and coke—Analysis and testing, Part 14.1: Higher rank coal ash and coke ash—Major and minor elements—Borate fusion/flame atomic absorption spectrometric method*.

Part 14.1 specifies decomposition of the ash by borate fusion. This Standard sets out a bomb digestion procedure using a hydrochloric acid/hydrofluoric acid mixture for the decomposition of coal ash and coke ash, followed by flame atomic absorption spectrometry for the determination of various elements in the ash.

By convention, sulfur is included in the normal ash constituent analysis.

Phosphorus could be also determined spectrophotometrically in the solution prepared from the ash. Sulfur can be determined by the high temperature procedure.

The objective of this Standard is to provide those responsible for the analysis of coal ash and coke ash with a uniform method for the procedure.

The term 'informative' is used in this Standard to define the application of the Appendix to which it applies. An informative Appendix is for information and guidance only.

This Standard confirms the method of determining major and minor elements by the acid digestion/flame atomic absorption spectrometric method and has been editorially updated to the current format.

CONTENTS

	Page
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	5
3 DEFINITIONS.....	5
4 PRINCIPLE	5
5 SAFETY	5
6 REAGENTS	5
7 APPARATUS	8
8 SAMPLE PREPARATION.....	10
9 DETERMINATION OF ALUMINIUM, CALCIUM, IRON, MAGNESIUM, MANGANESE, POTASSIUM, SILICON, SODIUM AND TITANIUM	10
10 CALCULATION	13
11 REPORTING OF RESULTS	13
12 PRECISION.....	14
13 TEST REPORT.....	14
APPENDIX A PRECISION DATA FOR ELEMENTAL ANALYSIS OF COAL ASH AND COKE ASH.....	15

STANDARDS AUSTRALIA

Australian Standard

Coal and coke—Analysis and testing

Part 14.2: Higher rank coal ash and coke ash—Major and minor elements—
Acid digestion/flame atomic absorption spectrometric method

1 SCOPE

This Standard sets out methods for the determination of silicon, aluminium, iron, calcium, magnesium, sodium, potassium, titanium and manganese in higher rank coal ash and coke ash by flame atomic absorption spectrometry after acid digestion.

NOTE: Although a volumetric approach has been specified for solution preparation, a gravimetric alternative may be used.

A spectrophotometric method for the determination of phosphorus and a method for the determination of sulfur are also referenced.

This method is applicable to the determination of the elements listed above (expressed as oxides), in the concentration ranges specified in Table 1.

Table 1 has been devised to accommodate any type of ash that is likely to arise from Australian higher rank coals or cokes.

NOTE: The results in Appendix A have been obtained from test work carried out on the available samples. Although testing was not carried out with a comprehensive range of likely coal compositions, the method is expected to apply over the wider ranges covered by the calibration standards and indicated in Table 1.

TABLE 1
CONCENTRATION RANGES

Element	Reported as oxide	Range, %
Silicon	SiO ₂	20 to 85
Aluminium	Al ₂ O ₃	10 to 50
Iron	Fe ₂ O ₃	0.1 to 15
Calcium	CaO	0.5 to 25
Magnesium	MgO	0.5 to 25
Sodium	Na ₂ O	0.5 to 12.5
Potassium	K ₂ O	0.05 to 12.5
Titanium	TiO ₂	0.1 to 5
Manganese	Mn ₃ O ₄	0.005 to 0.6
Phosphorus	P ₂ O ₅	0.01 to 5
Sulfur	SO ₃	0.1 to 10