

Australian Standard[®]

**Methods for the analysis and
testing of coal and coke**

**Part 17: Determination of
moisture-holding capacity
(equilibrium moisture) of higher
rank coal**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 13 February 1989 and published on 11 August 1989.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Industry Research Laboratories
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Coal Preparation Society of N.S.W.
Coal Preparation Society of Queensland
Confederation of Australian Industry
CSIRO, Division of Coal Technology
Department of Minerals and Energy, N.S.W.
Department of Mines, Qld
Department of Primary Industries and Energy
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
National Association of Testing Authorities, Australia
Queensland Coal Board
Royal Australian Chemical Institute
Standing Committee on Coalfield Geology of New South Wales
University of New South Wales

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

**Methods for the analysis and
testing of coal and coke**

**Part 17: Determination of
moisture-holding capacity
(equilibrium moisture) of higher
rank coal**

First published as AS 1038.17—1989.

PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Coal Evaluation under the supervision of the Committee on Coal and Coke and the direction of the Minerals Standards Board in order to provide a method for determination of moisture-holding capacity which is used in the classification of higher rank coals.

CONTENTS

| | <i>Page</i> |
|-------------------------------|-------------|
| 1 SCOPE | 3 |
| 2 REFERENCED DOCUMENTS | 3 |
| 3 PRINCIPLE | 3 |
| 4 SAFETY | 3 |
| 5 REAGENTS | 3 |
| 6 APPARATUS | 3 |
| 7 PREPARATION OF SAMPLE | 6 |
| 8 PROCEDURE | 6 |
| 9 CALCULATION OF RESULT | 6 |
| 10 REPORTING OF RESULT | 6 |
| 11 PRECISION | 6 |
| 12 TEST REPORT | 6 |

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Methods for the analysis and testing of coal and coke

Part 17: Determination of moisture-holding capacity (equilibrium moisture) of higher rank coal

1 SCOPE. This Standard sets out a method for the determination of the moisture-holding capacity of higher rank coal (i.e. coals, as defined in AS 2096, having a gross specific energy of 21.00 MJ/kg or greater on an ash-free, moist basis and having a gross specific energy of 27.00 MJ/kg or greater on a dry, ash-free basis).

NOTE: The full moisture-holding capacity is that of the solid in equilibrium with an atmosphere saturated with moisture vapour, but as there are insuperable experimental difficulties in working with such atmospheres, a slightly lower humidity (96 percent) has been adopted as the standard one.

2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

| | |
|---------|---|
| AS | |
| 1038 | Methods for the analysis and testing of coal and coke |
| 1038.3 | Part 3: Proximate analysis of higher rank coal |
| 1038.16 | Part 16: Acceptance and reporting of results |
| 2096 | Classification and coding systems for Australian coals |
| 2243 | Safety in laboratories |
| 2508 | Safe storage and handling information cards for hazardous materials |
| 2706 | Numerical values-Rounding and interpretation of limiting values |

3 PRINCIPLE. The sample is brought to equilibrium and conditioned in an atmosphere of 96 percent relative humidity (attained by means of a potassium sulfate pulp) at 30°C, and at reduced pressure (not greater than 4 kPa). The moisture content is then determined by drying the conditioned coal to constant mass at 105°C, in a nitrogen atmosphere.

4 SAFETY. For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2508.

5 REAGENTS

5.1 General. Unless otherwise specified, all reagents shall be of analytical reagent grade, and only distilled water or water of equivalent purity shall be used.

5.2 Potassium sulfate pulp. Add sufficient potassium sulfate (K_2SO_4) to water to form a pulp. An excess of crystalline K_2SO_4 shall extend above the solution level.

5.3 Desiccant—granular anhydrous magnesium perchlorate for use in the drying tower (6.4) for drying air.

WARNING: REGENERATION BY OVEN DRYING SHOULD NOT BE ATTEMPTED BECAUSE OF THE RISK OF EXPLOSION. WHEN EXHAUSTED, MAGNESIUM PERCHLORATE SHOULD BE WASHED DOWN THE SINK WITH A STREAM OF WATER.

6 APPARATUS.

6.1 Conditioning vessel. The conditioning vessel shall be a vacuum desiccator with a base diameter between 120 mm and 150 mm and of sufficient depth to accommodate a bed of potassium sulfate pulp (5.2) 30 mm to 40 mm thick. The conditioning vessel is fitted with a glass, ceramic or corrosion-resistant metal stand to carry dishes above the level of the pulp, so that the dishes are protected from spray resulting from frothing. A second perforated parallel plate over the one actually covering the pulp prevents fouling of the support for the dishes. A suitable vessel is shown in Figure 1.

6.2 Constant-temperature incubator. The constant-temperature incubator shall be either a water bath or air cabinet of sufficient size to accommodate one or more vacuum desiccators, and shall be provided with a temperature regulator and heater to maintain a uniform temperature of $30.0 \pm 0.1^\circ\text{C}$.

A suitable incubator incorporating a water bath is illustrated in Figure 1. In this system, a steel block or similar mass of 2 kg to 3 kg will be required to weigh down the conditioning vessel. The steel block should be protected from corrosion by two coats of immiscible epoxy or plastic coating. The block may be placed in the bottom of the desiccator and covered with the potassium sulfate pulp.

A suitable air cabinet is illustrated in Figure 2. The air cabinet shall be of double-walled construction, with the cavity between the walls filled with insulation material. The required temperature can be attained by regulating two 100 W electric light bulbs mounted in parallel on the floor near the rear of the incubator. The sensor of the thermostat should be shielded from direct exposure to the heat sources. A small fan mounted in the incubator is used to ensure adequate circulation of air and to minimize temperature variations. An adequate seal shall be provided between the door and the incubator body.

The particular cabinet shown in Figure 2 has inner and outer walls constructed of 10 mm plywood, and has a wall cavity of 20 mm.

6.3 Balance—capable of weighing to an accuracy of ± 0.1 mg.

6.4 Drying tower—250 mL capacity, packed with magnesium perchlorate (5.3) for drying the air.