

Australian Standard™

Coal and coke—Analysis and testing

**Part 17: Higher rank coal—
Moisture-holding capacity
(equilibrium moisture)**



Standards Australia

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 29 September 2000 and published on 13 November 2000.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Preparation Society
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Coalfield Geology Council of N.S.W.
CSIRO, Energy Technology
Department of Mines and Energy, Qld
Electricity Supply Association of Australia
Institution of Engineers Australia
Minerals Council of Australia
University of Newcastle
University of New South Wales
University of Queensland

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

Coal and coke—Analysis and testing

**Part 17: Higher rank coal—
Moisture-holding capacity
(equilibrium moisture)**

Originated as AS 1038.17—1989.
Second edition 2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 3637 8

PREFACE

This Standard was prepared by the Standards Australia Committee MN/1, Coal and Coke, as a revision of AS 1038.17—1989, *Methods for the analysis and testing of coal and coke, Part 17: Determination of moisture-holding capacity (equilibrium moisture) of higher rank coal*.

Major differences from the previous edition are as follows:

- (a) Inclusion of a Foreword outlining the history of the development of the test method.
- (b) Inclusion of notes referring to difficulties in applying the Standard to coals containing significant quantities of free-swelling clays.

CONTENTS

	<i>Page</i>
FOREWORD	3
1 SCOPE	5
2 REFERENCED DOCUMENTS	5
3 PRINCIPLE	5
4 SAFETY	5
5 REAGENTS	5
6 APPARATUS	6
7 SAMPLE	8
8 PROCEDURE	9
9 CALCULATION	10
10 REPORTING OF RESULT	10
11 PRECISION	10
12 TEST REPORT	11

FOREWORD

The moisture-holding capacity, (MHC), or equilibrium moisture procedure, was originally developed as a means of estimating the ‘true’ bed moisture of coal and was later adopted by ASTM (1936)¹ for use in classifying Northern American coals by rank.

The history of the development of the test has been described by Rees et al (1939)² and Edwards (1968)³. These developments were as follows.

- (a) The first equilibration procedure devised by Stansfield and Gilbert (circa 1907) involved the exposure of crushed coal in shallow trays in a box, which also held trays containing a solution of calcium chloride of 1.3 S (50% relative humidity). The coal was weighed from time to time until a maximum weight was recorded. The method could be prolonged, in some cases up to 6 weeks, and was abandoned in 1910.
- (b) In a second method devised by Stansfield and Gilbert (circa 1923), crushed coal was equilibrated in a rapid stream of air at 60% relative humidity. By this method, practical equilibration was achieved within 48 hours. In 1931 the method was improved by inclusion of temperature control at 30°C. In the same year Stansfield and Gilbert developed a vacuum-desiccator procedure for equilibration at constant temperature over a range of selected relative humidity conditions. The moisture content of the equilibrated samples was determined by the usual method of drying at 105°C. Results were then extrapolated to 100% relative humidity; the so-called ‘true’ equilibration moisture.
- (c) Kreulen (circa 1951) modified the procedure by treating the coal with water, the surplus being removed by filtration before the sample was brought into equilibrium with the atmosphere of prescribed humidity.
- (d) Over subsequent years, the notion of true equilibrium moisture became disused and was subsequently replaced by ‘the equilibrium moisture-holding capacity in an atmosphere of 96% r.h. at 30°C’.

The current Australian Standard method is technically equivalent to BS 1016: Part 21/ISO 1018⁴ which were based primarily on the work of Edwards (1968)³. Test variables such as: samples preparation, size of dishes, test portion mass, equilibration time, dish lids on or off during equilibration, and the time interval for reintroducing the equilibrated samples to atmospheric pressure, were evaluated by Edwards at that time.

A comparison between the AS, BS/ISO and the ASTM D1412⁵ methods is given in the table below.

	AS 1038	BS 1016/ ISO 1018	ASTM D1412
Applicability	Higher rank coal	Hard coal	All coals
General	Reduced pressure equilibration	Atmospheric or reduced pressure equilibration	Reduced pressure equilibration
Coal topside	212 µm nominal topsize	212 µm nominal topsize	1.18 mm (16 mesh) nominal topsize
Sample pretreatment	20 g wetted coal is filtered then pressed between filter pads	20 g wetted coal is filtered then pressed between filter pads	20–25 g wetted coal is filtered only