

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 6.3.2: Higher rank coal and coke—  
Ultimate analysis—Total sulfur—High-  
temperature combustion method**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 5 August 2003 and published on 29 September 2003.

---

The following are represented on Committee MN-001:

Australian Institute of Mining and Metallurgy  
Australian Building Codes Board  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
Coalfield Geology Council of NSW  
CSIRO Energy Technology  
Department of Natural Resources and Mines, Qld  
Electricity Supply Association of Australia  
Institution of Engineers Australia  
Minerals Council of Australia  
University of New South Wales  
University of Newcastle  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia website at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 6.3.2: Higher rank coal and coke—  
Ultimate analysis—Total sulfur—High-  
temperature combustion method**

Originated as part of AS CK2.3—1949.  
Previous edition AS 1038.6.3.2—1997.  
Third edition 2003.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5483 X

## PREFACE

This Standard was prepared by the Standards Australia Subcommittee MN-001-01, Coal Evaluation under the supervision of Committee MN-001, Coal and Coke, as a revision of AS 1038.6.3.2—1997, to standardize specific technical aspects, (such as the concentration of mercury (II) oxycyanide), between this Standard and AS 1038.8.2, *Coal and coke—Analysis and testing*, Part 8.2: *Coal and coke—Chlorine—High-temperature combustion method* as both standard methods use similar chemical principles and reagents.

The objective of this Standard is to provide those responsible for the testing of coal and coke with a standardized procedure for the determination of the total sulfur content by high-temperature combustion and titration.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS.....	5
3 DEFINITIONS.....	5
4 PRINCIPLE.....	5
5 SAFETY.....	6
6 REAGENTS.....	6
7 APPARATUS.....	7
8 SAMPLE.....	8
9 PROCEDURE.....	8
10 CALCULATION.....	11
11 REPORTING OF RESULTS.....	11
12 PRECISION.....	11
13 TEST REPORT.....	11

## FOREWORD

The ultimate analysis of coal and coke comprises the determination of the elements carbon, hydrogen, nitrogen and sulfur. Determination of the total amounts of these elements, regardless of their origin, is described in the AS 1038.6 series. Carbon includes that which is present in the mineral carbonates and hydrogen includes that which is present both in the moisture (for which a correction is made in the calculation) and in water of constitution of the argillaceous constituents of the mineral matter. All nitrogen is assumed to be present in the carbonaceous substance. Sulfur is normally present in three forms: inorganic sulfides such as pyrite ( $\text{FeS}_2$ ), inorganic sulfates associated with the mineral matter and organic sulfur in the carbonaceous substance.

An estimate of the percentage of oxygen on an air-dry basis can be obtained by subtracting the sum of the determined percentages of moisture, ash, carbon, hydrogen, nitrogen and sulfur from 100. The value thus obtained should be termed 'oxygen by difference' (see AS 1038.16). A more satisfactory value for oxygen by difference is obtained when the ultimate analysis is expressed on a dry, mineral matter-free basis after making all appropriate corrections.

This Standard covers the determination of total sulfur, using the method of high temperature combustion followed by base-acid titration.

## STANDARDS AUSTRALIA

### Australian Standard

### Coal and coke—Analysis and testing

#### Part 6.3.2: Higher rank coal and coke—Ultimate analysis—Total sulfur—High-temperature combustion method

## 1 SCOPE

This Standard sets out a method for the determination of total sulfur in the analysis sample of higher rank coal and coke by the high-temperature combustion method.

## 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- |          |   |
|----------|---|
| 1038     | Coal and coke—Analysis and testing  |
| 1038.3   | Part 3: Proximate analysis of higher rank coal                            |
| 1038.4   | Part 4: Coke—Proximate analysis   |
| 1038.6.1 | Part 6.1: Higher rank coal and coke—Ultimate analysis—Carbon and hydrogen |
| 1038.8.2 | Part 8.2: Coal and coke—Chlorine—High-temperature combustion method       |
| 1038.16  | Part 16: Assessment and reporting of results                              |
| 2243     | Safety in laboratories (series)   |
| 2418     | Coal and coke—Glossary of terms   |
| 2508     | Safe storage and handling information cards (series)                      |
| 2706     | Numeric values—Rounding and interpretation of limiting values             |
| 4264     | Coal and coke—Sampling  |
| 4264.1   | Part 1: Higher rank coal—Sampling procedures                              |
| 4264.2   | Part 2: Coke—Sampling procedures  |

BS

- |      |  |
|------|--|
| 1752 | Laboratory sintered or fritted filters |
|------|--|

## 3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2418 and that below apply.

### 3.1 Repeatability ( $r$ )

The value at or below which the absolute difference between two single test results obtained with the same method on identical test material under the same conditions (same operator, same apparatus, same laboratory and the minimum practical time consistent with separate tests) may be expected to lie with the specified probability. In the absence of other specifications, the probability is 95%.

## 4 PRINCIPLE

A known mass of the sample is burnt in a stream of oxygen in a tube furnace at 1350°C. Aluminium oxide is added to modify the rate of combustion of the sample. The oxides of