

Australian Standard[®]

**Coal and coke—Analysis and
testing**

**Part 9.1: Coal and coke—
Phosphorus—Ash digestion/
molybdenum blue method**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 3 February 1992 and published on 15 June 1992.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Industry Research Laboratories
Australian Coal Preparation Society
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
CSIRO, Division of Coal and Energy Technology
Department of Resource Industries, Queensland
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
National Association of Testing Authorities, Australia
Queensland Coal Board
Royal Australian Chemical Institute
Standing Committee on Coalfield Geology of New South Wales
University of Newcastle
University of New South Wales
University of Queensland

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

Coal and coke—Analysis and testing

**Part 9.1: Coal and coke—
Phosphorus—Ash digestion/
molybdenum blue method**

First published as AS K152.9—1965 (endorsement of
BS 1016.9—1960 with amendment).
Revised and redesignated AS 1038.9—1977.
Revised and redesignated AS 1038.9.1—1992.

PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Coal Evaluation, under the supervision of the Committee on Coal and Coke, as a revision in part of AS 1038.9–1977, *Methods for the analysis and testing of coal and coke, Part 9: Phosphorus in coal and coke*. Major differences from the previous edition are as follows:

(a) Division of AS 1038.9 into the following individual parts:

- Part 9.1: Ash digestion/molybdenum blue method
- Part 9.2: Coal extraction method
- Part 9.3: Ash digestion method

Part 9.3 is a reproduction of the method currently contained in AS 1038.14.2, *Methods for the analysis and testing of coal and coke, Part 14.2: Analysis of higher rank coal ash and coke ash (acid digestion – Flame atomic absorption spectrometric method)*

(b) The addition of a pH adjustment prior to colour development in the dry oxidation procedure.

(c) Deletion of the wet oxidation procedure.

This Standard is not technically equivalent to ISO 622:1981, *Solid mineral fuels – Determination of phosphorus content – Reduced molybdophosphate photometric method*.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 PRINCIPLE	3
5 SAFETY	3
6 REAGENTS	3
7 APPARATUS	4
8 SAMPLE	4
9 PROCEDURE	4
10 CALCULATION OF RESULT	6
11 REPORTING OF RESULT	6
12 PRECISION	6
13 TEST REPORT	6

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified. The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Coal and coke – Analysis and testing

Part 9.1: Coal and coke – Phosphorus – Ash digestion/molybdenum blue method

1 SCOPE This Standard sets out a method for the spectrophotometric determination of phosphorus in coal and coke, as molybdenum blue.

This method is applicable also to the determination of phosphorus as phosphorus pentoxide in coal ash and coke ash.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

1038	Methods for the analysis and testing of coal and coke
1038.3	Part 3: Proximate analysis of higher rank coal
1038.4	Part 4: Proximate analysis of coke
1038.16	Part 16: Acceptance and reporting of results
2096	Classification and coding systems for Australian coals
2243	Safety in laboratories
2508	Safe storage and handling information cards for hazardous materials
2646	Sampling of solid mineral fuels
2646.6	Part 6: Hard coal – Preparation of samples
2646.7	Part 7: Coke – Preparation of samples
2706	Numerical values – Rounding and interpretation of limiting values
3753	Recommended practice for chemical analysis by ultraviolet/visible spectrophotometry

SAA

ASCRM-009 Certified reference coal sample

ASCRM-010 Certified reference coal ash sample

3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

3.1 Higher rank coal (as defined in AS 2096) coal having a gross specific energy of 21 MJ/kg or greater on an ash-free, moist basis *and* a gross specific energy of 27 MJ/kg or greater on a dry, ash-free basis.

3.2 Coke – the agglomerated product of coal carbonization, generally at a temperature in excess of 900°C.

3.3 Ash – the inorganic matter remaining after the coal or coke has been incinerated to constant mass under standard conditions.

4 PRINCIPLE The carbonaceous matter of the coal or coke is removed by ashing and the phosphorus extracted from the ash by treatment with sulfuric and hydrofluoric acid, silicon being volatilized as silicon tetrafluoride. The addition of a reagent solution, containing ammonium molybdate and ascorbic acid as a reducing agent, to a measured quantity of the extracted solution produces a molybdenum blue colouration, the absorbance of which is measured. The amount of phosphorus in the solution is obtained by reference to a standard solution.

Errors due to the presence of arsenic in the amounts normally found in coal ash or coke ash are insignificant.

5 SAFETY For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2506.

6 REAGENTS

6.1 General Unless otherwise specified, all reagents shall be of analytical reagent grade, and only distilled water, or water of equivalent purity, shall be used.

6.2 Solutions

6.2.1 Hydrofluoric acid, (ρ_{20} 1.15 g/mL), 40 percent m/m.

WARNING: HARMFUL TO SKIN AND EYES.

6.2.2 Sulfuric acid solution (5 mol/L) Add 28 mL of sulfuric acid (ρ_{20} 1.84 g/mL) to 50 mL of water. Cool, dilute to 100 mL and mix.