

Australian Standard[®]

Storage water heaters

Part 3: Specific requirements for water heaters with composite shells

[Title allocated by Defence Cataloguing Authority:
HEATER, WATER, ELECTRIC (Storage Type, Composite
Shell, NSC 4410, 4520)]

This Australian Standard was prepared by Committee EL/20, Electric Water Heating Appliances. It was approved on behalf of the Council of Standards Australia on 21 December 1990 and published on 28 March 1991.

The following interests are represented on Committee EL/20;

Australian Consumers Association
Australian Electrical and Electronic Manufacturers' Association
Australian Gas Association
Confederation of Australian Industry
Electricity Supply Association of Australia
Engineering and Water Supply Department, S.A.
Heat Exchange Water Heater Manufacturers Association
Metal Trades Industry Association of Australia

Additional interests participating in preparation of Standard:

Material suppliers

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications. This information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

Storage water heaters

Part 3: Specific requirements for water heaters with composite shells

First published as part of AS C316–1970.
AS C316–1970 revised and redesignated as
AS 1056–1972.
AS C316–1970 withdrawn 1974.
Second edition AS 1056–1977.
AS 1056–1977 revised and redesignated in part as
AS 1056.3–1985.
Second edition 1991.

PREFACE

This Standard was prepared by the Standards Australia Committee on Electric Water Heating Appliances to supersede the 1985 edition, to remove outdated references, to recognize changes to referenced Standards and to introduce a revised procedure for determining the solubility of vitreous enamel (see Appendix A, Paragraphs A2 and A7).

This Standard is one of a series covering storage water heaters, the other Standards in the series being as follows:

AS

1056 Storage water heaters

1056.1 Part 1: General requirements

1056.2 Part 2: Specific requirements for water heaters with single shells

1056.4 Part 4: Calculations of energy consumption

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 APPLICATION	3
3 REFERENCED DOCUMENTS	3
4 SHELLS WITH METALLIC INSERTS	3
5 BONDED VITREOUS ENAMELLED SHELLS	4
6 BONDED PLASTICS-LINED SHELLS	5
7 THERMOSTAT SETTINGS	7
8 DETERMINATION OF COMPLIANCE	8
APPENDICES	
A METHOD FOR THE DETERMINATION OF THE SOLUBILITY OF VITREOUS ENAMEL LINING	9
B METHOD FOR THE DETERMINATION OF THE RESISTANCE TO OXYGEN OF BONDED PLASTICS LININGS	11
C METHOD FOR THE DETERMINATION OF THE RESISTANCE TO THERMAL SHOCK OF BONDED PLASTICS LININGS	13
D METHOD FOR THE DETERMINATION OF THE RESISTANCE TO THERMAL CYCLING OF BONDED PLASTICS-LINED SHELLS	15

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

**Australian Standard
Storage water heaters**

Part 3: Specific requirements for water heaters with composite shells

1 SCOPE This Standard specifies requirements for water heaters with composite shells made from steel and protected as follows:

- (a) With a metallic insert.
- (b) With a bonded vitreous enamel lining.
- (c) With bonded plastics lining.

2 APPLICATION The requirements of this Standard are in addition to those in AS 1056.1.

3 REFERENCED DOCUMENTS The following Standards are referred to in this Standard:

AS

1056	Storage water heaters
1056.1	Part 1: General requirements
1449	Wrought alloy steels—Stainless and heat-resisting steel plate, sheet and strip
1566	Copper and copper alloys—Rolled flat products
1627	Metal finishing—Preparation and pretreatment of surfaces
1627.4	Part 4: Abrasive blast cleaning
1627.9	Part 9: Pictorial surface preparation standards for painting of steel surfaces
2812	Welding, brazing and cutting of metals—Glossary of terms

4 SHELLS WITH METALLIC INSERTS

4.1 Non-ferrous metallic insert

4.1.1 Material The insert shall be made from one of the following materials complying with AS 1566:

- (a) Silicon bronze alloy A, Designation AS 1566/655.
- (b) 90/10 copper-nickel, Designation AS 1566/705.
- (c) Phosphorus deoxidized copper, high residual phosphorus, Designation AS 1566/122.

NOTE: Other materials may be considered by the Standards Australia Committee EL/20 for possible inclusion in this Standard on production of satisfactory evidence of long-term suitability.

4.1.2 Thickness When checked at 20 representative points on the walls and ends, the insert shall have a thickness of not less than 0.50 mm.

4.1.3 Conformity with steel shell The insert shall be in intimate contact with the steel shell over virtually its entire surface.

4.2 Steel shell The shell shall be made from a grade of steel that will consistently ensure satisfactory jointing with the insert.

4.3 Jointing

4.3.1 Welding of the shell The welds shall be of a quality not inferior to that produced by the submerged-arc process. The longitudinal seam shall be butt welded.

Weld beads and edges against which the insert will bear shall be finished so that local stresses are not imposed upon the metallic insert.

4.3.2 Jointing of the insert Joints in the insert shall be either welded or brazed. The jointing shall be finished so that intimate contact with the steel is ensured.

4.4 Watertightness Where tested with water at the maximum working pressure, the insert shall not leak. Where a shell has openings for the expulsion of air from the interspace or for the detection of leaks, these openings shall be sealed at the conclusion of this test and while the shell is subjected to pressure.

To provide access to the interspace, shells intended for type testing shall be fitted with at least three sealable openings of 3 mm to 5 mm diameter (see Figure 1).