

1995 ED.
FWD 95020

94021

AS 1085.1—1990

1995 ED.

Australian Standard®

Railway permanent way material

Part 1: Steel rails



STANDARDS AUSTRALIA



This Australian Standard was prepared by Committee CE/2, Railway Permanent Way Materials. It was approved on behalf of the Council of Standards Australia on 23 July 1990 and published on 12 November 1990.

The following interests are represented on Committee CE/2:

Bureau of Steel Manufacturers of Australia

Railways of Australia Committee

Review of Australian Standards To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcome. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

AS 1085
Railway permanent way
material

AS 1085.1—1995 31pp GG
Steel rails
Specifies requirements for
rolled steel rails and profiles
for asymmetric switch rails and
elevated guardrails for railway
purposes.

(CE2): Supersedes AS 1085.1—80.
DR 94021: Publication date
1995-05-05.

Australian Standard®

Railway permanent way material

Part 1: Steel rails

First published as AS 1085.1—1977.
Second edition 1981.
Third edition 1990.

PREFACE

This Standard was prepared by the Standards Australia Committee on Railway Permanent Way Materials to supersede AS 1085.1—1981.

The principal changes in this edition are the deletion of requirements for 47 kg and 53 kg rails and the replacement of Appendix G on rounding of numbers by a reference to AS 2706, *Numerical values—Rounding and interpretation of limiting values*. This edition also incorporates a new Appendix E on Eddy Current Test.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS.

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DESIGNATION	4
4 CHEMICAL COMPOSITION	4
5 TREATMENT FOR HYDROGEN REMOVAL	4
6 CUTTING TO LENGTH	5
7 HOLES FOR FISHBOLTS	5
8 DIMENSIONS AND DIMENSIONAL TOLERANCES	6
9 TESTING AND COMPLIANCE	6
10 IDENTIFICATION	7
11 ROUNDING OF NUMBERS	7

APPENDICES

A RAIL PROFILES	9
B IMPACT TEST FOR ROLLED STEEL RAILS	14
C TENSILE TEST FOR ROLLED STEEL RAILS	15
D ULTRASONIC TEST FOR ROLLED STEEL RAILS	16
E EDDY CURRENT TEST FOR ROLLED STEEL RAILS	18
F ECCENTRICITY GAUGE	20
G DIFFUSION TREATMENT FOR HYDROGEN REMOVAL	21
H GUIDE TO PURCHASERS	22
I METHODS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	23

STANDARDS AUSTRALIA

Australian Standard

Railway permanent way material

Part 1: Steel rails

1 SCOPE The Standard specifies requirements for rolled steel rails for railway purposes.

NOTE: Guidelines to purchasers are given in Appendix H.

2 REFERENCED DOCUMENTS The documents below are referred to in this Standard.

AS

1050 Methods for the analysis of iron and steel

1100 Technical drawing

1100.201 Part 201: Mechanical drawing

1199 Sampling procedures and tables for inspection by attributes

1213 Iron and steel—Methods of sampling

1290 General requirements for linear measuring instruments for construction

1391 Methods for tensile testing of metals

1399 Guide to AS 1199—Sampling procedures and tables for inspection by attributes

1929 Non-destructive testing—Glossary of terms

2083 Calibration blocks and their methods of use in ultrasonic testing

2706 Numerical values—Rounding and interpretation of limiting values

3900 Quality systems—Guide to selection and use

3904 Quality systems—Guide to quality management and quality system elements

K1 Methods for the sampling and analysis of iron and steel

ISO General rules for ISO and IFC international third-party certification schemes for products
Guide 44

3 DESIGNATION The nominal rail size shall be designated by the nominal mass, in kilograms, of a 1 m length of rail.

The nominal rail sizes are 31, 41, 50 and 60 kg and they shall be referred to as 31 kg rail, 41 kg rail, 50 kg rail and 60 kg rail respectively.

4 CHEMICAL COMPOSITION

4.1 General The method of sampling for chemical analysis shall be in accordance with AS 1213. Chemical composition shall be determined by any procedures which are not less accurate than AS 1050 or AS K1.

4.2 Cast analysis A chemical analysis of the steel from each ladle shall be made to determine the proportion of the specified elements. Where it is impracticable to obtain samples from the liquid steel, analysis of test samples from solid metal taken in accordance with AS 1213 may be reported as cast analysis.

4.3 Composition The cast analysis of the steel (see Clause 4.2) shall conform to the limits given in Table 1 for the appropriate size of the rail.

5 TREATMENT FOR HYDROGEN REMOVAL All 50 kg and 60 kg rails shall be produced in such a manner as to limit the amount of hydrogen present by the time the hot-rolled rails are cooled.

NOTE: Methods that may be employed to remove hydrogen include—

(a) diffusion treatment of hot-rolled rails;

NOTE: A suitable method is described in Appendix G.

(b) diffusion treatment of blooms; and

(c) vacuum degassing of the molten steel.