

Australian Standard 1110-1980

ISO METRIC HEXAGON PRECISION BOLTS AND SCREWS

[Titles allocated by Defence Cataloguing Authority:

BOLT, MACHINE .. NSC 5306

SCREW, MACHINE (ISO Metric, Steel, Hexagon Head, Precision Products) .. NSC 5305]



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Institute of Steel Construction
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Electricity Supply Association of Australia
Fasteners Institute of Australia
Federal Chamber of Automotive Industries
Institution of Production Engineers
Metal Trades Industry Association of Australia
Petroleum Refinery Engineers Advisory Committee
Railways of Australia Committee
Telecom Australia
University of Sydney

This standard, prepared by Committee M-29, Fasteners, was approved on behalf of the Council of the Standards Association of Australia on 1 August 1980, and was published on 1 November 1980.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by monthly listings in the SAA journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 79188 ✓

ISO METRIC HEXAGON PRECISION BOLTS AND SCREWS

AS 1110-1980

First published	1972 ✓
Second edition	1980

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 2029 9



PREFACE

This standard was prepared by the Association's Committee on Fasteners to supersede the 1972 edition. The latter was intended to cover the anticipated needs of Australian industry under the metric system for metric hexagon bolts and screws. In the interests of international trade and international standardization, the standard at the time was fully aligned with the recommendations of the International Organization for Standardization (ISO), which had emanated from its technical committee TC2.

Since 1972 there have been several important changes introduced in the international standards, also the needs of Australian industry have become more crystallized, and hence a complete revision was necessary to take all factors into account. The changes in the ISO standards have been introduced after a great deal of technical study and research within ISO/TC 2, and were to a large degree initiated by the U.S.A. which, when the metric system was first seriously proposed for adoption in that country, developed a new metric fastener system (The Optimum Metric Fastener System). This system was forwarded to ISO as a U.S.A. proposal for a revision of the relevant ISO standards. In the original submission, a very large number of changes were proposed for both metric fasteners and metric screw threads. The ensuing discussions within ISO/TC 2 which took place over several years, were aimed at reducing the technical changes to existing ISO standards to a minimum consistent with achieving improved performance without significantly increasing product costs.

The most significant changes in ISO standards and in this standard from the user's point of view are in the across-flat hexagon sizes, the attention is drawn to Appendix F where this is fully detailed. A further change has been the upgrading of the tensile strength for property class 8.8 fasteners over M16 from 800 MPa to 830 MPa.

In AS 1110 — 1972, four property classes only were specified which it was felt would cover the needs of Australian industry at least during the transition to the metric (SI) system. More recently it has become apparent that other strength grades were becoming popular particularly in the automotive industry, and consequently a further two property classes, i.e. property classes 9.8 and 12.9, have been included in this edition.

This standard has been based on analysis in alignment with the following ISO standards, with the exception that the tolerance on overall length of js16 has been retained:

- ISO 898/1 Mechanical Properties of Fasteners
 - Part 1 — Bolts, Screws and Studs
- ISO 272 Fasteners — Hexagon Products — Widths Across Flats
- ISO/R 733 Hexagon Bolts and Nuts — Metric Series — Tolerances on Widths Across Flats, Widths Across Corners
- ISO 885 General Purpose Bolts and Screws — Metric Series — Radii Under the Head
- ISO 886 Bolts, Screws and Studs — Nominal Lengths and Thread Lengths for General Purpose Bolts
- ISO 4014 Hexagon Head Bolts — Product Grades A and B
- ISO 4017 Hexagon Head Screws — Product Grades A and B
- ISO 4759 Tolerances for Fasteners
 - Part 1 — Bolts, Screws and Nuts with Thread Diameters between 1.6 (inclusive) and 150 mm (inclusive) and Product Grades A, B and C.

This standard may require reference to the following Australian standards:

- AS 1112 ISO Metric Hexagon Nuts including Thin Nuts, Slotted Nuts and Castle Nuts
- AS 1214 Hot-dip Galvanized Coatings on Threaded Fasteners (ISO Metric Coarse Thread Series)
- AS 1236 Split Cotter Pins (Metric Series)
- AS 1275 Metric Screw Threads for Fasteners
- AS 1391 Methods for Tensile Testing of Metals
- AS 1544 Methods for Impact Tests on Metals
 - Part 3 — Charpy U-notch and Keyhole Notch

- AS 1654 Limits and Fits for Engineering
- AS 1721 General Purpose Metric Screw Threads
- AS 1815 Method for Rockwell Hardness Test
- AS 1816 Method for Brinell Hardness Test
- AS 1817 Method for Vickers Hardness Test
- AS 1897 Electroplated Coatings on Threaded Components (Metric Coarse Series)

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1980
Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	5
2 Definitions	5
3 Method of Manufacture	6
4 Shape, Dimensions and Finish	6
5 Materials and Mechanical Properties	10
6 Testing of Mechanical Properties of Hexagon Steel Bolts and Screws	14
7 Marking	18
APPENDICES	
A Non-preferred Sizes	20
B Basis for Derivation of Tolerances	21
C Shank and Head Dimensions for Hexagon Bolts and Screws over M	22
D Drilled Bolts and Screws for Split-pins	24
E Recommended Combinations of Bolts and Screws with Associated Nuts	25
F Notes on Hexagon Sizes of Metric Bolts and Screws	26
G A Suggested Sampling Plan for Mechanical Properties	27
H Complete Designation for the Purpose of an Enquiry or Order	28
FIGURES	
1 Concentricity, Symmetry and Squareness of Hexagon Bolts and Screws	7
2 ISO Metric Precision Hexagon Bolts and Screws	7
3 Proof Loading Test	15
4 Application of Proof Load	15
5 Wedge Loading Test	16
6 Wedge Loading of Full-size Bolt or Screw	16
7 Machined Test Piece	17
8 Zones of Decarburization	17
9 Hardness Measurements for Decarburization Test	18
10 Example of Marking of Metric Forged Product	18
11 Example of Marking of Bar Turned Product	18
TABLES	
1 Nominal Thread Lengths for Bolts	6
2 General Dimensions of ISO Metric Precision Bolts and Screws	8
3 Lengths of Hexagon Bolts	9
4 Lengths of Hexagon Screws	10
5 Mechanical Properties of Steel Bolts and Screws	11
6 Chemical Composition of Steel Bolts and Screws	12
7 Acceptance Tests for Full-size Bolts and Screws	13
8 Acceptance Tests for Machined Proportional Test Pieces	13
9 Tensile and Proof Loads for Steel Bolts and Screws	14
10 Dimensions for Wedge Loading Test	16
11 Values for h_s and h_d	18
12 Property Class Marking of Bolts and Screws	18

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
ISO METRIC HEXAGON PRECISION BOLTS AND SCREWS

1 SCOPE. This standard specifies requirements for precision hexagon bolts (with full sized shanks) and precision hexagon screws, with ISO metric coarse pitch series threads in diameters from 1.6 mm to 36 mm inclusive.

This standard is intended primarily to apply to steel bolts and screws used within the temperature range of -50°C to $+300^{\circ}\text{C}$, and does not make provision for products requiring special properties, such as weldability, or for corrosion-resistant materials.

The dimensional and marking requirements (except property class marking) of this standard also apply to non-ferrous and stainless steel fasteners.

NOTES:

1. The range of nominal sizes included in this standard is considered adequate for most of the applications for which this series is likely to be employed, but for the convenience of users requiring larger sizes, further information in relation to the derivation of tolerances and head dimensions is provided in Appendix B and Appendix C respectively. Nuts for use with bolts to this standard are given in AS 1112. For information on recommended property classes of nuts to be associated with each property class of precision hexagon bolts and screws, see Appendix E.
2. Bolts and screws manufactured of free-cutting steel to property class 4.6 (see Clause 5.1) should not be used at a temperature in excess of $+250^{\circ}\text{C}$.
3. Hexagon bolts and screws given in this standard are in complete agreement with those given in international standards, for product Grades A and B, except for the tolerance on bolt length which is unchanged from the previous edition of this standard.
The hexagon sizes for M10, M12, M14 and M20 have also been changed from those given in the previous edition, reflecting changes introduced in ISO 272. Further information on this aspect is given in Appendix F.
4. Inclusion of the property class given in this standard does not necessarily imply that such types are stock items. The purchaser should refer to the manufacturer's listings for stock availability.
5. If bolts with other than coarse pitch series threads are required, these are subject to agreement between the manufacturer and the purchaser, and the thread series should be selected from AS 1721.

2 DEFINITIONS. For the purpose of this standard, the following definitions apply:

2.1 Precision bolts and screws — products made to relatively close tolerances on all dimensions and having surfaces finished to provide a general high grade appearance.

2.2 Transition diameter (D_t) — the diameter of a groove formed at the transition between the fillet radius r and the bearing surface of the head.

2.3 Concentricity tolerance — of a bolt, is the allowable deviation of the shank with respect to the screw thread (see Fig. 1).

2.4 Symmetry tolerance — of a bolt or screw, is

the allowable deviation of the across-flats dimension with respect to the shank or the major diameter of a screw (see Fig. 1).

2.5 Nominal length (l) — of a bolt or screw is the distance from the bearing surface of the head to the extreme end of the shank including any chamfer or radius (see Fig. 2).

2.6 Thread length (b) — of a bolt, is the difference between the nominal length of the bolt and the distance between the bearing surface of the head and the nearest face of a nut with no internal chamfer, screwed as far as practicable on to the bolt by hand.

2.7 Length of unthreaded shank (l_1) — of a bolt, is the distance from the bearing surface of the bolt head to the last scratch of thread, or top of the extrusion angle, whichever is closer to the head.

2.8 Grip length (g) — of a bolt, is the minimum thickness of materials which can be clamped, but excluding the washer thickness.

2.9 Thread runout.

2.9.1 Bolts and screws with rolled threads — the distance from the top of the extrusion cone to the nearest face of a nut with no internal chamfer, screwed on to the bolt as far as practicable by hand.

2.9.2 Bolts and screws with cut threads — the distance from the last witness of thread to the nearest face of a nut with no internal chamfer, screwed on to the bolt as far as practicable by hand.

2.10 Carburization and decarburization.

2.10.1 Base metal hardness — the hardness closest to the surface (when traversing from core to outside diameter) just before an increase or decrease occurs denoting carburization or decarburization.

2.10.2 Decarburization — generally, the loss of carbon at the surface of commercial ferrous materials (steels).

2.10.3 Partial decarburization — decarburization with loss of carbon sufficient to cause a lighter shade of tempered martensite and significantly lower hardness than that of the adjacent base metal.

2.10.4 Complete decarburization — decarburization with sufficient carbon loss to show only clearly defined ferrite grains under metallographic examination.

2.10.5 Carbon restoration — a process of restoring carbon loss by heat treating in a furnace atmosphere of properly controlled carbon potential.

2.10.6 Carburization — a process of increasing surface carbon to a content above that of the base metal.