

Australian Standard[®]

**Steel conductors and stays—
Bare overhead**

Part 2: Aluminium clad (SC/AC)

This Australian Standard was prepared by Committee EL/10, Overhead Lines. It was approved on behalf of the Council of Standards Australia on 21 July 1992 and published on 12 October 1992.

The following interests are represented on Committee EL/10:

Australian Electrical and Electronic Manufacturers Association
Australian Porcelain Insulators Association
Confederation of Australian Industry
Electricity Supply Association of Australia
Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvement of Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 91133.

Australian Standard[®]

**Steel conductors and stays—
Bare overhead**

Part 2: Aluminium clad (SC/AC)

First published as AS 1222.2 — 1973.
Second edition 1992.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 7727 4

PREFACE

This Standard was prepared by the Standards Australia Committee on Overhead Lines to supersede AS 1222.2—1973, *Steel conductors and stays for overhead power transmission purposes*, Part 2: *Aluminium clad (SC/AC)*, and it is the second part of a two-part series, viz.

AS 1222—*Steel conductors and stays—Bare overhead*

Part 1: *Galvanized (SC/GZ)*

Part 2: *Aluminium clad (SC/AC)*

The Standard conforms generally with various International Electrotechnical Commission (IEC) publications on overhead conductors and with IEC draft, document 7 (Central Office) 434.

In determining conductor sizes, a range of wire sizes has been provided similar to that for conductors specified in the 1973 edition. Conductors with other dimensions can also be supplied by reference to this Standard.

Wire sizes have not been changed from the previous edition but major modifications have been made in the following areas:

- (a) The provisions allowing joining of finished wires has been eliminated.
- (b) The sampling rate of specimens for routine tests relies on a quality assurance plan.
- (c) A new Appendix B covers the coefficient of linear expansion and the theoretical basis for the calculation of modulus of elasticity.
- (d) A new Appendix C has been included which highlights items to be specified by the purchaser or agreed between purchaser and manufacturer at the time of order.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 DEFINITIONS	4
1.4 NOMENCLATURE	5
SECTION 2 MATERIAL REQUIREMENTS AND WIRE PROPERTIES	
2.1 GENERAL	6
2.2 MATERIALS	6
2.3 WIRE PROPERTIES	6
SECTION 3 CONDUCTOR REQUIREMENTS	
3.1 GENERAL	8
3.2 JOINTS IN FINISHED WIRES	8
3.3 LAY	8
3.4 STANDARD SIZES AND CALCULATED PROPERTIES OF CONDUCTORS	8
SECTION 4 TESTS	
4.1 SELECTION OF TEST SPECIMENS	10
4.2 MECHANICAL TESTS	10
4.3 COATING THICKNESS TEST	11
4.4 RESISTIVITY TEST	11
4.5 LAY RATIO	11
4.6 PLACE OF TESTING	11
SECTION 5 PACKING AND MARKING	
5.1 PACKING	12
5.2 MARKING	12
5.3 COIL MARKING	12
5.4 CERTIFICATE OF COMPLIANCE	12
APPENDICES	
A CALCULATION OF CONDUCTOR PROPERTIES	13
B COEFFICIENT OF LINEAR EXPANSION AND CALCULATION OF MODULUS OF ELASTICITY	14
C PURCHASING GUIDELINES	15

STANDARDS AUSTRALIA

Australian Standard
Steel conductors and stays — Bare overhead

Part 2: Aluminium clad (SC/AC)

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard specifies requirements and tests for bare electrical conductors for overhead power transmission purposes, constructed from aluminium-clad steel wires, having a minimum aluminium radial thickness of 5% of the nominal diameter of the wire. This corresponds to IEC class '20SA' type A of aluminium-clad steel wires.

For the purpose of this Standard, the term 'conductor' includes 'stays'.

NOTES:

- 1 Appendix A gives methods to calculate conductor properties.
- 2 Appendix B gives the coefficient of linear expansion and the theoretical basis for the calculation of modulus of elasticity.
- 3 Appendix C lists information which should be supplied with enquiries and orders for conductors.

1.2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- | | |
|--------|---|
| 1057 | Quality assurance and quality control — Glossary of terms |
| 1391 | Methods of tensile testing of metals |
| 1442 | Carbon steels and carbon-manganese steels — Hot-rolled and semi-finished products |
| 2505 | Methods for bend and related testing of metals |
| 2505.5 | Part 5: Torsion and wrapping tests on wire |
| 2848 | Aluminium and aluminium alloys — Compositions and designations |
| 2848.1 | Part 1: Wrought products |
| 2857 | Timber drums for insulated electric cables and bare conductors |
| 3983 | Metal drums for insulated electric cables and bare conductors |

IEC

- | | |
|-----|---|
| 468 | Methods of measurement of resistivity of metallic materials |
|-----|---|

ASTM

- | | |
|------|--|
| D566 | Test method for dropping point of lubricating grease |
|------|--|

1.3 DEFINITIONS For the purpose of this Standard, the definitions given in AS 1057 and those below apply.

1.3.1 Wire—a filament of drawn metal having a constant circular cross section.

1.3.2 King wire—a central wire of a conductor having a nominal diameter larger than that of the surrounding wires.

1.3.3 Conductor—a finished circular stranded assembly consisting of three or more wires laid up together.

1.3.4 Diameter—the mean of two measurements at right angles taken at any one cross-section.

1.3.5 Direction of lay—the direction of lay is defined as right-hand or left-hand, as follows:

- (a) Right-hand lay—when the slope of the wires is in the direction of the central part of the letter Z when the conductor is held vertically.
- (b) Left-hand lay—when the slope of the wires is in the direction of the central part of the letter S when the conductor is held vertically.

1.3.6 Lay length—the axial length of one complete turn of the helix formed by an individual wire in a stranded conductor.

1.3.7 Lay ratio—the ratio of the lay length to the nominal external diameter of the corresponding layer of wires in the stranded conductor.

1.3.8 Breaking load of a wire—the maximum load obtained in a tensile test of wire.

1.3.9 Ultimate tensile stress—the breaking load divided by the original cross-sectional area of the test wire.