



Methods of test for pulp and paper

Method 437: Tensile strength of wetted paper and paperboard (ISO 3781:2011, MOD)

STANDARDS
Australia



AS 1301.437:2019

This Australian Standard ® was prepared by PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 6 March 2019.

This Standard was published on 22 May 2019.

The following are represented on Committee PK-019:

Appita
Australian Institute of Packaging
Monash University

This Standard was issued in draft form for comment as DR AS 1301.437:2019.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76072 460 3



Methods of test for pulp and paper

Method 437: Tensile strength of wetted paper and paperboard (ISO 3781:2011, MOD)

Originates as AS 1301.437rp—1970.
Previous edition AS 1301.437s—1989.
Jointly revised and designated as AS/NZS 1301.437s:2007.
Revised and redesignated as AS 1301.437:2019.

COPYRIGHT

© ISO 2019 — All rights reserved
© Standards Australia Limited 2019

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard was prepared by the Australian members of Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper, to supersede AS/NZS 1301.437s:2007 *Methods of test for pulp and paper, Method 437s: Tensile strength of wetted paper and paperboard*.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this Standard is to specify a test method for the determination of the wet tensile strength of paper or board after its immersion in water for a specified period.

This Standard is an adoption with national modifications, and has been reproduced from, ISO 3781:2011, *Paper and board — Determination of tensile strength after immersion in water*. The modifications are additional requirements and are set out in [Appendix ZZ](#), which has been added at the end of the source text.

[Appendix ZZ](#) lists the variations to ISO 3781:2011 for the application of this Standard in Australia.

As this document has been reproduced from an International Standard, the following applies:

- (a) In the source text “this International Standard” should read “this Australian Standard”.
- (b) A full point substitutes for a comma when referring to a decimal number.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Sampling	2
7 Conditioning	2
8 Preparation of test pieces	2
9 Procedure	3
10 Calculation and expression of results	3
10.1 General	3
10.2 Wet tensile strength	3
10.3 Wet tensile strength retention	3
11 Test report	4
Annex A (informative) Precision data	5
Bibliography	6
Appendix ZZ (normative) Variations to ISO 3701:2011 for Australia	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3781 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This third edition cancels and replaces the second edition (ISO 3781:1983), of which it constitutes a minor revision. It is no longer applicable to tissue paper or tissue products, which are covered by ISO 12625-5. In addition, precision data have been added.

Australian Standard[®]

Methods of test for pulp and paper

Method 437: Tensile strength of wetted paper and paperboard (ISO 3781:2011, MOD)

1 Scope

This International Standard specifies a test method for the determination of the wet tensile strength of paper or board after its immersion in water for a specified period.

In principle, the method is applicable to both paper and board, provided an appropriate soaking time is agreed between the interested parties.

This International Standard is not applicable to tissue paper and tissue products or other lightweight, highly absorbent paper which is difficult to handle or of low strength when wet (see ISO 12625-5^[1]).

NOTE The tensile strength testing is performed using an apparatus operating at a constant rate of elongation of 20 mm/min, as per ISO 1924-2, or 100 mm/min, as per ISO 1924-3. Therefore, depending on which method is chosen, only one or the other of those International Standards is needed for performing the test.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 1924-2, *Paper and board — Determination of tensile properties — Part 2: Constant rate of elongation method (20 mm/min)*

ISO 1924-3, *Paper and board — Determination of tensile properties — Part 3: Constant rate of elongation method (100 mm/min)*

ISO 14487, *Pulps — Standard water for physical testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

wet tensile strength

maximum tensile force per unit width that a test piece soaked with water will withstand before breaking in a tensile test

[SOURCE: ISO 12625-5:2005, definition 3.1]

Note 1 to entry: It is expressed in kilonewtons per metre.