

Australian Standard[®]

Tinplate and blackplate

This Australian Standard was prepared by Committee MT/1, Iron and Steel. It was approved on behalf of the Council of Standards Australia on 21 September 1990 and published on 11 February 1991.

The following interests are represented on Committee MT/1:

Australian Foundry Institute
Australian Institute of Steel Construction
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Metal Trades Industry Association of Australia
Railways of Australia Committee
Society of Automotive Engineers, Australasia

Additional interests participating in preparation of Standard:

Australian Tin Information Centre
Canmakers Institute of Australia
CSIRO, Division of Food Research

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 88162.

Australian Standard[®]

Tinplate and blackplate

First published in part as AS 1517.1—1973.
Second edition 1982.
AS 1517.2 first published 1973.
Second edition 1982.
AS 1517.1—1982 and AS 1517.2—1982 revised.
amalgamated and redesignated AS 1517—1991.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 6577 2

PREFACE

This Standard was prepared by the Standards Australia Committee on Iron and Steel to supersede AS 1517—1982, *Tinplate and blackplate*, Part 1: *Sheet*, and Part 2: *Coil*. In this edition, the former Parts 1 and 2 have been combined to form one document.

This edition includes requirements for double cold-reduced blackplate, double cold-reduced electrolytic tinplate and low tin-coated steel, commonly referred to as LTS. Requirements for double cold-reduced electrolytic tinplate are the same as those specified in ISO 4977—1984, *Double cold-reduced electrolytic tinplate*, Part 1: *Sheet*, issued by the International Organization for Standardization.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 DEFINITIONS	4
1.4 DESIGNATION	6
1.5 MARKING	7
1.6 PACKAGING	8
1.7 ROUNDING OF TEST RESULT NUMBERS	8
SECTION 2 THE STEEL BASE	
2.1 SCOPE OF SECTION	9
2.2 CHEMICAL COMPOSITION	9
2.3 JOINTS (COIL ONLY)	10
2.4 SELECTION OF TEST SPECIMENS	10
2.5 MECHANICAL PROPERTIES	10
2.6 DIMENSIONS	11
SECTION 3 THE TIN COATING	
3.1 SCOPE OF SECTION	15
3.2 PURITY OF TIN COATING	15
3.3 TIN COATING MASS	15
APPENDICES	
A PURCHASING GUIDELINES	16
B MEANS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD ...	17
C CONVERSION OF ROCKWELL HR 15 T HARDNESS VALUES TO ROCKWELL HR 30 T VALUES	18
D SUPPLEMENTARY INFORMATION TO APPENDIX A	19
E METHOD FOR DETERMINING TIN COATING MASS (IODINE METHOD) ...	20

STANDARDS AUSTRALIA

Australian Standard
Tinplate and blackplate

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard specifies requirements for standard grade cold-reduced electrolytic tinplate and cold-reduced blackplate, either in sheet form or in wide coil and slit coil form, as follows:

- (a) Single cold-reduced material with nominal thickness from 0.20 mm up to and including 0.60 mm.
- (b) Double cold-reduced material with nominal thickness from 0.14 mm up to and including 0.29 mm.

It includes requirements for equally-coated, differentially-coated and low tin-coated (LTC) tinplate. This Standard does not apply to material described commercially as tinned sheets, steel sheets or TFS (electrolytic chromium-coated steel).

NOTES:

- 1 Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in the purchasing guidelines set out in Appendix A.
- 2 Alternative means for determining compliance with this Standard are given in Appendix B.

1.2 REFERENCED DOCUMENTS The documents below are referred to in this Standard:

AS	
1050	Methods for the analysis of iron and steel
1199	Sampling procedures and tables for inspection by attributes
1213	Iron and steel—Methods of sampling
1391	Methods for tensile testing of metals
1399	Guide to AS 1199—Sampling procedures and tables for inspection by attributes
2025	Method for Rockwell superficial hardness test
2025.1	Part 1: Testing of metals, N and T scales
2706	Numerical values—Rounding and interpretation of limiting values
3900	Quality systems—Guide to selection and use
3904	Quality systems—Guide to quality management and quality system elements
K1	Methods for the sampling and analysis of iron and steel
ISO	
Guide 44	General rules for ISO or IEC international third-party certification scheme for products.

1.3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

1.3.1 Area—area of tinplate or blackplate, expressed in SITA (System International Tinplate Area) units, where—

$$1 \text{ SITA} = 100 \text{ m}^2.$$

1.3.2 Batch—a quantity of some commodity produced under conditions which are considered uniform.

NOTE: Each batch is assumed, as far as practicable, to consist of materials or items of a single type, grade, class, size and composition, and to have been manufactured under essentially the same conditions at essentially the same time.

1.3.3 Batch annealing—annealing of cold-reduced strip in tight coil form, within a protective atmosphere.

1.3.4 Blackplate—low carbon steel sheet or coil normally not oiled or otherwise treated. Thicknesses range from 0.14 mm up to and including 0.60 mm.

NOTE: Steel sheet intended for blackplate is line inspected during processing, and material having visible imperfections of only moderate magnitude or frequency is selected. Blackplate is liable to rust but, at the time it is made available by the manufacturer, has a surface condition suitable for normal lacquering and printing.