

Australian Standard[®]

Methods for fire tests on building materials, components and structures

Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release

This Australian Standard was prepared by Committee BD/18, Fire Tests—Building Materials, Components and Structures. It was approved on behalf of the Council of Standards Australia on 7 July 1989 and published on 13 November 1989.

The following interests are represented on Committee BD/18:

Australian British Chamber of Commerce
Australian Fire Protection Association
Australian Institute of Building
Australian Uniform Building Regulations Coordinating Council
Board of Fire Commissioner, New South Wales
Bureau of Steel Manufacturers of Australia
Cement and Concrete Association of Australia
Commonwealth Fire Board
Confederation of Australian Industry
CSIRO Division of Building, Construction and Engineering
Fire Protection Industry Association of Australia
Forestry Commission of N.S.W.
Metropolitan Fire Brigades Board, Melbourne
Plastics Institute of Australia
Royal Australian Institute of Architects

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

Methods for fire tests on building materials, components and structures

Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release

First published as part of AS A30—1958.
Revised and redesignated AS A30 Part III—1970.
Revised and redesignated AS 1530.3—1976.
Second edition 1982.
Third edition 1989.
Incorporating:
Amdt 1—1992

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5867 9

PREFACE

This edition of this Standard was prepared by the Standards Australia Committee on Fire Tests on building Materials, Components and Structures to supersede AS 1530.3—1982, *Methods for fire tests on building materials, components and structures, Part 3: Test for early fire hazard properties of materials*. The title has been changed to more accurately indicate the fire characteristics to be assessed. The basic method of test has not been changed. In the opinion of the committee, this edition of the Standard will not cause variations from results obtained when materials were subjected to testing in accordance with AS 1530.3—1982. Changes incorporated in this edition clarify the requirements for the equipment used in the smoke monitoring system, require the reporting of test results as well as indices and provide a more complete list of referenced documents.

The Standard regime of increased radiant heat applied to the test specimens in this test method was originally defined following studies made at the Experimental Building Station of the heat energy impressed on the walls of a test room when various small fires were deliberately kindled. This test provides data for assessing the potential hazard of wall lining during the early growth of fire in a compartment. It also provides a discriminating assessment of fire behaviour of different materials.

Fire is a complex phenomenon and the fire hazard of a building material is a function of the characteristics of the material, how it is installed and used, and the environment in which it is present. No single test method can give a full assessment of fire hazard under all conditions of fire that may apply. There must therefore be a constant awareness of the above variables in using the results from this test to assess the fire hazard of any particular material or component under other fire exposures or used in applications other than walls.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced or stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 PRINCIPLE	4
1.4 APPLICATION TO THE ASSESSMENT OF FIRE HAZARD	4
SECTION 2. TEST PROCEDURE	
2.1 APPLICATION	5
2.2 SPECIMENS	5
2.3 TEST APPARATUS	5
2.4 CALIBRATION	6
2.5 TEST PROCEDURE	6
2.6 COMPUTATIONS FOR INDIVIDUAL SPECIMENS	7
2.7 COMPUTATION OF MEAN VALUES AND STANDARD ERRORS	7
2.8 REQUIREMENTS FOR SUPPLEMENTARY TESTING	7
SECTION 3. COMPUTATION OF INDICES AND CLASSIFICATIONS FOR REGULATORY PURPOSES	
3.1 INDICES	10
3.2 CLASSIFICATION FOR IGNITABILITY	10
3.3 CLASSIFICATION FOR SPREAD OF FLAME	10
3.4 CLASSIFICATION FOR HEAT EVOLVED	10
3.5 CLASSIFICATION FOR SMOKE DEVELOPED	10
SECTION 4. REPORTING OF RESULTS	
4.1 DESCRIPTION	11
4.2 RESULTS	11
4.3 SUPPLEMENTARY OBSERVATIONS	11
4.4 INDICES FOR REGULATORY PURPOSES	11
4.5 APPLICATION TO FIRE HAZARD ASSESSMENT	11
4.6 REFERENCE IN OTHER AUSTRALIAN STANDARDS	11
4.7 COMMERCIAL LITERATURE	11
APPENDIX A. GUIDE TO THE INTERPRETATION OF RESULTS	12

STANDARDS AUSTRALIA

Australian Standard

Methods for fire tests on building materials, components and structures

Part 3: Simultaneous determination of ignitability, flame propagation,
heat release and smoke release

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This Standard sets out a test method for the assessment of building materials and components according to—

- (a) their tendencies to ignite;
- (b) their tendencies to propagate flame;
- (c) the heat they release once ignition has occurred; and
- (d) their tendencies to release smoke.

NOTE: A guide to the interpretation of the results of this test, together with a full list of references, is given in Appendix A.

1.2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS

- | | |
|---------|--|
| 1530 | Methods for fire tests on building materials, components and structures |
| 1530.2 | Part 2: Test for flammability of materials |
| 2111 | Methods of test for textile floor coverings |
| 2111.18 | Part 18: Method for the determination of fire propagation properties—Fire propagation of the use-surface using a small ignition source |

1.3 PRINCIPLE. The specimen is held in a vertical configuration in a plane parallel to a radiant heater and the specimen moved towards the heater in steps over a period of 20 min or until ignition, induced by a pilot flame, occurs.

1.4 APPLICATION TO THE ASSESSMENT OF FIRE HAZARD. The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

These results provide information on ignitability, flame propagation, heat release and smoke release that has been related to performance of wall linings in simulated fires in the corner of a compartment. A consumer or Regulatory Authority should consider the relevance of this information to the fire hazard represented by the intended application of the material or component. The performance in the test applies to the thickness of the specimen in a flat panel shape. The results may not be valid for other shapes or assemblies unless verified by further tests.

The results may also provide a comparison of the fire behaviour of different materials and components. The application of the information obtained from the test to the fire hazard requires consideration of the form and fixing of the specimen as tested and the intended building use of the material or component.

The standard regime of increasing impinged radiant heat applied to the specimens in this test method was originally defined following studies of experimental room fires. The increasing intensity of radiant heat simulates that which could be experienced during the early development of a building fire. Early work was carried out by J.E. Ferris at the Commonwealth Experimental Building Station in Sydney in 1955.

NOTES:

1. Ignition is initiated by a pilot flame that is held near, but does not touch, the specimen. A material which does not ignite during the standard test may ignite if contacted with a pilot flame during the test.
2. The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2 mm that are sufficiently flexible to be bent by hand around a mandrel of 2 mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.
3. Since the heat source for the abovementioned test is a radiator, a reduction in the reflective properties of certain materials by the deposition of dust and soot, by surface damage and by the formation of the surface corrosion products, may produce a significant change in the results from those obtained when the materials were tested in a new and a clean condition.
4. Some materials are subjected to cleaning treatments throughout their useful life. Some treatments could adversely affect the fire hazard indices by, for example, removal or redistribution of fire-retarding agents. It is advisable that testing also be performed after a number of treatments in accordance with commercial cleaning practice.
5. Building regulations in Australia generally require that the core of sandwich-panel-type products be tested separately.