

Australian Standard[®]

**Fine grained, weldable steel plates for
pressure equipment**

STANDARDS
Australia



This Australian Standard® was prepared by Committee ME-001, Pressure Equipment. It was approved on behalf of the Council of Standards Australia on 31 March 2008. This Standard was published on 5 May 2008.

The following are represented on Committee ME-001:

- ACT Workcover
- Australasian Institute of Engineer Surveyors
- Australian Aluminium Council
- Australian Building Codes Board
- Australian Chamber of Commerce and Industry
- Australian Industry Group
- Australian Institute for the Certification of Inspection Personnel
- Australian Institute of Energy
- Australian Institute of Petroleum
- Bureau of Steel Manufacturers of Australia
- Department of Consumer and Employment Protection, WorkSafe Division, WA
- Department of Industrial Relations (Queensland)
- Department of Justice, Workplace Standards Tasmania
- Department of the Premier and Cabinet, Safework SA
- Energy Networks Association
- Engineers Australia
- Insurance Council of Australia
- LPG Australia
- Materials Australia
- National Association of Testing Authorities
- Pressure Equipment Association
- Victorian WorkCover Authority
- Welding Technology Institute of Australia
- WorkCover NSW

This Standard was issued in draft form for comment as DR 07147.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting www.standards.org.au

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Fine grained, weldable steel plates for
pressure equipment**

Originally as part of AS E6—1925.
Previous edition AS 1548—1995.
Fifth edition 2008.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 8639 1

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee ME-001, Pressure Equipment and supersedes AS 1548—1995, *Steel plates for pressure equipment*.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

For a summary of the major changes introduced in this edition of the Standard, refer to the Foreword.

The objective of this Standard is to specify requirements for hot-rolled fully killed carbon-manganese steel plates to a maximum thickness of 150 mm for use in the construction of pressure equipment.

Statements expressed in mandatory terms in notes to tables and figures are deemed to be requirements of this Standard.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

| | <i>Page</i> |
|--|-------------|
| FOREWORD..... | 4 |
| 1 SCOPE..... | 5 |
| 2 APPLICATION | 5 |
| 3 REFERENCED DOCUMENTS..... | 5 |
| 4 DEFINITIONS..... | 6 |
| 5 DESIGNATION..... | 7 |
| 6 DELIVERY CONDITION | 8 |
| 7 CHEMICAL COMPOSITION | 9 |
| 8 STEELMAKING PROCESS | 10 |
| 9 MANUFACTURING TOLERANCES..... | 11 |
| 10 FREEDOM FROM DEFECTS..... | 11 |
| 11 FREQUENCY OF SAMPLING | 12 |
| 12 SELECTION OF TEST SAMPLES | 12 |
| 13 POSITION OF TEST SPECIMEN..... | 13 |
| 14 ORIENTATION OF TEST PIECES | 13 |
| 15 PREPARATION OF TEST PIECES FOR MECHANICAL TESTING | 13 |
| 16 STRESS-RELIEVING TREATMENT..... | 14 |
| 17 TESTING PROCEDURES | 15 |
| 18 MECHANICAL TEST REQUIREMENTS..... | 16 |
| 19 RETESTS | 17 |
| 20 IDENTIFICATION..... | 18 |
| 21 TEST CERTIFICATE..... | 19 |
| 22 INTERPRETATION OF SPECIFIED LIMITING VALUES..... | 19 |
| APPENDICES | |
| A PURCHASING GUIDELINES..... | 22 |
| B EQUIVALENCE OF CURRENT AND PREVIOUS GRADES | 24 |
| C INFLUENCE OF FABRICATION AND HEAT TREATMENT ON MECHANICAL PROPERTIES..... | 26 |
| D INTERCHANGEABILITY OF STRENGTH GRADES..... | 28 |
| E CREEP RUPTURE PROPERTIES | 29 |

FOREWORD

The following is a summary of the changes from AS 1548—1995:

- (a) The '5' and '7' designations have been replaced by 'PT', which partially aligns with the ISO and EN designations. 'P' is for pressure equipment and 'T' is for tensile strength designation as opposed to the yield strength designation used by the ISO and EN Standards. Essentially, the property requirements have not changed from the previous edition.
- (b) The 'R' and 'A' designations have been combined into a new normalized rolled 'NR' designation. This aligns the former 'R' and 'A' interchangeability clause with ISO and EN. The definition of normalized rolling aligns with EN 10028 except that the EN Standard allows it be designated as an 'N' grade. It was thought that this would create confusion in the Australian industry and hence the 'NR' designation was formed.

The designation 'NRA' has been added to allow for the ordering of NR grades with simulated normalized test results.

- (c) All grades are to be Charpy tested to exhibit some level of toughness, in line with the ISO and EN Standards. The former 'base' grades were expected to meet a certain toughness level in the pressure vessel design Standard AS 1210, based upon the performance of BlueScope Steel's grades but without any explicit requirements in AS 1548.
- (d) The Charpy energy values have been changed to align with those expected in AS 1210, and with those in the ISO and EN standards.
- (e) With the removal of the '5' and '7' designations, it was decided to retain the strength requirements of the former 5-490 grade but allow NR and T to be supplied in addition to the original N. This is in line with the ISO and EN Standards.
- (f) The elevated temperature tensile test values (in Table 5) have been changed to align with the ISO and EN Standards. They now represent a lower 2 standard deviation yield stress value and are not a pass/fail criteria, but are more like design values. In case of disputes, the minimum acceptable elevated temperature yield strength is set at 5% below the tabulated values. The expected removal of the safety factor penalty for non-tested elevated temperature grades from AS 1210 and AS 1228 may reduce the need for the L_g grade, but it is retained for purchasers who want a test result.

Elevated temperature tensile strength (R_{mT}) values have not been listed.

- (g) A new grade PT540T has been included, up to 40 mm thickness, which takes advantage of the strength levels that can be achieved from thermomechanical controlled rolling. Creep rupture properties for this grade have not been included, as data is not yet available.
- (h) A definition of fine grained steels has been included.
- (i) Guidance on the effect of excessive stress relieving has been added.
- (j) Changes to Appendices C, D and E have been made to accommodate the new designations.
- (k) References to continuous mill product have been removed from the standard.
- (l) C and CE limits are tighter but well within the capacity of the standard grades.
- (m) For grades L20 and below, the allowable Niobium level has increased from 0.025% to 0.030%.

STANDARDS AUSTRALIA

Australian Standard

Fine grained, weldable steel plates for pressure equipment

1 SCOPE

This Standard specifies requirements for hot-rolled, fine grained, fully killed carbon-manganese steel plates to a maximum thickness of 150 mm for use in the construction of pressure equipment.

NOTE: Guidelines to purchasers on requirements that should be specified by the purchaser and those that should be agreed to at the time of enquiry or order, or both, are given in Appendix A.

2 APPLICATION

This edition of AS 1548 supersedes all previous editions of the Standard, however this does not imply that material manufactured to previous editions is now invalid, or that designs using previous grades are invalidated. It is intended that existing designs, procedures, specifications, materials etc. need not be altered in response to the publication of the new edition of this Standard. The equivalency of current and previous grades of steel to AS 1548, and the application of current grades to existing designs, specifications, procedures, etc. is described in Appendix B.

3 REFERENCED DOCUMENTS

The following documents are referred to in this Standard.

AS

- | | |
|--------|---|
| 1210 | Pressure vessels |
| 1391 | Metallic materials—Tensile testing at ambient temperature |
| 1544 | Methods for impact tests of metals |
| 1544.2 | Part 2: Charpy V-notch |
| 1710 | Non-destructive testing—Ultrasonic testing of carbon and low alloy steel plate and universal sections—Test methods and quality classification |
| 1733 | Methods for the determination of grain size in metals |
| 2291 | Metallic materials—Tensile testing at elevated temperatures |
| 2706 | Numerical values—Rounding and interpretation of limiting values |

AS/NZS

- | | |
|------|--|
| 1050 | Methods for the analysis of iron and steel (all parts) |
| 1575 | Tolerances for flat-rolled steel products |
| 3572 | Pressure equipment—Welding and brazing qualification |

ISO

- | | |
|--------|---|
| 2566 | Steel—Conversion of elongation values |
| 2566-1 | Part 1: Carbon and low alloy steels |
| 9328 | Steel flat products for pressure purposes—Technical delivery conditions |
| 9328-2 | Part 2: Non-alloy and alloy steels with specified elevated temperature properties |