

Australian Standard™

Refractory bricks and shapes

Part 3: High alumina

Currently in preview, click buy full version

This Australian Standard was prepared by Committee MN-007, Refractories and Refractory Materials. It was approved on behalf of the Council of Standards Australia on 14 March 2003 and published on 25 March 2003.

The following are represented on Committee MN-007:

Australian Ceramic Society
Australasian Institute of Mining and Metallurgy
Australian Aluminium Council
Bureau of Steel Manufacturers of Australia
CSIRO—Manufacturing and Infrastructure Technology
Institute of Refractories Engineers
Refractories Manufactur

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02457.

Australian Standard™

Refractory bricks and shapes

Part 3: High alumina

Originated as AS 2778—1985.
Previous edition AS 1617.3—1993.
Second edition 2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5146 6

PREFACE

This Standard was prepared by Standards Australia Committee MN-007, Refractories and Refractory Materials to supersede AS 1617.3—1993.

This Standard refers only to the main high-alumina refractory types produced by the Australian refractory industry and was originally developed from a survey of refractories and available raw materials used by that industry.

This Standard is a companion Standard to AS 1617.4, *Refractory bricks and shapes, Part 4: Silica* and AS 1617.5, *Refractory bricks and shapes, Part 5: Magnesite, chrome*.

It is emphasized that the assignment of certain AQL values is included in this Standard to provide guidance to the quality of the bricks/shapes specified herein. Users are entitled to specify other AQL values appropriate to the end use of the product, but any corresponding adjustments to the physical requirements must be in accordance with the quality specified herein.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 MATERIALS	3
5 CLASSIFICATION	3
6 DIMENSIONS	4
7 ALUMINA CONTENT	4
8 PHYSICAL REQUIREMENTS	4

STANDARDS AUSTRALIA

Australian Standard Refractory bricks and shapes

Part 3: High alumina

1 SCOPE

This Standard specifies requirements for machine-made high alumina refractory bricks and shapes.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- | | |
|---------|---|
| 1618 | Dimensions and preferred sizes for refractory bricks |
| 1774 | Refractories and refractory materials—Physical test methods |
| 1774.1 | Method 1: Determination of cold compressive strength |
| 1774.3 | Method 3: Determination of cold modulus of rupture |
| 1774.5 | Method 5: The determination of density, porosity and water absorption |
| 1774.13 | Method 13: Permanent dimensional change |
| 2497 | Procedures for acceptance testing of refractory products |
| 2497.1 | Part 1: Batch procedure |
| 2503 | Refractories and refractory materials—Chemical analysis |
| 2503.3 | Part 3: High alumina materials |
| 2780 | Refractories and refractory materials—Glossary of terms |

3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2780 and that below apply.

3.1 High alumina refractory

A general name for all alumina-silicate refractories having an alumina content higher than that of pure, calcined kaolin, i.e. greater than 46% by mass.

4 MATERIALS

The bricks and shapes, classified in accordance with Table 1, shall be produced essentially from the predominant raw materials listed in Table 1.

5 CLASSIFICATION

The bricks and shapes are classified on the basis of the—

- predominant raw material;
- alumina content; and
- bond, in accordance with Table 1.