

AS 1627.6:2025



STANDARDS
Australia



Metal finishing — Preparation and pretreatment of surfaces

Part 6: Phosphate and chromate conversion treatment of metals



currently in preview, click buy full version

AS 1627.6:2025

This Australian Standard™ was prepared by MT-009, Metal Finishing. It was approved on behalf of the Standards Australia's Standards Development and Accreditation Committee on 06 February 2025.

This Standard was published on 21 March 2025.

The following are represented on Committee MT-009:

- Australasian Corrosion Association Incorporated
- Australasian Institute of Surface Finishing
- Australian Aluminium Council
- Australian Chamber of Commerce and Industry
- Australian Industry Group
- Australian Paint Manufacturers Federation
- Bureau of Steel Manufacturers of Australia
- CSIRO
- Engineers Australia
- Galvanizers Association of Australia
- Materials Australia
- National Painting and Decorating Institute

This Standard was issued in draft form for comment as DR AS 1627.6:2024.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76175 065 6

Metal finishing — Preparation and pretreatment of surfaces

Part 6: Phosphate and chromate conversion treatment of metals

First published as AS CK9.6—1968.
Revised and redesignated AS 1627.6—1977.
Second edition 1994.
Previous edition 2003.
Fourth edition 2025.

© Standards Australia Limited 2025

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard has been prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-009, Metal Finishing, to supersede AS 1627.6-2003, *Metal finishing—Preparation and pretreatment of surfaces Part 6: Chemical conversion treatment of metals*.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this document is to specify requirements and procedures for chemical coatings for ferrous and non-ferrous metals and for chromate conversion coatings for aluminium, magnesium, zinc and their alloys.

The major changes in this edition are as follows:

- (a) Change of title to reflect the 2 types of conversion treatment covered in this document.
- (b) General revision of text with minimal changes to technical requirements.

The terms “normative” and “informative” are used in Standards to define the application of the appendices to which they apply. A “normative” appendix is an integral part of a Standard, whereas an “informative” appendix is only for information and guidance.

Contents

Preface	ii
Introduction	v
Section 1 Scope and general	1
1.1 Scope	1
1.2 Normative references	1
1.3 Terms and definitions	1
1.4 New designs and innovations	2
Section 2 Phosphate conversion treatment	3
2.1 Scope of section	3
2.2 Coating classification	3
2.2.1 Coatings for iron and steel	3
2.2.2 Coatings for non-ferrous metals	3
2.3 Requirements for phosphate coatings	3
2.3.1 General	3
2.3.2 Coating mass	4
2.3.3 Freedom from corrosive residues	4
2.3.4 Resistance to corrosion	4
2.4 Methods of application	5
2.4.1 General	5
2.4.2 Surface preparation	5
2.4.3 Phosphate treatment	5
2.4.4 Rinsing	5
2.4.5 Staining	6
2.4.6 Drying	6
2.4.7 Treatment of creviced component	6
2.4.8 Treatment of composite articles	6
2.4.9 Treatment of high tensile steels	6
2.4.10 Coating	7
Section 3 Chromate conversion treatment of aluminium, magnesium, zinc and their alloys	8
3.1 Scope of section	8
3.2 Coating classification	8
3.3 Requirements for chromate coatings	8
3.3.1 General	8
3.3.2 Test specimens and sampling	8
3.3.3 Coating mass	9
3.3.4 Adhesion	9
3.3.5 Corrosion resistance of chromate coating on aluminium	9
3.3.6 Coating identification	9
3.4 Methods of application	10
3.4.1 Surface preparation	10
3.4.2 Method of application of chromate coatings	10
3.4.3 Rinsing and drying	10
Appendix A (informative) Purchasing guidelines	11
Appendix B (normative) Test methods to determine phosphate coating mass	12
Appendix C (normative) Test method to determine the freedom of phosphate coatings from corrosive residues	16
Appendix D (normative) Test methods to determine corrosion resistance of phosphate coatings	17
Appendix E (normative) Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement	19

Appendix F (normative) Determination of chromate coating mass on aluminium and its alloys	22
Appendix G (informative) Qualitative testing of the composition of chromate coatings	25
Appendix H (informative) Chromate treatment sequence options	27
Bibliography	28

Currently in preview, click buy full version

Introduction

Phosphate conversion coatings are produced by treatment with solutions containing the relevant dihydrogen orthophosphates. These coatings are applied principally to ferrous materials, aluminium and zinc. The coating mass per unit area and the apparent density are dependent on —

- (a) the base material and its surface condition;
- (b) the previous mechanical and chemical treatment of the base material; and
- (c) the processing conditions for phosphating.

All phosphate conversion coatings are porous but can be sealed to a substantial degree by appropriate after-treatment.

Chromate and chromium-free conversion coatings are applied to aluminium, magnesium, zinc and their alloys to retard corrosion, as a base for organic films including paints, powder coatings, plastics and adhesives, and as a protective coating having a low electrical contact resistance.

NOTES

Currently in preview, click buy full version

Australian Standard®

Metal finishing — Preparation and pretreatment of surfaces Part 6: Phosphate and chromate conversion treatment of metals

Section 1 Scope and general

1.1 Scope

This document specifies requirements and procedures for the chemical conversion treatment of metals usually before the application of a suitable organic protective coating.

This document covers —

- (a) phosphate conversion coatings for ferrous and non-ferrous metals; and
- (b) chromate conversion coatings for aluminium, magnesium, zinc and their alloys.

NOTE See [Appendix A](#) for information to be supplied by the purchaser at the time of enquiry or order.

This document does not cover —

- (i) conversion coatings for electroplated work (refer to AS 1789);
- (ii) chromium free coatings (refer to the supplier); or
- (iii) conversion coatings based on chemistries other than phosphates and chromates.

1.2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document.

NOTE Documents referenced for informative purposes are listed in the Bibliography.

AS 1580.408.4, *Paints and related materials—Methods of test, Method 408.4: Adhesion (cross-cut)*

AS 2331.3.1, *Methods of test for metallic and related coatings, Method 3.1: Corrosion and related property tests—Neutral salt spray (NSS test)*

AS 2483, *Metal finishing—Recommended sampling plans for the inspection and testing of coatings*

1.3 Terms and definitions

For this document, the definitions given in AS 4108 and the following apply.

1.3.1

chromate coatings, non-rinsed

chromate coatings that are dried immediately after the chromating step without receiving a water rinse

Note 1 to entry: This type of coating is typically used on long coils of aluminium sheet stock or zinc-coated coil that receives an immediate subsequent paint or adhesive coating. It is sometimes referred to as coil coating.

1.3.2

chromate coatings, rinsed

chromate coatings that are rinsed in water before drying

Note 1 to entry: This type of coating is typically applied to extruded aluminium fabricated parts and castings and to zinc and magnesium fabricated parts and castings.