

Australian Standard[®]

LEAD ALLOYS

**Part 3—DETERMINATION OF
HIGH CONCENTRATIONS OF
ANTIMONY IN LEAD ALLOYS
CONTAINING NOT MORE THAN
2.5 PERCENT ARSENIC AND
1.0 PERCENT COPPER—
TITRIMETRIC METHOD**

This Australian standard was prepared by Committee CH/10—Analysis of Metals under the direction of Chemical Standards Board. It was approved on behalf of the Council of the Standards Association of Australia on 24 February 1987 and published on 4 May 1987.

The following interests are represented on Committee CH/10:

- Aluminium Development Council
- Australasian Institute of Mining and Metallurgy
- Australian Lead Development Association
- Australian Mineral Development Laboratories
- Australian Tin Information Centre
- Australian Zinc Development Association
- Bureau of Steel Manufacturers of Australia
- Confederation of Australian Industry
- Copper Technical Data Centre
- Department of Defence
- Electricity Supply Association of Australia
- Metal Trades Industry Association of Australia
- National Association of Testing Authorities
- Railways of Australia Committee
- Royal Australian Chemical Institute

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard' which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

First published	1975
Second edition	1987

This standard was issued in draft form for comment as DR 85299.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1671.3—1987

Lead alloys

Part 3: Determination of high concentrations of antimony in lead alloys containing not more than 2.5 percent arsenic and 1.0 percent copper—Titrimetric method

RECONFIRMATION NOTICE

Technical Committee CH-010 has reviewed the content of this publication, and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 31 July 2016.

The following are represented on Technical Committee CH-010:

Australian Aluminium Council
Bureau of Steel Manufacturers of Australia
International Copper Association Australia
International Precious Metals Institute
National Association of Testing Authorities Australia

NOTES

Currently in preview, click buy full vers.

PREFACE

This edition of this standard was prepared by the Association's Committee on the Analysis of Metals under the direction of the Chemical Standards Board. It supersedes AS 1671.3—1975, Methods for the Analysis of Lead Alloys, Higher Concentration Antimony in Lead and White Metal Alloys Containing Not More Than 2.5 percent Arsenic and 1.0 percent Copper (Volumetric Method).

CONTENTS

1	SCOPE	4
2	APPLICATION	4
3	REFERENCED DOCUMENTS	4
4	PRINCIPLE	4
5	REAGENTS	4
6	APPARATUS	4
7	SAMPLING	4
8	PROCEDURE	4
9	CALCULATION	5
10	PRECISION	5
11	ACCEPTANCE OF ANALYTICAL VALUES	5
12	TEST REPORT	6
APPENDICES		
A	STANDARDIZATION OF POTASSIUM BROMATE SOLUTIONS	7
B	NOTES ON THE SAMPLING TECHNIQUES USED DURING THE REPRODUCIBILITY TRIAL TESTING	8

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
LEAD ALLOYS

**PART 3—DETERMINATION OF HIGH CONCENTRATIONS OF
ANTIMONY IN LEAD ALLOYS CONTAINING NOT MORE THAN
2.5 PERCENT ARSENIC AND 1.0 PERCENT COPPER—
TITRIMETRIC METHOD**

1 SCOPE. This standard sets out a titrimetric method for the determination of antimony in lead alloys.

2 APPLICATION. The method is applicable to lead alloys with antimony contents in the range 2.0 to 27.0 percent and containing not more than 2.5 percent arsenic and 1.0 percent copper.

NOTE: For samples containing greater than 1.0 percent copper, an additional amount of copper (as copper-sulphate solution 5.3.3)) equivalent to the copper present should be added to calibration solutions after sulphuric acid addition.

3 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 2162	Code of Practice for the Use of Volumetric Glassware
AS 2164	One-mark Volumetric Flasks
AS 2165	Burettes and Bulb Burettes
AS 2166	One-mark Pipettes
AS 2534	Lead and Lead Alloys—Sampling and Preparation of Samples for Chemical Analysis
AS 4237	Report on Reproducibility of Methods of Chemical Analysis Used in the Iron and Steel Industry.

4 PRINCIPLE. Antimony is reduced to the trivalent state with sodium sulphite in sulphuric acid/hydrochloric acid medium and determined by potassium bromate titration.

5 REAGENTS.

5.1 General requirements. During the analysis, only reagents of recognized analytical reagent grade, and only distilled water or water of equivalent purity, shall be used.

5.2 Solids.

5.2.1 Antimony. Purity not less than 99.99 percent.

5.2.2 Lead. Purity not less than 99.99 percent and containing less than 5 µg Sb/g.

5.2.3 Sodium sulphite (anhydrous).

5.3 Solutions.

5.3.1 Hydrochloric acid (ρ₂₀ 1.16 g/mL).

5.3.2 Sulphuric acid (ρ₂₀ 1.84 g/mL).

5.3.3 Copper sulphate solution (5 g/L). Dissolve 0.5 g of copper sulphate pentahydrate (CuSO₄·5H₂O) in water, dilute to 100 mL and mix.

5.3.4 Methyl orange indicator. Dissolve 0.5 g of methyl orange in about 50 mL of water. Filter, dilute to 100 mL and mix.

5.4 Standard solutions.

5.4.1 Potassium bromate solution. Weigh 1.3917 ± 0.0001 g of potassium bromate (KBrO₃) previously dried at 105° to 110°C to constant mass. Dissolve in water, transfer to a 1 L volumetric flask, dilute to volume and mix. This solution shall be standardized by the procedure in Appendix A prior to use.

5.4.2 Potassium bromate solution. Weigh 2.7834 ± 0.0001 g of potassium bromate (KBrO₃) previously dried at 105° to 110°C to constant mass. Dissolve in water, transfer to a 1 L volumetric flask, dilute to volume and mix. This solution shall be standardized by the procedure in Appendix A prior to use.

6 APPARATUS.

6.1 Glassware. Grade A volumetric glassware shall be used throughout. Pipettes shall comply with AS 2166 and burettes with AS 2165. Use of volumetric glassware shall be in accordance with AS 2162.

6.2 Analytical balance. Capable of weighing accurately to 0.0001 g.

7 SAMPLING. Sampling shall be in accordance with AS 2534.

NOTES:

- The tendency of most lead and tin alloys to segregate should be stressed and care should be taken to avoid a biased analysis caused by sample segregation.
- Adhering contamination should be cleaned from all surfaces of the sample pieces (see Appendix B).
- Where hacksaw sampling produces a mixture of coarse and fine particles, they should be screened to separate the coarse and fine fractions. These should then be weighed to determine the proportion of the fractions. Suitable masses of these sized fractions should be combined for the assay samples.
- Alternatively, for antimonial-lead alloys containing in excess of 10 percent antimony, it is recommended that a molten sample be chill cast in a suitable iron mould to produce two or four prong pin samples. The diameter of the pins should be 6 mm and the length of the pins should be approximately 50 mm below the lug of the metal.

To obtain the desired mass of sample for analysis, snip approximately 5 mm from the bottom of a pin. File a sample from the clean edge of the remaining pin, collecting the filings on a clean sheet of sample paper. When sufficient sample has been collected, pass a magnet over the sample before weighing. Transfer all filings from the sample sheet to the balance pan. This is essential as segregation can occur in filings of different particle size. A clean, sharp 200 mm flat bastard file is a suitable tool for this operation.