

Australian Standard[®]

Copper

**Part 2: Determination of copper
content—Electrogravimetric method**

This Australian Standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of Standards Australia on 9 May 1997 and published on 5 July 1997.

The following interests are represented on Committee CH/10:

AMDEL

Australasian Institute of Mining and Metallurgy

Australasian Railway Association

Australian Aluminium Council

Australian Chamber of Commerce and Industry

Australian Chamber of Manufactures

Bureau of Steel Manufacturers of Australia

Copper Technical Data Centre, Australia

Metal Trades Industry Association

National Association of Testing Authorities Australia

The Royal Australian Chemical Institute

University of New South Wales

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest editions and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard[®]

Copper

**Part 2: Determination of copper
content—Electrogravimetric method**

Originated as AS K208.1—1970 (withdrawn July 1996).
Revised and redesignated as AS 1696.2—1997.

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/10, Analysis of Metals to supersede AS K208.1—1970.

The objective of this Standard is to provide an electrogravimetric method for the determination of copper content in high grade copper (>97%).

This Standard is the result of a consensus among Australia and New Zealand representatives of the Joint Committee to produce it as an Australian Standard.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 PRINCIPLE	3
4 REAGENTS	3
5 APPARATUS	4
6 SAMPLING	5
7 PROCEDURE	5
8 CALCULATION OF RESULTS	7
9 PRECISION	7
10 ACCEPTANCE OF ANALYTICAL VALUES	8
11 TEST REPORT	8

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Copper

Part 2: Determination of copper content—Electrogravimetric method

1 SCOPE This Standard sets out an electrogravimetric method for the determination of copper in blister, anode and high grade copper (copper content >97%). The method is particularly applicable in situations where impurities would normally interfere with the electrode deposition of copper.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 2134 Recommended practice for chemical analysis by atomic absorption spectrometry
- 2134.1 Part 1: Flame atomic absorption spectrometry
- 2162 Verification and use of volumetric apparatus
- 2162.1 Part 1: General—Volumetric glassware
- 2164 Laboratory glassware—One-mark volumetric flasks
- 2166 One-mark pipettes
- 2614 Copper and copper alloys—Sampling for chemical analysis and electrical resistivity
- 2850 Chemical analysis—Interlaboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct

ISO

- 3696 Water for analytical laboratory use—Specification and test methods

3 PRINCIPLE The copper sample is dissolved in nitric acid and arsenic, antimony, selenium and tellurium are oxidized to their higher oxidation states. Silver is removed as silver chloride. Bismuth is removed by coprecipitating on hydrated manganese oxide. Copper is then determined by electrode deposition.

4 REAGENTS

4.1 General requirements Except where specified otherwise, only reagents of recognized analytical grade and Type 2 water as specified in ISO 3696 shall be used. The purity of each metal and reagent used to prepare the standard solutions shall be greater than 99.99%.

4.2 Solutions

4.2.1 Nitric acid (ρ_{20} 1.42 g/mL)

4.2.2 Nitric acid (1 + 3) Slowly add 25 mL of nitric acid (4.2.1) to 75 mL of water while stirring continuously.

4.2.3 Ammonium hydroxide solution (ρ_{20} 0.88 g/mL)

4.2.4 Potassium persulfate