

Australian Standard™

AS 1774.22

Refractories and refractory materials—Physical test methods

Method 22: Refractory mortar—Test methods

PREFACE

This Standard was prepared by the Standards Australia Committee MN/7, Refractories and Refractory Materials as a revision of AS 1774.22—1985, *Methods for physical testing of refractories and refractory materials*, Method 22: *Bonding strength of refractory mortar*.

In the preparation of this Standard cognizance was taken of BS 1902.11:1990 *Methods of testing refractory materials*, Part 11: *Refractory mortars and putties* and GB 5024.1—85 *Test methods for refractory mortars*.

The objective of this revision is to provide a suite of tests for the evaluation of refractory mortars.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	3
1.2 REFERENCED DOCUMENTS.....	3
1.3 DEFINITIONS.....	3
1.4 SAFETY.....	3
1.5 GENERAL APPARATUS.....	3
1.6 PREPARATION OF MORTAR.....	4
SECTION 2 DETERMINATION OF CONSISTENCY	
2.1 GENERAL.....	5
2.2 PENETROMETER METHOD.....	5
2.3 TAP FLOW METHOD.....	7
SECTION 3 DETERMINATION OF TROWELABILITY	
3.1 SCOPE.....	10
3.2 APPARATUS.....	10
3.3 PROCEDURE.....	10
3.4 TEST REPORT.....	10
SECTION 4 DETERMINATION OF WATER RETENTION	
4.1 SCOPE.....	11
4.2 APPARATUS.....	11
4.3 PROCEDURE.....	11
4.4 TEST REPORT.....	11



SECTION 5 DETERMINATION OF JOINT STIFFENING TIME	
5.1	PRINCIPLE 12
5.2	APPARATUS 12
5.3	SAMPLING 12
5.4	PROCEDURE 12
5.5	TEST REPORT 13
SECTION 6 DETERMINATION OF BONDING STRENGTH	
6.1	PRINCIPLE 14
6.2	APPARATUS 14
6.3	SAMPLING OF TEST MORTAR 14
6.4	PREPARATION OF TEST SPECIMEN 14
6.5	FIRING PROCEDURE 15
6.6	TEST PROCEDURE 15
6.7	TEST REPORT 15
SECTION 7 DETERMINATION OF COLD SHEAR BONDING STRENGTH	
7.1	SCOPE 16
7.2	APPARATUS 16
7.3	SAMPLING AND PREPARING SPECIMENS 16
7.4	PROCEDURE 17
7.5	CALCULATIONS 18
7.6	TEST REPORT 18
SECTION 8 DETERMINATION OF REFRACTORINESS BY PIER TEST	
8.1	PRINCIPLE 19
8.2	APPARATUS 19
8.3	PREPARATION OF MORTAR 19
8.4	TEST PROCEDURE 19
8.5	TEST REPORT 20
SECTION 9 SIEVE ANALYSIS 21	
SECTION 10 DETERMINATION OF PERMANENT DIMENSIONAL CHANGE	
10.1	SCOPE 22
10.2	PRINCIPLE 22
10.3	APPARATUS 22
10.4	PREPARATION OF MORTAR 22
10.5	PROCEDURE 22
10.6	CALCULATIONS 23
10.7	TEST REPORT 24

METHOD

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard sets out methods for the preparation and testing of specimens of refractory mortars for determining a range of properties.

1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1774	Refractories and refractory materials—Physical test methods
1774.3	Method 3: Determination of cold modulus of rupture
1774.10	Method 10: Pyrometric cone equivalent (refractoriness)
1774.19	Method 19: The determination of sieve analysis and water content
1774.30	Method 30: Drying and firing schedules
2243	Safety in laboratories (series)
2701	Methods of sampling and testing mortar for masonry constructions
2701.7	Part 7: Method for determination of water retention
2780	Refractories and refractory materials—Glossary of terms

1.3 DEFINITIONS

For the purpose of this Standard, the definitions in AS 2780 apply.

1.4 SAFETY

This Standard may involve hazardous materials, operations, and equipment. This Standard does not purport to address the safety problems associated with its use. It is the responsibility of the user of this Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Reference should be made to relevant parts of AS 2243.

1.5 GENERAL APPARATUS

1.5.1 Balance

A weighing device capable of weighing at least 5 kg to the nearest 10 g.

1.5.2 Drying oven

A fan-forced, ventilated oven capable of maintaining a temperature of $110 \pm 5^\circ\text{C}$.

1.5.3 Mixer

A planetary or paddle mixer having the casing and blades constructed of a material that is inert to the materials being mixed.

1.5.4 Spacing rods

Spacing rods which are made of corrosion resistant metal, 2.00 ± 0.05 mm in thickness, and of appropriate length.