

Australian Standard[®]

**Metallic materials — Brinell
hardness test**

This Australian Standard was prepared by Committee MT/6, Mechanical Testing of Metals. It was approved on behalf of the Council of Standards Australia on 21 June 1990 and published on 10 December 1990.

The following interests are represented on Committee MT/6:

Aluminium Development Council
Bureau of Steel Manufacturers of Australia
CSIRO, Division of Applied Physics
Confederation of Australian Industry
Department of Defence
Federal Chamber of Automotive Industries
Metal Trades Industry Association of Australia
National Association of Testing Authorities, Australia
Railways of Australia Committee
Society of Automotive Engineers—Australasia
University of Sydney
University of Wollongong

Additional interests participating in preparation of Standard:

Calibrating organizations
Testing and research organizations

Review of Australia Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic revision and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

All details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 87212.

Australian Standard[®]

**Metallic materials—Brinell
hardness test**

AS 1816—1990 first published in part as B81—1941 (endorsement of BS 240—1937 without amendment). AS B81—1941 revised and redesignated AS B81.1—1955 (endorsement of BS 240—1937 with amendment). Second edition 1963 (endorsement of BS 240.1—1962 with amendment). AS B81.1—1963 and redesignated AS 1816.1—1977. AS B81.2 first published 1954 (endorsement of BS 240.2—1950 without amendment). Second edition 1968. AS B81.2—1968 revised and redesignated AS 1816.2—1976. AS 1816.1—1977 and AS 1816.2—1976 revised, amalgamated and redesignated AS 1816—1990.

PREFACE

This Standard was prepared under the direction of the Standards Australia Committee on Mechanical Testing of Metals to supersede AS 1816, *Method for Brinell hardness test, Part 1 — 1977: Testing of metals*, and Part 2 — 1976: *Calibration of the testing machine*.

In this edition, the testing and calibration requirements have been combined into the one Standard for simplification and the avoidance of duplication.

This edition was prepared at the request of the National Association of Testing Authorities, Australia to alleviate problems associated with calibration in relation to cost, adequacy and range of hardness blocks available for user checks.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 DEFINITIONS	4
1.4 PRINCIPLE OF TEST	4
1.5 DESIGNATION OF BRINELL HARDNESS	5
1.6 TABLES OF HARDNESS VALUES	5
1.7 HARDNESS CONVERSIONS	5
SECTION 2 TESTING OF METALS	
2.1 SCOPE OF SECTION	6
2.2 RELATION OF FORCE TO BALL DIAMETER	6
2.3 TESTING MACHINE	6
2.4 INDENTER	7
2.5 MEASURING APPARATUS	7
2.6 SUPPORT OF TEST PIECE	7
2.7 PERFORMANCE OF MACHINE	7
2.8 MAINTENANCE OF THE TESTING MACHINE BY THE USER	7
2.9 TEST PIECE	8
2.10 TEST PROCEDURE	9
2.11 RECORD OF TEST RESULTS	10
2.12 TEST REPORT	11
SECTION 3 COMPLETE CALIBRATION OF THE TESTING MACHINE	
3.1 GENERAL	12
3.2 PRELIMINARY INSPECTION	12
3.3 INDENTING FORCES	12
3.4 CALIBRATION OF BALLS	12
3.5 MEASURING APPARATUS	12
3.6 PERFORMANCE TEST	13
3.7 RECORD OF RESULTS	13
3.8 REPORT OF COMPLETE CALIBRATION	13
SECTION 4 PARTIAL CALIBRATION OF THE TESTING MACHINE	
4.1 GENERAL	14
4.2 PRELIMINARY INSPECTION	14
4.3 INDENTING PROCEDURE	14
4.4 ASSESSMENT OF PERFORMANCE	14
4.5 RECORD OF RESULTS	15
4.6 REPORT OF PARTIAL CALIBRATION	15
SECTION 5 CALIBRATION OF STANDARD HARDNESS BLOCKS	
5.1 GENERAL	16
5.2 REQUIREMENTS FOR STANDARD HARDNESS BLOCKS	16
5.3 CALIBRATION OF STANDARD HARDNESS BLOCKS	16
5.4 STANDARDIZING MACHINE	17
SECTION 6 CALIBRATION OF BALL INDENTERS	
6.1 GENERAL	18
6.2 SURFACE CONDITION	18
6.3 DIAMETER	18
6.4 HARDNESS	18
APPENDIX A TABLES OF BRINELL HARDNESS VALUES	19

STANDARDS AUSTRALIA

Australian Standard

Metallic materials—Brinell hardness test

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE This Standard sets out methods for measuring the hardness of metals and metal products on scales of Brinell hardness. It includes requirements for the installation and calibration of the testing machine, and recommendations for its maintenance by the user.

NOTE: In some Brinell hardness testing machines, the indentation measuring apparatus is integral with the machine. In others, the function of the machine is limited to the indenting process, the measurement of the indentation being made separately. It is acceptable, therefore, for the indenting process to be performed in a compression testing machine which has suitable indenter attachments and which can apply the appropriate force in accordance with this Standard.

This Standard does not preclude the use of portable hardness testing machines which meet those requirements of Section 2 which are appropriate to non-portable machines.

1.2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

1199 Sampling procedures and tables for inspection by attributes

1817 Method for Vickers hardness test

1817.1 Part 1: Testing of metals

2193 Methods for calibration and grading of force-measuring systems of testing machines

ISO

4964 Steel—Hardness conversions

1.3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

1.3.1 Calibration—all the operations for determining the values of the errors of a Brinell hardness testing machine (and, if necessary, for determining other metrological properties).

1.3.2 Calibrating authority—any approved person or organization qualified and equipped to perform the tests set out in Sections 3 or 4 or both.

NOTE: The National Association of Testing Authorities, Australia, registers laboratories for performance of these calibrations.

1.3.3 Hardness test blocks—metal blocks made by a manufacturer recognized by the National Association of Testing Authorities, for the purpose of maintaining surveillance of the performance of hardness testing machines between periodic calibrations.

NOTE: This Standard permits the alternative use of user test blocks (test blocks manufactured and checked by the user) for checking the hardness machine performance when using ball diameters of 5 mm and 10 mm (see Clause 2.8.3).

1.3.4 Standard hardness blocks—metal blocks having a calibration traceable to a national standard scale of hardness which is recognized by the Australian standardizing authority, for the purpose of verifying the performance of hardness testing machines.

1.3.5 Standardizing authority—an authority which maintains the standard of Brinell hardness.

NOTE: In Australia the standardizing authority is the CSIRO, Division of Applied Physics, National Measurement Laboratory.

1.3.6 Test piece—a prepared piece for testing made from a test specimen by some mechanical operation.

1.3.7 Test specimen—a portion of material or a single item taken from the test sample for applying a particular test.

NOTE: Brinell hardness tests can be made on test pieces or test specimens, the latter often being in the form of finished products or components.

1.4 PRINCIPLE OF TEST The test consists of pressing a hardened steel ball or tungsten carbide ball of diameter, D , into the surface of a test piece and measuring the diameter of the indentation, d , left in the surface after removal of the test force F . The theoretical depth of indentation is designated as h (see Figure 1.1.)

The steel ball is used for materials with a Brinell hardness not exceeding 450 HB.

The tungsten carbide ball is used for materials with a Brinell hardness not exceeding 650 HB.

NOTE: The values obtained using a steel ball or a tungsten carbide ball are significantly different for hardnesses above 350 HB.