

Australian Standard™

Austenitic cast iron

Currently in preview, click buy full version

This Australian Standard was prepared by Committee MT-001, Iron and Steel. It was approved on behalf of the Council of Standards Australia on 17 May 2002 and published on 4 June 2002.

The following interests are represented on Committee MT-001:

Australian Institute of Steel Construction
Australian Chamber of Commerce and Industry
Australian Industry Group
Australasian Railway Association
Australian Building Codes Board
Australian Foundry Institute
Bureau of Steel Manufacturers of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

Austenitic cast iron

Revised as AS G15—1969.
Previous edition AS 1833—1986.
Third edition 2002.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4533 4

PREFACE

This Standard was prepared by Standards Australia Committee MT-001, Iron and Steel to supersede AS 1833—1986, *Iron castings—Austenitic cast iron*.

The Standard is identical with and has been reproduced from ISO 2892:1973, *Austenitic cast iron*.

This Standard is one of a series of Standards covering the range of cast irons. The series comprises the following:

AS

1830	Grey cast iron
1831	Ductile cast iron
1832	Malleable cast iron
1833	Austenitic cast iron
2027	Wear resistant white cast iron
5049	Cast iron—Designation of microstructure of graphite

As this Standard is reproduced from an International Standard, the following applies:

- Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- In the source text, 'this International Standard' should read 'this Australian Standard'.
- A full point should be substituted for a comma when referring to a decimal marker.

References to International Standards should be replaced by Australian Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian Standard</i>	
ISO		AS	
R 83	Charpy impact test (U-notch) for steel	1544	Methods for impact tests on metals
		1544.3	Method 3: Charpy U-notch and keyhole notch
148	Steel—Charpy impact test (V-notch)	1544.2	Method 2: Charpy V-notch
R 945	Designation of microstructure of graphite in cast iron	—	

AUSTRALIAN STANDARD

Austenitic cast iron

0 INTRODUCTION

Austenitic cast irons are high alloy materials in which the metallic matrix has been rendered austenitic at ambient temperature by the use of alloying elements and in which the carbon is present predominantly as either flake or spheroidal graphite. Carbides are often also present, particularly in the high chromium grades.

Spheroidal graphite grades of austenitic cast iron have mechanical properties superior to those of the flake graphite types. Generally they exhibit superior resistance to heat and corrosion and have other physical properties which differ from those of the flake graphite types of similar basic composition.

Martensite may be present subject to an agreement between the manufacturer and the purchaser.

1 SCOPE AND FIELD OF APPLICATION

This International Standard relates to nine grades of flake graphite austenitic cast iron and eleven grades of spheroidal or nodular graphite austenitic cast iron intended for subsequent use in the manufacture of castings. These grades of material are based on chemical composition and mechanical properties.

2 REFERENCES

- ISO/R 83, *Charpy impact test (U-notch), for steel.*
 ISO 148, *Steel – Charpy impact test (V-notch).*¹⁾

1) At present at the stage of draft. (Revision of ISO/R 148.)

ISO/R 945, *Designation of the microstructure of graphite in cast iron.*

3 SYMBOLS AND ABBREVIATIONS

Each grade having a microstructure of flake graphite in accordance with Form I of ISO/R 945 is designated by the initial letter "L".

Each grade having a microstructure of spheroidal or nodular graphite in accordance with Form V and Form VI of ISO/R 945 is designated by the initial letter "S".

In each case the initial letter is followed by appropriately spaced chemical symbols and figures indicating the alloying elements and their approximate mean levels, as shown in the following examples:

Examples

- 1) L – Ni Cu Cr 15 6 3 (Refer to Table 1 for actual composition)
- 2) S – Ni Si Cr 20 5 2 (Refer to Table 2 for actual composition)

4 PRODUCTION

The method of producing austenitic cast irons is left to the discretion of the manufacturer, who should ensure that the property requirements, defined in this International Standard, are complied with for the grade of material required on the order.