

AS 1874—2000

Reconfirmed 2018

AS 1874

Australian Standard™

**Aluminium and aluminium
alloys—Ingots and castings**



Standards Australia

This Australian Standard was prepared by Committee MT/3, Aluminium and Aluminium Alloys. It was approved on behalf of the Council of Standards Australia on 15 February 2000 and published on 12 May 2000.

The following interests are represented on Committee MT/3:

Australasian Railway Association
Australian Aluminium Council
Australian Automobile Association
Australian Chamber of Commerce and Industry
Australian Window Association
New Zealand Manufacturers Federation
Society of Automotive Engineers—Australasia
Australian Automobile Association

Additional interests participating in the preparation of this Standard:

Non-ferrous foundries
Light metal consultants

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using the current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for the improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1874–2000

**Aluminium and aluminium
alloys–Ingots and castings**

RECONFIRMATION NOTICE

Major stakeholders of this publication have reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 29 August 2018.

NOTES

Currently in preview, click buy full vers.

Australian Standard™

**Aluminium and aluminium
alloys—Ingots and castings**

Originates as part of AS H49—1950 and AS H61—1961.
Previous edition AS 1874—1988.
Third edition 2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd

PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3306 9

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee MT/3, Aluminium and Aluminium Alloys, to supersede AS 1874—1988.

The objective of this revision is to upgrade the requirements for aluminium and aluminium alloy ingots and castings.

This Standard is the result of a consensus among Australian and New Zealand representatives on the Joint Committee to produce it as an Australian Standard.

During the preparation of this Standard cognizance was taken of the publication *Aluminium Standards and Data—Ingots and Castings*, published in 1997 by the Australian Aluminium Council. Cognizance was also taken of the following International, National and European Standards:

ISO 3522:1984	Cast aluminium alloys—Chemical composition and mechanical properties
BS 1490:1988	Aluminium and aluminium alloy ingots and castings for general engineering purposes
EN 1706:1998	Aluminium and aluminium alloys—Castings—Chemical composition and mechanical properties

Whereas the alloys contained in the above three Standards are similar to those listed in this Standard, Australian industry favours the use of designations of American origin rather than adopting the ISO and European designations which comprise chemical symbols and numbers.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 DESIGNATION	5
5 FREEDOM FROM DEFECTS	5
6 RECLAMATION AND REPAIR OF CASTINGS	6
7 SHAPE AND DIMENSIONS OF CASTINGS	6
8 CHEMICAL COMPOSITION	6
9 MECHANICAL PROPERTIES OF CASTINGS (EXCLUDING PRESSURE DIE CASTINGS)	6
10 ADDITIONAL INSPECTION REQUIREMENTS FOR CASTINGS	6
11 PROVISION AND PREPARATION OF TEST SAMPLES	7
12 PREPARATION OF TEST PIECES	7
13 MECHANICAL TESTS	7
14 RETESTS	7
15 IDENTIFICATION	8
16 ROUNDING OF TEST RESULT VALUES	8
 APPENDICES	
A PURCHASING GUIDELINES	17
B ALLOY DESIGNATION SYSTEM AND REQUIREMENTS FOR THE MODIFICATION OF ORIGINAL ALLOYS	22
C TEMPER DESIGNATION	24
D RELATED COMPOSITION SPECIFICATIONS	26
E GUIDE TO THE SELECTION OF ALLOYS	27
F TYPICAL PHYSICAL PROPERTIES OF ALUMINIUM CASTING ALLOYS	34

STANDARDS AUSTRALIA

Australian Standard

Aluminium and aluminium alloys—Ingots and castings

1 SCOPE This Standard specifies requirements for aluminium ingots and aluminium alloy ingots and castings.

NOTE: Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in Appendix A.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

- 1391 Methods for tensile testing of metals
- 2062 Non-destructive testing—Penetrant testing of products and components
- 2612 Aluminium and aluminium alloys—Sampling for chemical and spectrochemical analysis
- 2706 Numerical values—Rounding and interpretation of limiting values
- 3719 Aluminium and aluminium alloys
- 3719.1 Part 1: Determination of iron—Spectrophotometric method
- 3719.2 Part 2: Determination of silicon—Gravimetric method

BS

- 1728 Methods for the analysis of aluminium and aluminium alloys (all parts)

ASTM

- E 34 Test methods for chemical analysis of aluminium and aluminium-base alloys
- E 227 Test method for optical emission spectrometric analysis of aluminium and aluminium alloys by the point-to-plane technique

3 DEFINITIONS For the purpose of this Standard, the definitions below apply.

3.1 Annealing—thermal treatment to soften metal by the removal of strain hardening resulting from cold working, by recrystallization and/or by coalescing precipitates from the solid solution.

3.2 Artificial ageing—a thermal treatment of an alloy carried out above room temperature to produce strengthening by precipitation of soluble constituents from a super-saturated solid solution. Also known as ‘precipitation heat treatment’.

3.3 Batch (ingot)—a series of ingots cast from a single uniform melt.

3.4 Cast (non-continuous melting)—the product of either one furnace melt, or a number of furnace melts where such are aggregated and mixed prior to sampling or pouring.

3.5 Cast (continuous melting)—the product of continuous melting when the contents of a melting/holding furnace are supplemented from time to time by the addition of metal to maintain an adequate bulk of liquid metal. A cast comprises up to 500 kg of metal poured.

3.6 Dressing (fettling)—the cleaning up of a casting by removing flashes and runners.

3.7 Ingot—a cast metal product prepared in a suitable form for remelting.